

# AEROSPACE MATERIAL SPECIFICATIONS

**AMS 5507**

SOCIETY OF AUTOMOTIVE ENGINEERS, Inc. 485 Lexington Ave., New York 17, N.Y.

Issued 1-15-63  
RevisedSTEEL SHEET, STRIP, AND PLATE, CORROSION AND HEAT RESISTANT  
17Cr - 13Ni - 2.5Mo (316L)

1. ACKNOWLEDGMENT: A vendor shall mention this specification number in all quotations and when acknowledging purchase orders.
2. APPLICATION: Primarily for parts and assemblies requiring both corrosion and heat resistance up to 1600 F (870 C). At high temperatures, strength of this steel is slightly higher than, and oxidation resistance is similar to, that of 18-8 types.

3. COMPOSITION:

|            |               |
|------------|---------------|
| Carbon     | 0.03 max      |
| Manganese  | 2.00 max      |
| Silicon    | 1.00 max      |
| Phosphorus | 0.040 max     |
| Sulfur     | 0.030 max     |
| Chromium   | 16.00 - 18.00 |
| Nickel     | 12.00 - 14.00 |
| Molybdenum | 2.00 - 3.00   |
| Copper     | 0.50 max      |

- 3.1 Check Analysis: Composition variations shall meet the requirements of the latest issue of AMS 2248.

4. CONDITION:

- 4.1 Sheet: Cold rolled, solution heat treated free from continuous carbide network, and descaled (No. 2D Finish).
  - 4.2 Strip: Cold rolled, solution heat treated free from continuous carbide network, and descaled (No. 1 Strip Finish).
  - 4.3 Plate: Hot rolled, solution heat treated, and descaled.

5. TECHNICAL REQUIREMENTS:

- 5.1 Tensile Properties:

|                        |             |
|------------------------|-------------|
| Tensile Strength, psi  | 100,000 max |
| Elongation, % in 2 in. |             |
| Nominal Thickness, in. |             |
| Up to 0.025, excl      | 40 min      |
| 0.025 in. and over     | 45 min      |

5.1.1 For widths 9 in. and over, tensile test specimens shall be taken with the axis perpendicular to the direction of rolling. For widths less than 9 in., tensile test specimens shall be taken with the axis parallel to the direction of rolling.

5.2 Bending: Material shall withstand, without cracking, bending at room temperature through the angle indicated below around a diameter equal to the bend factor times the nominal thickness of the material, with axis of bend parallel to the direction of rolling:

| Nominal Thickness<br>Inch | Type of Bend | Angle<br>deg, min | Bend Factor |
|---------------------------|--------------|-------------------|-------------|
| Up to 0.249, incl         | Free Bend    | 180               | 1           |
| Up to 0.249, incl         | V-Block      | 135               | 1           |
| Over 0.249 to 0.749, incl | Free Bend    | 90                | 1           |
| Over 0.249 to 0.749, incl | V-Block      | 135               | 2           |

6. QUALITY: Material shall be uniform in quality and condition, clean, sound, and free from foreign materials and from internal and external defects detrimental to fabrication or to performance of parts.

7. TOLERANCES: Unless otherwise specified, tolerances shall conform to all applicable requirements of the latest issue of AMS 2242.

8. REPORTS:

8.1 Unless otherwise specified, the vendor of the product shall furnish with each shipment three copies of a report of the results of tests for chemical composition of each heat in the shipment and the results of tests on each thickness from each heat to determine conformance to the tensile and bending requirements of this specification. This report shall include the purchase order number, heat number, material specification number, thickness, size, and quantity from each heat.

8.2 Unless otherwise specified, the vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, material specification number, contractor or other direct supplier of material, part number, and quantity. When material for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of material to determine conformance to the requirements of this specification, and shall include in the report a statement that the material conforms, or shall include copies of laboratory reports showing the results of tests to determine conformance.

9. IDENTIFICATION: Unless otherwise specified, each sheet, strip, and plate shall be marked, in the respective location indicated below, with AMS 5507, heat number, manufacturer's identification, and nominal thickness in inches. The characters shall be not less than 3/8 in. in height, shall be applied using a suitable marking fluid, and shall be capable of being removed in hot alkaline cleaning solution without rubbing. The markings shall have no deleterious effect on the material or its performance. The characters shall be sufficiently stable to withstand ordinary handling.