

AEROSPACE MATERIAL SPECIFICATIONS

SOCIETY OF AUTOMOTIVE ENGINEERS, Inc. 485 Lexington Ave., New York 17, N.Y.

AMS 5508A

Issued 1-15-57
Revised 1-31-64

STEEL SHEET, STRIP, AND PLATE, CORROSION AND MODERATE HEAT RESISTANT 13Cr - 2.0Ni - 3.0W

1. **ACKNOWLEDGMENT:** A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. **APPLICATION:** Primarily for parts and assemblies, such as shrouds, ducts, and cases, requiring oxidation resistance up to 1000 F (540 C). Creep strength and resistance to tempering of this steel are better than those of the common 13Cr type.

3. **COMPOSITION:**

	min	max
Carbon	0.15	0.20
Manganese	--	0.50
Silicon	--	0.50
Phosphorus	--	0.040
Sulfur	--	0.030
Chromium	12.00	14.00
Nickel	1.80	2.20
Tungsten	2.50	3.50
Molybdenum	--	0.50
Aluminum	--	0.15
Copper	--	0.50
Tin	--	0.05

- 3.1 **Check Analysis:** Composition variations shall meet the requirements of the latest issue of AMS 2248.

4. **CONDITION:**

- 4.1 **Sheet:** Hot rolled, annealed, and descaled, having a surface finish as close as possible to a commercial corrosion resistant steel No. 2D finish; standards for acceptance and rejection shall be as agreed upon by purchaser and vendor.
 - 4.2 **Strip:** Cold rolled, annealed, and descaled (No. 1 Strip Finish).
 - 4.3 **Plate:** Hot rolled, annealed, and descaled.

5. **TECHNICAL REQUIREMENTS:**

- 5.1 **Tensile Properties:**

	Tensile Strength, psi	150,000 max
Ø	Elongation, % in 2 in.	10 min

- 5.2 **Hardenability:** Material 0.375 in. and less in thickness and 0.375 in. thick specimens cut from thicker material shall be capable of meeting the following test:

Section 8.3 of the SAE Technical Board rules provides that: "All technical reports, specifications, and standards, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no liability on the part of the Society of Automotive Engineers, Inc. for any technical report, specification, or standard which may be found to conform to or be guided by any technical report, specification, or standard. The user is responsible for protecting themselves against infringement of patents which may apply to the subject matter. Prospective users of the report, specification, or standard are advised to view the full PDF of AMS 5508A at www.sae.org/standards/AMS/AMS5508A.pdf to view the full PDF of AMS 5508A.