



AEROSPACE MATERIAL

Society of Automotive Engineers, Inc.

400 COMMONWEALTH DRIVE, WARRENDALE, PA. 15096

SPECIFICATION

AMS 5512F

Superseding AMS 5512E

Issued 9-1-47

Revised 1-15-78

UNS S34700

STEEL SHEET, STRIP, AND PLATE, CORROSION AND HEAT RESISTANT
18Cr - 10.5Ni - (Cb+Ta) (SAE 30347)

1. SCOPE:

1.1 Form: This specification covers a corrosion and heat resistant steel in the form of sheet, strip, and plate.

1.2 Application: Primarily for parts and assemblies requiring both corrosion and heat resistance and especially when such parts and assemblies are welded during fabrication. Parts and assemblies requiring oxidation resistance up to approximately 1500°F (815°C), but useful at that temperature only when stresses are low.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2242 - Tolerances, Corrosion and Heat Resistant Steel and Iron Base Alloy Sheet, Strip, and Plate and Titanium and Titanium Alloy Sheet, Strip, and Plate

AMS 2248 - Chemical Check Analysis Limits, Wrought Heat and Corrosion Resistant Steels and Alloys

AMS 2350 - Standards and Test Methods

AMS 2371 - Quality Assurance Sampling of Corrosion and Heat Resistant Alloys, Wrought Products Except Forgings

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM A262 - Detecting Susceptibility to Intergranular Attack in Stainless Steels

ASTM A370 - Mechanical Testing of Steel Products

ASTM E353 - Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys

2.3 Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Federal Standards:

Federal Test Method Standard No. 151 - Metals; Test Methods

2.3.2 Military Standards:

MIL-STD-163 - Steel Mill Products, Preparation for Shipment and Storage

SAE Technical Board rules provide that: "All technical reports, including standards, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

3. TECHNICAL REQUIREMENTS:

- 3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E353, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other approved analytical methods:

	min	max
Carbon	--	0.08
Manganese	--	2.00
Silicon	0.50 -	1.00
Phosphorus	--	0.040
Sulfur	--	0.030
Chromium	17.00 -	19.00
Nickel	9.00 -	12.00
Columbium + Tantalum	10xC -	1.10
Molybdenum	--	0.75
Copper	--	0.50

- 3.1.1 Check Analysis: Composition variations shall meet the requirements of AMS 2248.

- 3.2 Condition: The product shall be supplied in the following condition:

- 3.2.1 Sheet: Cold rolled, solution heat treated, and descaled (No. 2D Finish).

- 3.2.2 Strip: Cold rolled, solution heat treated, and descaled unless solution heat treatment is performed in an atmosphere yielding a bright finish (No. 1 Strip Finish).

- 3.2.3 Plate: Hot rolled, solution heat treated, and descaled.

- 3.3 Properties: The product shall conform to the following requirements; tensile and bend testing shall be performed in accordance with ASTM A370:

- 3.3.1 Tensile Properties: Shall be as specified in Table I:

TABLE I

Nominal Thickness Inches	Tensile Strength psi, max	Elongation in 2 in. or 4D %, min
Over 0.002 to 0.003, incl	115,000	20
Over 0.003 to 0.004, incl	110,000	30
Over 0.004	105,000	40

TABLE I (SI)

Nominal Thickness Millimetres	Tensile Strength MPa, max	Elongation in 50 mm or 4D %, min
Over 0.051 to 0.076, incl	793	20
Over 0.076 to 0.102, incl	758	30
Over 0.102	724	40

- 3.3.2 Bending: Product 0.749 in. (19.02 mm) and under in nominal thickness shall withstand, without cracking, bending through the angle indicated below around a diameter equal to the bend factor times the nominal thickness of the product with axis of bend parallel to the direction of rolling. Only one type of test will be required in routine inspection; in case of dispute, results of tests using the V-block procedure shall govern.

Ø	Nominal Thickness		Type of Bend	Angle deg, min	Bend Factor
	Inch	(Millimetres)			
	Up to 0.249, incl	(Up to 6.32, incl)	Free Bend	180	1
	Up to 0.249, incl	(Up to 6.32, incl)	V-Block	135	1
	Over 0.249 to 0.749, incl	(Over 6.32 to 19.02, incl)	Free Bend	-90	1
	Over 0.249 to 0.749, incl	(Over 6.32 to 19.02, incl)	V-Block	135	2

- 3.3.2.1 Bend requirements for plate over 0.749 in. (19.02 mm) in nominal thickness shall be as agreed upon by purchaser and vendor.

- 3.3.3 Embrittlement: The product, after sensitizing treatment, shall meet the copper/copper sulfate/sulfuric acid test performed in accordance with ASTM A262, Practice E, without evidence of inter-crystalline surface attack and, after exposure, shall withstand bending as in 3.3.2.

- 3.4 Quality: The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from internal and external imperfections detrimental to usage of the product.

- 3.5 Tolerances: Unless otherwise specified, tolerances shall conform to all applicable requirements of AMS 2242.

4. QUALITY ASSURANCE PROVISIONS:

- 4.1 Responsibility for Inspection: The vendor of the product shall supply all samples and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to perform such confirmatory testing as he deems necessary to ensure that the product conforms to the requirements of this specification.

4.2 Classification of Tests:

- 4.2.1 Acceptance Tests: Tests to determine conformance to composition (3.1), tensile property (3.3.1), bending (3.3.2), and tolerance (3.5) requirements are classified as acceptance tests.

- 4.2.2 Periodic Tests: Tests to determine conformance to embrittlement (3.3.3) requirements are classified as periodic tests.

- 4.3 Sampling: Shall be in accordance with AMS 2371 and the following:

- 4.3.1 Specimens for tensile tests of widths 9 in. (229 mm) and over, shall be taken with the axis of the specimen perpendicular to the direction of rolling; for widths less than 9 in. (229 mm), specimens shall be taken with the axis parallel to the direction of rolling.

4.4 Reports:

- 4.4.1 The vendor of the product shall furnish with each shipment three copies of a report showing the results of tests for chemical composition of each heat and for tensile and bending properties of each size from each heat. This report shall include the purchase order number, heat number, material specification number and its revision letter, size, and quantity from each heat.

- 4.4.2 The vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, material specification number and its revision letter, contractor or other direct supplier of material, part number, and quantity. When material for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of material to determine conformance to the requirements of this specification, and shall include in the report a statement that the material conforms, or shall include copies of laboratory reports showing the results of tests to determine conformance.

- 4.5 Resampling and Retesting: Shall be in accordance with AMS 2371.

5. PREPARATION FOR DELIVERY:

- 5.1 Identification: Each sheet, strip, and plate shall be marked on one face, in the respective location indicated below, with AMS 5512F, heat number, manufacturer's identification, and nominal thickness. The characters shall be of such size as to be clearly legible, shall be applied using a suitable marking fluid, and shall be removable in hot alkaline cleaning solution without rubbing. The markings shall have no deleterious effect on the product or its performance and shall be sufficiently stable to withstand normal handling.

- 5.1.1 Flat Strip 6 In. (152 mm) and Under in Width: Shall be marked in one or more lengthwise rows of characters recurring at intervals not greater than 3 ft (914 mm).

- 5.1.2 Flat Sheet, Flat Strip Over 6 In. (152 mm) in Width, and Plate: Shall be marked in lengthwise rows of characters recurring at intervals not greater than 3 ft (914 mm), the rows being spaced not more than 6 in. (152 mm) apart and alternately staggered.

- 5.1.3 Coiled Sheet and Strip: Shall be marked near both the outside and inside ends of the coil; the markings shall be applied as in 5.1 or shall appear on a durable tag or label attached to the coil and marked with the information of 5.1. When the inside end of the coil is inaccessible, as when the product is wound on cores, the tag or label may be attached to the core.

5.2 Packaging:

- 5.2.1 The product shall be prepared for shipment in accordance with commercial practice and in compliance with applicable rules and regulations pertaining to the handling, packaging, and transportation of the product to ensure carrier acceptance and safe delivery. Packaging shall conform to carrier rules and regulations applicable to the mode of transportation.

- 5.2.2 For direct U.S. Military procurement, packaging shall be in accordance with MIL-STD-163, Level A or Level C, as specified in the request for procurement. Commercial packaging as in 5.2.1 will be acceptable if it meets the requirements of Level C.

6. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.

7. REJECTIONS: Material not conforming to this specification or to authorized modifications will be subject to rejection.

8. NOTES:

- 8.1 Marginal Indicia: The phi (ϕ) symbol is used to indicate technical changes from the previous issue of this specification.