

AEROSPACE MATERIAL SPECIFICATION

AMS 5514D
Superseding AMS 5514C

Issued 12-1-47
Revised 4-1-85

STEEL SHEET, STRIP, AND PLATE, CORROSION RESISTANT
18Cr - 11.5Ni (SAE 30305)
Solution Heat Treated

UNS S30500

1. SCOPE:

1.1 Form: This specification covers a corrosion-resistant steel in the form of sheet, strip, and plate.

1.2 Application: Primarily for parts manufactured by deep drawing or spinning and requiring corrosion resistance up to 800°F (425°C).

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2242 - Tolerances, Corrosion and Heat Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Sheet, Strip, and Plate
MAM 2242 - Tolerances, Metric, Corrosion and Heat Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Sheet, Strip, and Plate
AMS 2248 - Chemical Check Analysis Limits, Wrought Corrosion and Heat Resistant Steels and Alloys, Maraging and Other Highly-Alloyed Steels, and Iron Alloys
AMS 2350 - Standards and Test Methods
AMS 2371 - Quality Assurance Sampling of Corrosion and Heat Resistant Steels and Alloys, Wrought Products Except Forgings and Forging Stock

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

- 2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM A370 - Mechanical Testing of Steel Products

ASTM E353 - Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys

- 2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Federal Standards:

Federal Test Method Standard No. 151 - Metals; Test Methods

2.3.2 Military Standards:

MIL-STD-163 - Steel Mill Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

- 3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E353, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other analytical methods approved by purchaser:

	min	max
Carbon	--	0.12
Manganese	--	2.00
Silicon	--	1.00
Phosphorus	--	0.040
Sulfur	--	0.030
Chromium	17.00 - 19.00	
Nickel	10.00 - 13.00	
Molybdenum	--	0.75
Copper	--	0.75

- 3.1.1 Check Analysis: Composition variations shall meet the requirements of AMS 2248.

- 3.2 Condition: The product shall be supplied in the following condition:

- 3.2.1 Sheet and Strip: Cold rolled, solution heat treated, and, unless solution heat treatment is performed in an atmosphere yielding a bright finish, descaled having a surface appearance conforming to 3.2.1.1 or 3.2.1.2 as applicable.

- 3.2.1.1 Sheet: No. 2D finish.

- 3.2.1.2 Strip: No. 1 strip finish.

3.2.2 Plate: Hot rolled, solution heat treated, and descaled.

3.3 Properties: The product shall conform to the following requirements; tensile and bend testing shall be performed in accordance with ASTM A370:

3.3.1 Tensile Properties: Shall be as follows:

Tensile Strength, max	100,000 psi (690 MPa)
Elongation in 2 in. (50 mm) or 4D, min	
Nominal Thickness	
Under 0.025 in. (0.62 mm)	45%
0.025 in. (0.62 mm) and over	50%

3.3.2 Bending: Product 0.749 in. (18.75 mm) and under in nominal thickness shall withstand, without cracking, bending through the angle indicated below around a diameter equal to the bend factor times the nominal thickness of the product with axis of bend parallel to the direction of rolling. Only one type of test will be required in routine inspection; in case of dispute, results of tests using the V-block procedure shall govern.

Nominal Thickness		Type of Bend	Angle deg, min	Bend Factor
Inch	Millimetres			
Up to 0.249, incl	Up to 6.25, incl	Free Bend	180	1
Up to 0.249, incl	Up to 6.25, incl	V-Block	135	1
Over 0.249 to 0.749, incl	Over 6.25 to 18.75, incl	Free Bend	90	1
Over 0.249 to 0.749, incl	Over 6.25 to 18.75, incl	V-Block	135	2

3.3.2.1 Bending requirements for plate over 0.749 in. (18.75 mm) in nominal thickness shall be as agreed upon by purchaser and vendor.

3.4 Quality: The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.5 Tolerances: Unless otherwise specified, tolerances shall conform to all applicable requirements of AMS 2242 or MAM 2242.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

4.2 Classification of Tests: Tests to determine conformance to all technical requirements of this specification are classified as acceptance tests and shall be performed on each heat or lot as applicable.

4.3 Sampling: Shall be in accordance with AMS 2371.

4.4 Reports:

- 4.4.1 The vendor of the product shall furnish with each shipment a report showing the results of tests for chemical composition of each heat and for tensile and bending properties of each lot. This report shall include the purchase order number, heat number, AMS 5514D, size, and quantity from each heat.
- 4.4.2 The vendor of finished or semi-finished parts shall furnish with each shipment a report showing the purchase order number, AMS 5514D, contractor or other direct supplier of material, part number, and quantity. When material for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of material to determine conformance to the requirements of this specification and shall include in the report either a statement that the material conforms or copies of laboratory reports showing the results of tests to determine conformance.

4.5 Resampling and Retesting: Shall be in accordance with AMS 2371.

5. PREPARATION FOR DELIVERY:

- 5.1 Identification: Each sheet, strip, and plate shall be marked on one face, in the respective location indicated below, with AMS 5514D, heat number, manufacturer's identification, and nominal thickness. The characters shall be such size as to be legible, shall be applied using a suitable marking fluid, and shall be removable in hot alkaline cleaning solution without rubbing. The markings shall have no deleterious effect on the product or its performance and shall be sufficiently stable to withstand normal handling.
- 5.1.1 Flat Strip 6 In. (150 mm) and Under in Width: Shall be marked in one or more lengthwise rows of characters recurring at intervals not greater than 3 ft (900 mm).
- 5.1.2 Flat Sheet, Flat Strip Over 6 In. (150 mm) in Width, and Plate: Shall be marked in lengthwise rows of characters recurring at intervals not greater than 3 ft (900 mm), the rows being spaced not more than 6 in. (150 mm) apart and alternately staggered.
- 5.1.3 Coiled Sheet and Strip: Shall be marked near both the outside and inside ends of the coil; the markings shall be applied as in 5.1 or shall appear on a durable tag or label attached to the coil and marked with the information of 5.1. When the product is wound on cores, the tag or label may be attached to the core.