



AEROSPACE MATERIAL SPECIFICATION

AMS5546™**REV. E**

Issued	1964-01
Revised	1990-07
Noncurrent	1995-10
Reaf. Nonc.	2012-10
Stabilized	2017-04

Superseding AMS5546D

Steel Sheet and Strip, Corrosion and Moderate Heat Resistant
16.5Cr - 4.5Ni - 2.9Mo - 0.10N
Cold Rolled, Tempered

S35000

RATIONALE

AMS5546E stabilizes this document because it contains mature technology that is not expected to change and thus no further revisions are anticipated.

STABILIZED NOTICE

AMS5546E has been declared "STABILIZED" by the SAE AMS F Corrosion Heat Resistant Alloys Committee. This document was stabilized because this document contains mature technology that is not expected to change and thus no further revisions are anticipated. Previously this document was non-current. The last technical update of this document occurred in July, 1990. Users of this document should refer to the cognizant engineering organization for disposition of any issues with reports/certifications to this specification; including exceptions listed on the certification.

NOTE: In many cases, the purchaser may represent a sub-tier supplier and not the cognizant engineering organization.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2017 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

**SAE values your input. To provide feedback on this
Technical Report, please visit
<http://standards.sae.org/AMS5546E>**

1. SCOPE:

1.1 Form:

This specification covers a corrosion and moderate heat resistant steel in the form of sheet and strip.

1.2 Application:

Primarily for parts requiring high strength-to-weight ratio and oxidation resistance up to 800 °F (427 °C). Welding is generally not recommended because it destroys the effects of the cold work.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

2.1.1 Aerospace Material Specifications:

AMS 2242	Tolerances, Corrosion and Heat Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Sheet, Strip, and Plate
MAM 2242	Tolerances, Metric, Corrosion and Heat Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Sheet, Strip, and Plate
AMS 2248	Chemical Check Analysis Limits, Corrosion and Heat Resistant Steels and Alloys, Maraging and Other Highly-Alloyed Steels, and Iron Alloys
AMS 2371	Quality Assurance Sampling and Testing, Corrosion and Heat Resistant Steels and Alloys, Wrought Products and Forging Stock

2.2 ASTM Publications:

Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

ASTM A 370	Mechanical Testing of Steel Products
ASTM E 353	Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys

2.3 U.S. Government Publications:

Available from Standardization Documents Order Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.

2.3.1 Military Standards:

MIL-STD-163 Steel Mill Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E 353, by spectrochemical methods, or by other analytical methods acceptable to purchaser:

	min	max
Carbon	0.07	0.12
Manganese	0.50	1.25
Silicon	--	0.50
Phosphorus	--	0.040
Sulfur	--	0.030
Chromium	16.00	17.00
Nickel	4.00	5.00
Molybdenum	2.50	3.25
Nitrogen	0.07	0.13

3.1.1 Check Analysis: Composition variations shall meet the requirements of AMS 2248.

3.2 Condition:

The product shall be supplied in the following condition:

3.2.1 Sheet: Cold rolled, tempered, and descaled having a surface finish comparable to a commercial corrosion-resistant steel No. 2D finish (See 8.2).

3.2.2 Strip: Cold rolled, tempered, and unless tempering is performed in an atmosphere yielding a bright finish, descaled having a surface appearance comparable to a commercial corrosion-resistant steel No. 1 strip finish (See 8.2).

3.3 Properties:

The product shall conform to the following requirements; tensile and hardness testing shall be performed in accordance with ASTM A 370:

3.3.1 Tensile Properties: Shall be as specified in Table I.

TABLE I

Nominal Thickness Inch	Tensile Strength psi, min	Yield Strength at 0.2% Offset psi, min	Elongation in 2 Inches %, min
Up to 0.010, excl	200,000	180,000	6
0.010 to 0.080, incl	200,000	180,000	8
Over 0.010 to 0.125, incl	200,000	180,000	10

TABLE I (SI)

Nominal Thickness Millimeters	Tensile Strength MPa, min	Yield Strength at 0.2% Offset MPa, min	Elongation in 50.8 mm %, min
Up to 0.25, excl	1379	1241	6
0.25 to 2.03, incl	1379	1241	8
Over 2.03 to 3.18, incl	1379	1241	10

3.3.1.1 Tensile property requirements for product over 0.125 inch (3.18 mm) in nominal thickness shall be as agreed upon by purchaser and vendor.

3.3.2 Hardness: Should be not lower than 43 HRC, or equivalent, but the product shall not be rejected on the basis of hardness if the tensile property requirements are met.

3.4 Quality:

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.5 Tolerances:

Shall conform to all applicable requirements of AMS 2242 or MAM 2242 except that flatness tolerances shall be as agreed upon by purchaser and vendor.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

4.2 Classification of Tests:

Tests for all technical requirements are acceptance tests and shall be performed on each heat or lot as applicable.

4.3 Sampling and Testing:

Shall be in accordance with AMS 2371.