



AEROSPACE MATERIAL SPECIFICATION

AMS5549™**REV. H**

Issued	1959-11
Revised	1987-04
Noncurrent	1993-04
Reaf. Nonc.	2012-04
Stabilized	2017-04

Superseding AMS5549G

Steel, Corrosion and Heat Resistant, Plate
15.5Cr - 4.5Ni - 2.9Mo - 0.10N
Solution Heat Treated

UNS S35500

RATIONALE

AMS5549H stabilizes this document because it contains mature technology that is not expected to change and thus no further revisions are anticipated.

STABILIZED NOTICE

AMS5549H has been declared "STABILIZED" by the SAE AMS F Corrosion Heat Resistant Alloys Committee. This document was stabilized because this document contains mature technology that is not expected to change and thus no further revisions are anticipated. Previously this document was non-current. The last technical update of this document occurred in April, 1987. Users of this document should refer to the cognizant engineering organization for disposition of any issues with reports/certifications to this specification; including exceptions listed on the certification.

NOTE: In many cases, the purchaser may represent a sub tier supplier and not the cognizant engineering organization.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2017 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

**SAE values your input. To provide feedback on this
Technical Report, please visit**
<http://standards.sae.org/AMS5549H>

1. SCOPE:

1.1 Form:

This specification covers a corrosion and moderate heat resistant steel in the form of plate.

1.2 Application:

Primarily for parts requiring oxidation resistance and high strength up to 800°F (425°C) and where such parts may require welding during fabrication.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

- AMS 2242 Tolerances, Corrosion and Heat Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Sheet, Strip, and Plate
- MAM 2242 Tolerances, Metric, Corrosion and Heat Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Sheet, Strip, and Plate
- AMS 2248 Chemical Check Analysis Limits, Wrought Corrosion and Heat Resistant Steel and Alloys, Maraging and Other Highly-Alloyed Steels, and Iron Alloys
- AMS 2350 Standards and Test Methods
- AMS 2371 Quality Assurance Sampling of Corrosion and Heat Resistant Steels and Alloys, Wrought Products Except Forgings and Forging Stock

2.2 ASTM Publications:

Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

- ASTM A370 Mechanical Testing of Steel Products
- ASTM E353 Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys

2.3 U.S. Government Publications:

Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Military Standards:

MIL-STD-163 Steel Mill Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E353 or by spectrographic or other analytical methods approved by purchaser:

	min	max
Carbon	0.10	0.15
Manganese	0.50	1.25
Silicon	--	0.50
Phosphorus	--	0.040
Sulfur	--	0.030
Chromium	15.00	16.00
Nickel	4.00	5.00
Molybdenum	2.50	3.25
Nitrogen	0.07	0.13

3.1.2 Check Analysis: Composition variations shall meet the applicable requirements of AMS 2248.

3.2 Condition:

Hot rolled, solution heat treated free from continuous carbide network, and descaled.

3.3 Solution Heat Treatment:

The product shall be solution heat treated by heat to $1900^{\circ}\text{F} \pm 25$ ($1040^{\circ}\text{C} \pm 15$), holding at heat for 1 - 3 hr, and quenching in water or otherwise cooling as rapidly as possible to room temperature.

3.4 Properties:

The product shall conform to the following requirements, tensile, bend, and hardness testing shall be performed in accordance with ASTM A370:

3.4.1 As Solution Heat Treated:

- 3.4.1.1 Bending: Plate 0.750 in. (18.75 mm) and under in nominal thickness shall withstand, without cracking, bending at room temperature through the angle shown below around a diameter equal to three times the nominal thickness of the plate with axis of bend parallel to the direction of rolling:

Nominal Diameter		Angle
Inches	Millimetres	deg, min
Over 0.187 to 0.249, incl	Over 4.75 to 6.25, incl	130
Over 0.249 to 0.750, incl	Over 6.25 to 18.75, incl	90

- 3.4.1.2 Bending requirements for plate over 0.750 in. (18.75 mm) in nominal thickness shall be as agreed upon by purchaser and vendor.

- 3.4.2 As Re-solution Heat Treated, Sub-Zero Cooled, Austenite Conditioned, Sub-Zero Cooled, and Tempered: The product shall conform to the following requirements after being heat treated as follows: Re-solution heat treat by heating to 1900°F ± 25 (1040°C ± 15), holding at heat for 1 - 3 hr, and quenching in water; cool to -100°F (-75°C) or colder, hold at this temperature for not less than 3 hr, and warm in air to room temperature; austenite condition by heating to 1750°F ± 10 (955°C ± 5), holding at heat for 10 - 60 min., and quenching in water; cool to -100°F (-75°C) or colder, hold at this temperature for not less than 3 hr, and warm in air to room temperature; temper by heating to 1000°F ± 25 (540°C ± 5), holding at heat for not less than 3 hr, and cooling in air:

3.4.2.1 Tensile Properties:

Tensile Strength, min	165,000 psi (1140 MPa)
Yield Strength at 0.2% Offset, min	140,000 psi (965 MPa)
Elongation in 2 in. (50 mm), min	12%

- 3.4.2.2 Hardness: Should be 37 - 44 HRC, or equivalent, but the product shall not be rejected on the basis of hardness if the tensile property requirements of 3.4.2.1 are met.

3.5 Quality:

- 3.5.1 Steel shall be multiple melted using consumable electrode practice in the remelt cycle, using only one electrode to produce a single ingot.
- 3.5.2 The product, as received by purchaser, shall be uniform in quality and condition, free of grain boundary carbides, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.6 Tolerances:

Shall conform to all applicable requirements of AMS 2242 or MAM 2242. Flatness tolerances shall be as agreed upon by purchaser and vendor.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to requirements of this specification.

4.2 Classification of Tests:

Tests to determine conformance to all technical requirements of this specification are classified as acceptance tests and shall be performed on each heat or lot as applicable.

4.3 Sampling:

Shall be in accordance with AMS 2371; a heat shall be the consumable electrode remelted ingots from steel originally melted as a single furnace charge.

4.4 Reports:

- 4.4.1 The vendor of the product shall furnish with each shipment a report showing the results of tests for chemical composition of each heat and for tensile properties and hardness of each lot. This report shall include the purchase order number, heat number, AMS 5549H, size, and quantity.
- 4.4.2 The vendor of finished or semi-finished parts shall furnish with each shipment a report showing the purchase order number, AMS 5549H, contractor or other direct supplier of material, part number, and quantity. When material for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of material to determine conformance to the requirements of this specification and shall include in the report either a statement that the material conforms or copies of laboratory reports showing the results of tests to determine conformance.