



**Society of Automotive Engineers, Inc.**  
400 COMMONWEALTH DRIVE, WARRENDALE, PA. 15096

# AEROSPACE MATERIAL SPECIFICATION

**AMS 5577D**

Superseding AMS 5577C

Issued 2-15-52

Revised 4-1-81

UNS S31008

STEEL TUBING, WELDED, CORROSION AND HEAT RESISTANT  
25Cr - 20Ni (SAE 30310)

1. SCOPE:

1.1 Form: This specification covers a corrosion and heat resistant steel in the form of welded tubing.

1.2 Application: Primarily for parts and assemblies requiring both corrosion and heat resistance, especially when such parts and assemblies are welded during fabrication. Parts and assemblies requiring oxidation resistance up to 2000°F (1095°C) but useful at that temperature only when stresses are low.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2243 - Tolerances, Corrosion and Heat Resistant Steel Tubing

AMS 2248 - Chemical Check Analysis Limits, Wrought Heat and Corrosion Resistant Steels and Alloys

AMS 2350 - Standards and Test Methods

AMS 2371 - Quality Assurance Sampling of Corrosion and Heat Resistant Steels and Alloys, Wrought Products Except Forgings and Forging Stock

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM A370 - Mechanical Testing of Steel Products

ASTM E353 - Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys

2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Federal Standards:

Federal Test Method Standard No. 151 - Metals; Test Methods

2.3.2 Military Standards:

MIL-STD-163 - Steel Mill Products, Preparation for Shipment and Storage

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade or their use by governmental agencies is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

### 3. TECHNICAL REQUIREMENTS:

- 3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E353, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other analytical methods approved by purchaser:

|            | min           | max   |
|------------|---------------|-------|
| Carbon     | --            | 0.08  |
| Manganese  | --            | 2.00  |
| Silicon    | --            | 0.75  |
| Phosphorus | --            | 0.040 |
| Sulfur     | --            | 0.030 |
| Chromium   | 24.00 - 26.00 |       |
| Nickel     | 19.00 - 22.00 |       |
| Molybdenum | --            | 0.75  |
| Copper     | --            | 0.75  |

- 3.1.1 Check Analysis: Composition variations shall meet the requirements of AMS 2248.

- 3.2 Condition: Solution heat treated free from continuous carbide network and descaled.

- 3.3 Fabrication: Tubing shall be produced by a welded and drawn process. Any surface finishing operation applied to remove objectionable pits and surface blemishes shall be performed prior to final solution heat treatment. A light polish to improve surface appearance may be employed after solution heat treatment. Passivation treatment shall follow any polishing treatment.

- 3.4 Properties: Tubing shall conform to the following requirements:

- 3.4.1 Tensile Properties: Shall be as specified in Table I, determined in accordance with ASTM A370:

TABLE I

| Nominal OD<br>Inches | Tensile Strength<br>psi, max | Elongation in 2 in.<br>%, min |           |
|----------------------|------------------------------|-------------------------------|-----------|
|                      |                              | Strip                         | Full Tube |
| Up to 0.312, excl    | 105,000                      | 35                            | 40        |
| 0.312 and over       | 100,000                      | 35                            | 40        |

TABLE I (SI)

| Nominal OD<br>Millimetres | Tensile Strength<br>MPa, max | Elongation in 50 mm<br>%, min |           |
|---------------------------|------------------------------|-------------------------------|-----------|
|                           |                              | Strip                         | Full Tube |
| Up to 7.92, excl          | 724                          | 35                            | 40        |
| 7.92 and over             | 690                          | 35                            | 40        |

- 3.4.2 Flarability: Specimens as in 4.3.1 shall withstand flaring at room temperature, without formation of cracks or other visible defects, by being forced axially with steady pressure over a hardened and polished tapered steel pin having a 74 deg included angle to produce a flare having a permanent expanded OD not less than specified in Table II.

TABLE II

| Nominal OD<br>Inches | Expanded OD<br>Inches | Nominal OD<br>Inches | Expanded OD<br>Inches |
|----------------------|-----------------------|----------------------|-----------------------|
| 0.125                | 0.200                 | 0.750                | 0.937                 |
| 0.188                | 0.290                 | 1.000                | 1.187                 |
| 0.250                | 0.359                 | 1.250                | 1.500                 |
| 0.312                | 0.421                 | 1.500                | 1.721                 |
| 0.375                | 0.484                 | 1.750                | 2.106                 |
| 0.500                | 0.656                 | 2.000                | 2.356                 |
| 0.625                | 0.781                 |                      |                       |

TABLE II (SI)

| Nominal OD<br>Millimetres | Expanded OD<br>Millimetres | Nominal OD<br>Millimetres | Expanded OD<br>Millimetres |
|---------------------------|----------------------------|---------------------------|----------------------------|
| 3.18                      | 5.08                       | 19.05                     | 23.80                      |
| 4.78                      | 7.37                       | 25.40                     | 30.15                      |
| 6.35                      | 9.12                       | 31.75                     | 38.10                      |
| 7.92                      | 10.69                      | 38.10                     | 43.71                      |
| 9.52                      | 12.29                      | 44.45                     | 53.49                      |
| 12.70                     | 16.66                      | 50.80                     | 59.84                      |
| 15.88                     | 19.84                      |                           |                            |

3.4.2.1 Tubing with nominal OD between any two standard sizes given in 3.4.2 shall take the same percentage flare as shown for the larger of the two sizes.

3.4.2.2 Flarability requirements for tubing over 2.000 in. (50.80 mm) or less than 0.125 in. (3.18 mm) in nominal OD shall be as agreed upon by purchaser and vendor.

3.4.3 Pressure Testing: Tubing shall show no bulges, leaks, or other defects when subjected to an internal hydrostatic pressure, based on nominal dimensions, sufficient to cause a tensile stress of 20,000 psi (138 MPa) in the tubing wall.

### 3.5 Quality:

3.5.1 Tubing, as received by purchaser, shall be uniform in quality and condition and shall have a finish conforming to the best practice for high quality aircraft tubing. It shall be smooth and free from heavy scale or oxide, burrs, seams, tears, grooves, laminations, slivers, pits, and other imperfections detrimental to usage of the tubing. Surface imperfections such as handling marks, straightening marks, light mandrel and die marks, shallow pits, and scale pattern will not be considered injurious if the imperfections are removable within the tolerances specified for wall thickness but removal of such surface imperfections is not required.

3.5.2 If beads are present at the welds on the inner surface of the tubing, such beads shall not be thicker than 0.010 in. (0.25 mm), unless otherwise specified. The outer surfaces of the tubing shall be free from beads.

3.5.3 When specified by purchaser, tubing shall be subjected to nondestructive testing. Methods of testing and standards for acceptance shall be as agreed upon by purchaser and vendor.

- 3.6 Sizes: Except when exact lengths or multiples of exact lengths are ordered, straight tubing will be acceptable in mill lengths of 6 - 20 ft (1.8 - 6.1 m) but not more than 10% of any shipment shall be supplied in lengths shorter than 10 ft (3 m).
- 3.7 Tolerances: Unless otherwise specified, tolerances shall conform to all applicable requirements of AMS 2243.

#### 4. QUALITY ASSURANCE PROVISIONS:

- 4.1 Responsibility for Inspection: The vendor of tubing shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to sample and to perform such confirmatory testing as he deems necessary to ensure that the tubing conforms to the requirements of this specification.
- 4.2 Classification of Tests:
- 4.2.1 Acceptance Tests: Tests to determine conformance to requirements for composition (3.1), condition (3.2), tensile properties (3.4.1), pressure test (3.4.3), and tolerances (3.7) are classified as acceptance tests and shall be performed on each heat or lot as applicable.
- 4.2.2 Periodic Tests: Tests to determine conformance to requirements for flarability (3.4.2) are classified as periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.
- 4.3 Sampling: Shall be in accordance with AMS 2371 and the following:
- 4.3.1 Specimens for flarability test (3.4.3) shall be full tubes or sections cut from tubes. The end of the specimen to be flared shall be cut square, with the cut end smooth and free from burrs, but not rounded.
- 4.4 Reports:
- 4.4.1 The vendor of tubing shall furnish with each shipment three copies of a report showing the results of tests for chemical composition of each heat and for tensile properties and pressure test of each lot. This report shall include the purchase order number, heat number, AMS 5577D, size, and quantity from each heat.
- 4.4.2 The vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, AMS 5577D, contractor or other direct supplier of tubing, part number, and quantity. When tubing for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of tubing to determine conformance to the requirements of this specification, and shall include in the report a statement that the tubing conforms, or shall include copies of laboratory reports showing the results of tests to determine conformance.
- 4.5 Resampling and Retesting: Shall be in accordance with AMS 2371.
- #### 5. PREPARATION FOR DELIVERY:
- 5.1 Identification: Tubing shall be identified as follows: