



400 Commonwealth Drive, Warrendale, PA 15096-0001

AEROSPACE MATERIAL SPECIFICATION



AMS 5588E

Issued FEB 1965
Revised FEB 1995

Superseding AMS 5588D

Submitted for recognition as an American National Standard

NICKEL ALLOY, CORROSION AND HEAT RESISTANT, WELDED TUBING
47.5Ni - 22Cr - 1.5Co - 9.0Mo - 0.60W - 18.5Fe
Solution Heat Treated

UNS N06002

1. SCOPE:

1.1 Form:

This specification covers a corrosion and heat resistant nickel alloy in the form of welded and drawn tubing.

1.2 Application:

This tubing has been used typically for fluid lines operating in service under appreciable stresses at elevated temperatures, but usage is not limited to such applications. Alloy has good strength up to 1800 °F (982 °C) and oxidation resistance up to 2200 °F (1204 °C).

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

AMS 2263 Tolerances, Nickel, Nickel Alloy, and Cobalt Alloy Tubing
MAM 2263 Tolerances, Metric, Nickel, Nickel Alloy, and Cobalt Alloy Tubing
AMS 2269 Chemical Check Analysis Limits, Wrought Nickel Alloys and Cobalt Alloys
AMS 2371 Quality Assurance Sampling and Testing, Corrosion and Heat Resistant Steels and Alloys, Wrought Products and Forging Stock
AMS 2632 Ultrasonic Inspection of Thin Materials, 0.5 Inch (13 mm) and Thinner
AMS 2645 Fluorescent Penetrent Inspection
AMS 2807 Identification, Carbon and Low-Alloy Steels, Corrosion and Heat Resistant Steels and Alloys, Sheet, Strip, Plate, and Aircraft Tubing

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

AMS 5588E

SAE

AMS 5588E

2.2 ASTM Publications:

Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

ASTM E 8 Tension Testing of Metallic Materials
 ASTM E 8M Tension Testing of Metallic Materials (Metric)
 ASTM E 112 Determining the Average Grain Size
 ASTM E 354 Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys
 ASTM E 426 Electromagnetic (Eddy-Current) Testing of Seamless and Welded Tubular Products, Austenitic Stainless Steel and Similar Alloys

2.3 U.S. Government Publications:

Available from DODSSP, Subscription Services Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.

MIL-STD-163 Steel Mill Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:**3.1 Composition:**

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 354, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

Element	min	max
Carbon	0.05	0.15
Manganese	--	1.00
Silicon	--	1.00
Phosphorus	--	0.040
Sulfur	--	0.030
Chromium	20.50	23.00
Cobalt	0.50	2.50
Molybdenum	8.00	10.00
Tungsten	0.20	1.00
Iron	17.00	20.00
Aluminum	--	0.50
Titanium	--	0.15
Boron	--	0.010
Copper	--	0.50
Nickel	remainder	

3.1.1 Check Analysis: Composition variations shall meet the requirements of AMS 2269.

AMS 5588E

SAE

AMS 5588E

3.2 Condition:

Cold drawn, solution heat treated, and descaled. No specific solution heat treating instructions are specified but it is recommended that the tubing be solution heat treated by heating in a suitable protective atmosphere to $2150^{\circ}\text{F} \pm 25$ ($1177^{\circ}\text{C} \pm 14$), holding at heat for a time commensurate with section thickness, and cooling rapidly. In no case shall the solution heat treatment temperature be lower than 2100°F (1149°C).

3.3 Fabrication:

Tubing shall be fabricated from hot or cold rolled strip, fusion welded without addition of filler metal, cold drawn, and solution heat treated. The cold drawing operation on tubing 3.0 inches (76 mm) and under in nominal OD shall result in not less than 15% reduction in wall thickness; the amount of wall thickness reduction on tubing over 3.0 inches (76 mm) in nominal OD shall be as agreed upon by purchaser and vendor.

3.4 Properties:

Tubing shall conform to the following requirements:

- 3.4.1 Tensile Properties: Shall be as shown in Table 2, determined in accordance with ASTM E 8 or ASTM E 8M on tubing having nominal OD of 0.125 inch (3.18 mm) and over with nominal wall thickness of 0.015 inch (0.38 mm) and over.

TABLE 2 - Minimum Room Temperature, Tensile Properties

Property	Value
Tensile Strength	100 ksi (689 MPa)
Yield Strength at 0.2% Offset	45.0 ksi (310 MPa)
Elongation in 2 Inches (50.8 mm)	
Strip Specimens	20%
Full-Section Specimens	25%

- 3.4.2 Average Grain Size: Shall be ASTM No. 4 or finer, determined in accordance with (R) ASTM E 112, for tubing 0.125 inch (3.18 mm) and under in nominal wall thickness.

- 3.4.3 Flareability: Specimens as in 4.3.1 shall withstand, without formation of cracks or other visible defects, flaring at room temperature by being forced axially with steady pressure over a hardened and polished tapered steel pin having a 74-degree included angle to produce a flare having a permanent expanded OD not less than 1.2 times the original nominal diameter.

AMS 5588E

SAE

AMS 5588E

- 3.4.4 Pressure Test: Tubing shall show no bulges, leaks, pinholes, cracks, or other defects when subjected to an internal hydrostatic pressure (P), except that a diametric permanent set of 0.002 inch per inch (0.002 mm/mm) of diameter is acceptable. The hydrostatic pressure (P) shall be determined from Equation 1.

$$P = S \frac{D^2 - d^2}{D^2 + d^2} \quad (\text{Eq.1})$$

where:

P = Test pressure in ksi (MPa)

S = 45.0 ksi (310 MPa)

D = Nominal OD in inches (mm)

d = Nominal ID in inches (mm)

3.5 Quality:

Tubing, as received by purchaser, shall be uniform in quality and condition and shall have a finish conforming to the best practice for high quality aircraft tubing. It shall be smooth and free from heavy scale or oxide, burrs, seams, tears, grooves, laminations, slivers, pits, and other imperfections detrimental to usage of the tubing. Surface imperfections such as handling marks, straightening marks, light mandrel and die marks, shallow pits, and scale pattern will not be considered injurious if the imperfections are removable within the tolerances specified for wall thickness but removal of such imperfections is not required.

- 3.5.1 If beads are present at the weld on the inner surface of tubing over 3.0 inches (76 mm) in nominal OD, such beads shall be not thicker than 0.010 inch (0.25 mm). The outer surface of all tubing and the inner surface of tubing 3.0 inches (76 mm) and under in nominal OD shall be free from beads.

- 3.5.2 When specified by purchaser, tubing shall be subjected to fluorescent penetrant inspection in accordance with AMS 2645, to ultrasonic inspection in accordance with AMS 2632, to electromagnetic (eddy-current) inspection in accordance with ASTM E 426, or to any combination thereof. Standards for acceptance shall be as agreed upon by purchaser and vendor.

3.6 Tolerances:

Shall conform to all applicable requirements of AMS 2263 or MAM 2263.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

(R)

The vendor of tubing shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the tubing conforms to the requirements of this specification.