

AMS 5592

ADOPTION NOTICE

AMS 5592, "Steel, Corrosion and Heat Resistant, Sheet, Strip, and Plate 18.5Cr - 35Ni - 1.15Si Solution Heat Treated" was adopted on 10 January 1994 for use by the Department of Defense (DoD). Proposed changes by DoD activities must be submitted to the DoD Adopting Activity: ASC/ENOSD, Building 125 2335 Seventh Street, Suite 6, Wright-Patterson AFB OH 45433-7809. DoD activities may obtain copies of this standard from the Standardization Document Order Desk, 700 Robbins Avenue, Building 4D, Philadelphia, PA 19111-5094. The private sector and other Government agencies may purchase copies from the Society of Automotive Engineers Inc., 400 Commonwealth Drive, Warrendale, PA 15096-0001.

Custodians:
Army - MR
Navy - AS

Adopting Activity:
Air Force - 11
(Proj No. 9515-1014)

SAENORM.COM : Click to view the full PDF of ams5592d

FSC 9515

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

AEROSPACE MATERIAL SPECIFICATION

Submitted for recognition as an American National Standard

SAE

AMS 5592D

Issued JUL 1963
Revised APR 1996

Superseding AMS 5592C

IRON-NICKEL ALLOY, CORROSION AND HEAT RESISTANT, SHEET, STRIP, AND PLATE
44Fe - 18.5Cr - 35Ni - 1.15Si
Solution Heat Treated

UNS NO8330

1. SCOPE:

1.1 Form:

This specification covers a corrosion and heat resistant iron-nickel alloy in the form of sheet, strip, and plate.

1.2 Application:

These products have been used typically for parts requiring heat and oxidation resistance up to 2150 °F (1177 °C), but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

- | | |
|----------|---|
| AMS 2242 | Tolerances, Corrosion and Heat Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Sheet, Strip, and Plate |
| MAM 2242 | Tolerances, Metric, Corrosion and Heat Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Sheet, Strip, and Plate |
| AMS 2248 | Chemical Check Analysis Limits, Corrosion and Heat Resistant Steels and Alloys, Maraging and Other Highly-Alloyed Steels, and Iron Alloys |
| AMS 2371 | Quality Assurance Sampling and Testing, Corrosion and Heat Resistant Steels and Alloys, Wrought Products and Forging Stock |
| AMS 2807 | Identification, Carbon and Low-Alloy Steels, Corrosion and Heat Resistant Steels and Alloys, Sheet, Strip, Plate, and Aircraft Tubing |

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 1996 Society of Automotive Engineers, Inc.
All rights reserved.

Printed in U.S.A.

2.2 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959.

ASTM E 3 Preparation of Metallographic Specimens
 ASTM E 8 Tension Testing of Metallic Materials
 ASTM E 8M Tension Testing of Metallic Materials (Metric)
 ASTM E 18 Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials
 ASTM E 353 Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys

2.3 U.S. Government Publications:

Available from DODSSP, Subscription Services Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.

MIL-STD-163 Steel Mill Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 353, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

Element	min	max
Carbon	--	0.08
Manganese	--	2.00
Silicon	0.75	1.50
Phosphorus	--	0.030
Sulfur	--	0.030
Chromium	17.00	20.00
Nickel	34.00	37.00
Copper	--	0.75
Tin	--	0.025
Lead	--	0.005
Iron	remainder	

3.1.1 Check Analysis: Composition variations shall meet the requirements of AMS 2248.

3.2 Condition:

The product shall be supplied in the following condition:

3.2.1 Sheet and Strip: Hot or cold rolled, solution heat treated, and, unless solution heat treatment is performed in an atmosphere yielding a bright finish, descaled having a surface appearance comparable to the following commercial corrosion-resistant steel finishes, as applicable (See 8.2).

3.2.1.1 Sheet: No. 2D finish.

3.2.1.2 Strip: No. 1 strip finish.

3.2.2 Plate: Hot rolled, solution heat treated, and descaled.

3.3 Properties:

The product shall conform to the following requirements:

3.3.1 Tensile Properties: Shall be as shown in Table 2, determined in accordance with
(R) ASTM E 8 or ASTM E 8M.

TABLE 2 - Minimum Tensile Properties

Property	Value
Tensile Strength	70.0 ksi (483 MPa)
Yield Strength at 0.2% Offset	30.0 ksi (207 MPa)
Elongation in 2 Inches (50.8 mm) or 4D	30%

3.3.1.1 Elongation requirement does not apply to sheet or strip under 0.020 inch (0.51 mm) in nominal thickness.

3.3.2 Hardness: Shall be not higher than 95 HRB, or equivalent (See 8.3), determined in
(R) accordance with ASTM E 18.

3.3.3 Microstructure: Shall be free from continuous carbide network, determined by metallographic examination of specimens prepared in accordance with ASTM E 3.

3.4 Quality:

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.5 Tolerances:

Shall conform to all applicable requirements of AMS 2242 or MAM 2242.