

**ADOPTION NOTICE**

SAE-AMS5595, "STEEL, CORROSION RESISTANT, SHEET, STRIP, AND PLATE 9.0MN - 20CR - 6.5NI - 0.28N SOLUTION HEAT TREATED", was adopted on 15-AUG-90 for use by the Department of Defense (DoD). Proposed changes by DoD activities must be submitted to the DoD Adopting Activity: Commander, Defense Supply Center Philadelphia, ATTN: DSCP-ILEA, 700 Robbins Avenue, Philadelphia, PA 19111-5096. Copies of this document may be purchased from the Society of Automotive Engineers 400 Commonwealth Drive Warrendale, Pennsylvania, United States, 15096-0001. <http://www.sae.org/>

**Custodians:**

Army - MR  
Navy - AS  
Air Force - 11  
DLA - IS

**Adopting Activity:**

DLA - IS

SAENORM.COM : Click to view the full PDF of SAE-AMS5595e

**FSC 9515**

**DISTRIBUTION STATEMENT A:** Approved for public release; distribution is unlimited.

# AEROSPACE MATERIAL SPECIFICATION



AMS 5595E

Issued NOV 1968  
Revised APR 1992  
Reaffirmed SEP 2000

Superseding AMS 5595D

Steel, Corrosion Resistant, Sheet, Strip, and Plate  
9.0Mn - 20Cr - 6.5Ni - 0.28N  
Solution Heat Treated

UNS S21904

## 1. SCOPE:

### 1.1 Form:

This specification covers a corrosion-resistant steel in the form of sheet, strip, and plate.

### 1.2 Application:

These products have been used typically for parts requiring high strength and corrosion resistance from -423 to +1100 °F (-253 to +593 °C) where such parts may require welding during fabrication, but usage is not limited to such applications.

## 2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

### 2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

|          |                                                                                                                                                   |
|----------|---------------------------------------------------------------------------------------------------------------------------------------------------|
| AMS 2242 | Tolerances, Corrosion and Heat Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Sheet, Strip, and Plate                                  |
| MAM 2242 | Tolerances, Metric, Corrosion and Heat Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Sheet, Strip, and Plate                          |
| AMS 2248 | Chemical Check Analysis Limits, Wrought Corrosion and Heat Resistant Steels and Alloys, Maraging and Other Highly-Alloyed Steels, and Iron Alloys |
| AMS 2371 | Quality Assurance Sampling and Testing, Corrosion and Heat Resistant Steels and Alloys, Wrought Products and Forging Stock                        |
| AMS 2807 | Identification, Carbon and Low-Alloy Steels, Corrosion and Heat Resistant Steels and Alloys, Sheet, Strip, Plate, and Aircraft Tubing             |

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 2000 Society of Automotive Engineers, Inc.  
All rights reserved.

Printed in U.S.A.

QUESTIONS REGARDING THIS DOCUMENT:  
TO PLACE A DOCUMENT ORDER:  
SAE WEB ADDRESS:

(724) 772-7161  
(724) 776-4970  
<http://www.sae.org>

FAX: (724) 776-0243  
FAX: (724) 776-0790

Distributed under license from the IHS Archive

## 2.2 ASTM Publications:

Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

|            |                                                                                                         |
|------------|---------------------------------------------------------------------------------------------------------|
| ASTM A 262 | Detecting Susceptibility to Intergranular Attack in Austenitic Stainless Steel                          |
| ASTM A 370 | Mechanical Testing of Steel Products                                                                    |
| ASTM E 112 | Determining Average Grain Size                                                                          |
| ASTM E 353 | Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys |

## 2.3 U.S. Government Publications:

Available from Standardization Documents Order Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.

MIL-STD-163 Steel Mill Products, Preparation for Shipment and Storage

## 3. TECHNICAL REQUIREMENTS:

## 3.1 Composition:

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 353, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

| Element    | min   | max   |
|------------|-------|-------|
| Carbon     | --    | 0.04  |
| Manganese  | 8.00  | 10.00 |
| Silicon    | --    | 1.00  |
| Phosphorus | --    | 0.060 |
| Sulfur     | --    | 0.030 |
| Chromium   | 19.00 | 21.50 |
| Nickel     | 5.50  | 7.50  |
| Nitrogen   | 0.15  | 0.40  |
| Molybdenum | --    | 0.75  |
| Copper     | --    | 0.75  |

## 3.1.1 Check Analysis: Composition variations shall meet the requirements of AMS 2248.

### 3.2 Condition:

The product shall be supplied in the following condition:

3.2.1 Sheet and Strip: Cold rolled, solution heat treated, and, unless solution heat treatment is performed in an atmosphere yielding a bright finish, descaled having a surface appearance comparable to 3.2.1.1 or 3.2.1.2 as applicable (See 8.2).

3.2.1.1 Sheet: No. 2D finish.

3.2.1.2 Strip: No. 1 strip finish.

3.2.2 Plate: Hot rolled, solution heat treated, and descaled.

### 3.3 Solution Heat Treatment:

The product shall be solution heat treated by heating to a temperature not lower than 1900 °F (1038 °C), holding at the selected temperature within  $\pm 25$  °F ( $\pm 14$  °C) for a time commensurate with cross-sectional thickness and the heating equipment and procedure used, and cooling at a rate equivalent to a rapid air cool or faster.

### 3.4 Properties:

The product shall conform to the following requirements; tensile, hardness, and bend testing shall be performed in accordance with ASTM A 370:

3.4.1 Grain Size: Shall be as shown in Table 2, determined by comparison of a polished and etched specimen with the chart in ASTM E 112.

TABLE 2 - Average Grain Size

| Inch                | Millimeters         | ASTM<br>Grain Size No. |
|---------------------|---------------------|------------------------|
| Up to 0.1875, excl  | Up to 4.762, excl   | 7 or finer             |
| 0.1875 to 1.00 incl | 4.762 to 25.4, incl | 3 or finer             |

3.4.2 Tensile Properties: Shall be as shown in Table 3.

TABLE 3A - Minimum Tensile Properties, Inch/Pound Units

| Nominal Thickness<br>Inch | Tensile<br>Strength<br>ksi | Yield Strength<br>at 0.2% Offset<br>ksi | Elongation in<br>2 Inches or 4D<br>% |
|---------------------------|----------------------------|-----------------------------------------|--------------------------------------|
| Up to 0.1875, excl        | 100                        | 60.0                                    | 40                                   |
| 0.1875 and over           | 90.0                       | 50.0                                    | 40                                   |

TABLE 3B - Minimum Tensile Properties, SI Units

| Nominal Thickness<br>Millimeters | Tensile<br>Strength<br>MPa | Yield Strength<br>at 0.2% Offset<br>MPa | Elongation in<br>50.8 mm or 4D<br>% |
|----------------------------------|----------------------------|-----------------------------------------|-------------------------------------|
| Up to 4.762, excl                | 689                        | 414                                     | 40                                  |
| 4.762 and over                   | 621                        | 345                                     | 40                                  |

3.4.3 Hardness: Should be not higher than 100 HRB, or equivalent, but the product shall not be rejected on the basis of hardness if the tensile property requirements of 3.4.2 are met.

3.4.4 Bending: Product 0.749 inch (19.02 mm) and under in nominal thickness shall withstand, without cracking, bending through the angle shown in Table 4 around a diameter equal to the bend factor times the nominal thickness of the product with axis of bend parallel to the direction of rolling. Only one type of test will be required in routine inspection; in case of dispute, results of tests using the V-block procedure shall govern.

TABLE 4 - Bending Parameters

| Nominal Thickness<br>Inch | Nominal Thickness<br>Millimeters | Type of<br>Bend | Angle<br>Deg, min | Bend<br>Factor |
|---------------------------|----------------------------------|-----------------|-------------------|----------------|
| Up to 0.249, incl         | Up to 6.32, incl                 | Free Bend       | 180               | 1              |
| Up to 0.249, incl         | Up to 6.32, incl                 | V-Block         | 135               | 1              |
| Over 0.249 to 0.749, incl | Over 6.32 to 19.02, incl         | Free Bend       | 90                | 1              |
| Over 0.249 to 0.749, incl | Over 6.32 to 19.02, incl         | V-Block         | 135               | 2              |

3.4.4.1 Bend requirements for product over 0.749 inch (19.02 mm) in nominal thickness shall be as agreed upon by purchaser and vendor.

3.4.5 Susceptibility to Intergranular Attack: Specimens shall be sensitized by heating in air to 1250 °F ± 10 (677 °C ± 6), holding at heat for 60 minutes ± 5, and cooling in air. The sensitized specimens shall show no evidence of intergranular attack when immersed in acidified copper sulfate solution in accordance with ASTM A 262, Practice E, except that exposure time shall be 72 hours and metallic copper shall not be added. After immersion, the specimens shall withstand, without cracking, bending in accordance with ASTM A 262, Practice E.

3.5 Quality:

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.6 Tolerances:

Shall conform to all applicable requirements of AMS 2242 or MAM 2242.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests for composition (3.1), grain size (3.4.1), tensile properties (3.4.2), hardness (3.4.3), and tolerances (3.6) are acceptance tests and shall be performed on each heat or lot as applicable.

4.2.2 Periodic Tests: Tests for bending (3.4.4) and susceptibility to intergranular attack (3.4.5) are periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.3 Sampling and Testing:

Shall be in accordance with AMS 2371.

4.4 Reports:

The vendor of the product shall furnish with each shipment a report showing the results of tests for chemical composition of each heat, for grain size, tensile properties, and hardness of each lot and, when performed, the results of tests to determine conformance to the periodic test requirements. This report shall include the purchase order number, heat and lot number, AMS 5595E, size, and quantity.