



AEROSPACE MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
400 COMMONWEALTH DRIVE, WARRENDALE, PA. 15096

AMS 5599B
Superseding AMS 5599A

Issued 11-1-67
Revised 1-15-78

UNS NO6625

ALLOY SHEET, STRIP, AND PLATE, CORROSION AND HEAT RESISTANT
62Ni - 21.5Cr - 9.0Mo - 3.7 (Cb+Ta)

1. SCOPE:

- 1.1 Form: This specification covers a corrosion and heat resistant nickel alloy in the form of sheet, strip, and plate.
- 1.2 Application: Primarily for parts and assemblies requiring corrosion and oxidation resistance up to 2000°F (1095°C), particularly where such parts may require welding during fabrication.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

- 2.1 SAE Publications: Available from Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2262 - Tolerances, Nickel, Nickel-Base, and Cobalt-Base Alloy Sheet, Strip, and Plate
AMS 2269 - Chemical Check Analysis Limits, Wrought Nickel and Nickel Base Alloys
AMS 2350 - Standards and Test Methods
AMS 2371 - Quality Assurance Sampling of Corrosion and Heat Resistant Alloys, Wrought Products Except Forgings

- 2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM E8 - Tension Testing of Metallic Materials
ASTM E18 - Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials
ASTM E112 - Estimating the Average Grain Size of Metals
ASTM E290 - Semi-Guided Bend Test for Ductility of Metallic Materials
ASTM E354 - Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt-Base Alloys

- 2.3 Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Federal Standards:

Federal Test Method Standard No. 151 - Metals; Test Methods

2.3.2 Military Standards:

MIL-STD-163 - Steel Mill Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

SAE Technical Board rules provide that: "All technical reports, including standards approved by the Board, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

- 3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E354, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other approved analytical methods:

	min	max
Carbon	--	0.10
Manganese	--	0.50
Silicon	--	0.50
Phosphorus	--	0.015
Sulfur	--	0.015
Chromium	20.00 - 23.00	
Molybdenum	8.00 - 10.00	
Columbium + Tantalum	3.15 - 4.15	
Iron	--	5.00
Cobalt (3.1.1)	--	1.00
Titanium	Present but not exceeding	0.40
Aluminum	Present but not exceeding	0.40
Nickel	remainder	

- 3.1.1 Determination not required for routing acceptance.

- 3.1.2 Check Analysis: Composition variations shall meet the requirements of AMS 2269.

- 3.2 Condition: The product shall be supplied in the following condition:

- 3.2.1 Sheet and Strip: Cold rolled, annealed, and descaled unless annealing is performed in an atmosphere yielding a bright finish, having a surface appearance comparable to a commercial corrosion-resistant steel No. 2D finish; standards for acceptance shall be as agreed upon by purchaser and vendor.

- 3.2.2 Plate: Hot rolled, annealed, and descaled, unless otherwise ordered.

- 3.3 Properties: The product shall conform to the following requirements:

- 3.3.1 Tensile Properties: Shall be as follows, determined in accordance with ASTM E8.

Tensile Strength, min	120,000 psi (827 MPa)
Yield Strength at 0.2% Offset, min	60,000 psi (414 MPa)
Elongation in 2 in. (50.8 mm) or 4D, min	30%

- 3.3.1.1 Yield strength requirement does not apply to product less than 0.020 in. (0.51 mm) in nominal thickness.

- 3.3.1.2 Elongation requirement does not apply to product less than 0.010 in. (0.25 mm) in nominal thickness.

- 3.3.2 Bending: Product 0.250 in. (6.35 mm) and under in nominal thickness shall withstand, without cracking, bending in accordance with ASTM E290 through an angle of 180 deg around a diameter equal to the bend factor times the nominal thickness of the product with axis of bend parallel to the direction of rolling.

Nominal Thickness		Bend Factor
Inch	(Millimetres)	
Up to 0.050, incl	(Up to 1.27, incl)	1
Over 0.050 to 0.250, incl	(Over 1.27 to 6.35, incl)	2

3.3.2.1 Bending requirements for plate over 0.250 in. (6.35 mm) in nominal thickness shall be as agreed upon by purchaser and vendor.

3.3.3 Grain Size: Shall be not larger than the following, determined in accordance with ASTM E112:

Form	Nominal Thickness		ASTM Grain Size No.
	Inches	(Millimetres)	
Sheet and Strip	Up to 0.050, incl	(Up to 1.27, incl)	5
	Over 0.050 to 0.250, incl	(Over 1.27 to 6.35, incl)	4
Plate	-		As agreed upon by purchaser and vendor

3.4 Quality: The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from internal and external imperfections detrimental to usage of the product.

3.5 Tolerances: Unless otherwise specified, tolerances shall conform to all applicable requirements of AMS 2262.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of the product shall supply all samples and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to perform such confirmatory testing as he deems necessary to ensure that the product conforms to the requirements of this specification.

4.2 Classification of Tests: Tests to determine conformance to all technical requirements of this specification are classified as acceptance tests.

4.3 Sampling: Shall be in accordance with AMS 2371 and the following:

4.3.1 Specimens for tensile tests of widths 9 in. (229 mm) and over shall be taken with the axis of the specimen perpendicular to the direction of rolling; for widths less than 9 in. (229 mm), specimen shall be taken with the axis parallel to the direction of rolling.

4.4 Reports:

4.4.1 The vendor of the product shall furnish with each shipment three copies of a report showing the results of tests for chemical composition of each heat and for tensile property, bending, and grain size requirements on each thickness from each heat. This report shall include the purchase order number, heat number, material specification number and its revision letter, size, and quantity from each heat.

4.4.2 The vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, material specification number and its revision letter, contractor or other direct supplier of material, part number, and quantity. When material for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of material to determine conformance to the requirements of this specification, and shall include in the report a statement that the material conforms, or shall include copies of laboratory reports showing the results of tests to determine conformance.

4.5 Resampling and Retesting: Shall be in accordance with AMS 2371.

5. PREPARATION FOR DELIVERY: