

AEROSPACE MATERIAL SPECIFICATION

SAE AMS5608

REV. F

Issued 1971-05
Reaffirmed 2006-04
Revised 2010-08
Superseding AMS5608E

Cobalt Alloy, Corrosion and Heat Resistant, Sheet, Strip, and Plate
40Co - 22Cr - 22Ni - 14.5W - 0.07La
Solution Heat Treated

(Composition similar to UNS R30188)

RATIONALE

AMS5608F revises requirements for tensile testing (3.4.1.1.1, Tables 2 and 3), stress rupture testing (3.4.4.1), bending (3.4.2), and reports (4.4), and is a Five Year Review and update of this specification.

1. SCOPE

1.1 Form

This specification covers a corrosion and heat resistant cobalt alloy in the form of sheet, strip, and plate.

1.2 Application

These products have been used typically for formed and drawn parts requiring high strength up to 1800 °F (982 °C) and oxidation resistance up to 2000 °F (1093 °C), but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or 724-776-4970 (outside USA), www.sae.org.

AMS2262 Tolerances, Nickel, Nickel Alloy, and Cobalt Alloy Sheet, Strip, and Plate

AMS2269 Chemical Check Analysis Limits, Nickel, Nickel Alloys, and Cobalt Alloys

AMS2371 Quality Assurance Sampling and Testing, Corrosion and Heat-Resistant Steels and Alloys, Wrought Products and Forging Stock

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user." SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions. Copyright © 2010 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER:
Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
<http://www.sae.org>

SAE WEB ADDRESS:

SAE values your input. To provide feedback on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS5608F>

AMS2807	Identification, Carbon and Low-Alloy Steels, Corrosion and Heat-Resistant Steels and Alloys, Sheet, Strip, Plate, and Aircraft Tubing
AS4194	Sheet and Strip Surface Finish Nomenclature

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM A 480/A 480M	Flat-Rolled Stainless and Heat-Resisting Steel Plate, Sheet and Strip
ASTM E 8/E 8M	Tension Testing of Metallic Materials
ASTM E 21	Elevated Temperature Tension Tests of Metallic Materials
ASTM E 112	Determining Average Grain Size
ASTM E 139	Conducting Creep, Creep-Rupture, and Stress-Rupture Tests of Metallic Materials
ASTM E 290	Bend Testing Material for Ductility
ASTM E 354	Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 354, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - COMPOSITION

Element	min	max
Carbon	0.05	0.15
Manganese	--	1.25
Silicon	0.20	0.50
Phosphorus	--	0.020
Sulfur	--	0.015
Chromium	20.00	24.00
Nickel	20.00	24.00
Tungsten	13.00	16.00
Lanthanum	0.02	0.12
Boron	--	0.015
Iron	--	3.00
Cobalt	remainder	

3.1.1 Check Analysis

Composition variations shall meet the applicable requirements of AMS2269.

3.2 Condition

The product shall be supplied in the following condition:

3.2.1 Sheet and Strip

Hot rolled or cold rolled, solution heat treated, and, unless solution heat treatment is performed in an atmosphere yielding a bright finish, descaled having a surface appearance comparable to the following commercial corrosion-resistant steel finishes as described in ASTM A 480/A 480M and AS4194, and 3.2.1.1 or 3.2.1.2 as applicable.

3.2.1.1 Sheet

No. 2D or better finish.

3.2.1.2 Strip

No. 1 or better strip finish.

3.2.2 Plate

Hot rolled, solution heat treated, and descaled.

3.3 Heat Treatment

The product shall be solution heat treated by heating to a temperature within the range 2125 to 2250 °F (1163 to 1232 °C), holding at the selected temperature within ± 25 °F (± 14 °C) for a time commensurate with section thickness, and cooling at a rate equivalent to air cooling or faster.

3.3.1 Any thermal treatment following solution heat treatment as in 3.3 shall not involve use of temperatures higher than 2050 °F ± 25 (1121 °C ± 14).

3.4 Properties

The product shall conform to the following requirements:

3.4.1 Tensile Properties

3.4.1.1 At Room Temperature

Shall be as shown in Table 2, determined in accordance with ASTM E 8/E 8M.

3.4.1.1.1 For product 0.010 inch (0.25 mm) and under in nominal thickness, properties may be established using a sample up to 0.025 inch (0.64 mm) in nominal thickness from the same master coil and heat. The supplier's certification of test shall indicate the thickness at which the tensile test was performed

TABLE 2A - MINIMUM TENSILE PROPERTIES, INCH/POUND UNITS

Nominal Thickness Inch	Tensile Strength ksi	Yield Strength at 0.2% Offset ksi	Elongation in 2 Inches or 4D %
Up to 0.010, incl	125	55	Report
Over 0.010. to 0.020, incl	125	55	40
Over 0.020	125	55	45

TABLE 2B - MINIMUM TENSILE PROPERTIES, SI UNITS

Nominal Thickness Millimeter	Tensile Strength MPa	Yield Strength at 0.2% Offset MPa	Elongation in 50.8 mm or 4D %
Up to 0.25, incl	862	379	Report
Over 0.25 to 0.51, incl	862	379	40
Over 0.51	862	379	45

3.4.1.2 At 1200 °F (649 °C)

Shall be as shown in Table 3, determined in accordance with ASTM E 21 on specimens heated to 1200 °F $\pm$ 5 (649 °C $\pm$ 3), held at heat for not less than 20 minutes before testing, and tested at 1200 °F $\pm$ 5 (649 °C $\pm$ 3).

3.4.1.2.1 For product 0.010 inch (0.25 mm) and under in nominal thickness, properties may be established using a sample up to 0.025 inch (0.64 mm) in nominal thickness from the same master coil and heat. The supplier's certification of test shall indicate the thickness at which the tensile test was performed

TABLE 3A - MINIMUM TENSILE PROPERTIES, INCH/POUND UNITS

Nominal Thickness Inch	Tensile Strength ksi	Yield Strength at 0.2% Offset ksi	Elongation in 2 Inches or 4D %
Up to 0.010, incl	90	36.0	Report
Over 0.010 to 0.020, incl	90	36.0	40
Over 0.020	90	36.0	50

TABLE 3B - MINIMUM TENSILE PROPERTIES, SI UNITS

Nominal Thickness Millimeter	Tensile Strength MPa	Yield Strength at 0.2% Offset MPa	Elongation in 50.8 mm or 4D %
Up to 0.25, incl	621	248	Report
Over 0.25 to 0.51, incl	621	248	40
Over 0.51	621	248	50

3.4.2 Bending

Product 0.1874 inch (4.760 mm) and under in nominal thickness shall be tested in accordance with ASTM E 290 using a sample prepared nominally 0.75 inch (19.0 mm) in width with its axis of bending parallel to the direction of rolling and shall withstand without cracking when bending at room temperature through an angle of 180 degrees around a diameter equal to the bend factor shown in Table 4 times the nominal thickness of the product. In case of dispute, the results of tests using the guided bend test of ASTM E 290 shall govern.

TABLE 4 - BENDING PARAMETERS

Nominal Thickness Inch	Nominal Thickness Millimeters	Bend Factor
Up to 0.050, incl	Up to 1.27, incl	1.5
Over 0.050 to 0.1874, incl	Over 1.27 to 4.760, incl	2

3.4.3 Average Grain Size

Shall be ASTM No. 4 or finer, determined in accordance with ASTM E 112.

3.4.4 Stress-Rupture Properties at 1700 °F (927 °C)

A tensile specimen, maintained at 1700 °F $\pm$ 3 (927 °C $\pm$ 2) while the load required to produce the initial axial stress shown in Table 5 or higher stress is applied continuously, shall not rupture in less than 23 hours. The test shall be continued to rupture without change of load. Elongation after rupture, measured at room temperature, shall be as specified in Table 5. Tests shall be conducted in accordance with ASTM E 139.

TABLE 5A - STRESS-RUPTURE PROPERTIES, INCH/POUND UNITS

Nominal Thickness Inches	Stress ksi	Elongation in 2 Inches or 4D %, min
Up to 0.020, incl	9.0	8
Over 0.020	11.0	15

TABLE 5B - STRESS-RUPTURE PROPERTIES, SI UNITS

Nominal Thickness Millimeter	Stress MPa	Elongation in 50.8 mm or 4D %, min
Up to 0.51, incl	62.1	8
Over 0.51	75.8	15

- 3.4.4.1 The test of 3.4.4 may be conducted using incremental loading. In such case, the load required to produce the applicable initial axial stress specified in Table 5 or higher stress shall be used to rupture or for 23 hours, whichever occurs first. After the 23 hours and at intervals of 8 hours minimum, thereafter, the stress shall be increased in increments of 2.0 ksi (13.8 MPa). Time to rupture and elongation requirements shall be as specified in 3.4.4.
- 3.4.4.2 For product 0.010 inch (0.25 mm) and under in nominal thickness, stress rupture properties may be established using a sample up to 0.025 inch (0.64 mm) in nominal thickness from the same master coil and heat. The supplier's certification of test shall indicate the thickness at which the stress rupture test was performed.

3.4.5 Oxidation Resistance

A specimen representing each heat shall be prepared in accordance with 3.4.5.1, tested in accordance with 3.4.5.2, and meet the requirements of 3.4.5.3.

- 3.4.5.1 Specimens shall have not less than 1.5 square inch (9.7 cm²) test surface in excess of material required for fixturing. Test surfaces shall be hand polished, using 120 grit or finer silicon carbide paper, and degreased. Specimens may be fixtured during test by insertion into inert ceramic brick or by suspension from inert ceramic rods. Specimens shall not be placed in crucibles.
- 3.4.5.2 Specimens shall be subjected to four cycles; each cycle shall consist of heating to a temperature within the range 2000 to 2100 °F (1093 to 1149 °C), holding at the selected temperature within ± 25 °F (± 14 °C) for 25 hours ± 1 , and air cooling to 300 °F (149 °C) or lower between cycles. Heating shall be performed in a furnace which provides natural convection air flow such that test surfaces are equally exposed.
- 3.4.5.3 A polished cross-section, examined at not lower than 500X magnification, shall have not more than 0.0015 inch (0.038 mm) average affected metal (that metal converted to oxide scale plus any continuous intergranular oxidation) per side.

3.5 Quality

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.