



AEROSPACE MATERIAL SPECIFICATION

AMS5657™**REV. D**

Issued	1960-06
Cancelled	2007-02
Noncurrent	2007-08
Reaf. Nonc.	2012-10
Stabilized	2017-04

Superseding AMS5657C

Steel Bars and Forgings, Corrosion and Moderate Heat-Resistant
15Cr - 7.1Ni - 2.5Mo - 1.1Al
(Composition similar to UNS S15700)

RATIONALE

AMS5657D stabilizes this document because it contains mature technology that is not expected to change and thus no further revisions are anticipated.

STABILIZED NOTICE

AMS5657D has been declared "STABILIZED" by the SAE AMS F Corrosion Heat Resistant Alloys Committee. This document was stabilized because this document contains mature technology that is not expected to change and thus no further revisions are anticipated. Previously this document was non-current. The last technical update of this document occurred in February, 2007. Users of this document should refer to the cognizant engineering organization for disposition of any issues with reports/certifications to this specification; including exceptions listed on the certification.

NOTE: In many cases, the purchaser may represent a sub tier supplier and not the cognizant engineering organization.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2017 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
<http://www.sae.org>

SAE WEB ADDRESS:

**SAE values your input. To provide feedback on this
Technical Report, please visit**
<http://standards.sae.org/AMS5657D>

1. ACKNOWLEDGMENT:

A vendor shall mention this specification number in all quotations and when acknowledging purchase orders.

2. FORM:

Bars, forgings, and forging stock.

3. APPLICATION:

Primarily for parts requiring high strength and oxidation resistance up to 700 F, and where such parts may require welding during fabrication.

4. COMPOSITION:

Carbon	0.09	max
Manganese	1.00	max
Silicon	1.00	max
Phosphorus	0.040	max
Sulfur	0.030	max
Chromium	14.00 - 16.00	
Nickel	6.50 - 7.75	
Molybdenum	2.00 - 3.00	
Aluminum	0.75 - 1.50	

4.1 Check Analysis:

Unless otherwise specified, composition variations shall meet the requirements of the latest issue of AMS 2248.

5. CONDITION:

5.1 Bars:

Solution heat treated at 1950 F $\pm$ 25 and water quenched, having hardness as indicated below when tested midway between center and surface.

5.1.1 Rounds: Ground, turned, or polished, having hardness not higher than Brinell 269 or equivalent.

5.1.2 Hexagons: Cold drawn for size after solution treatment, having hardness not higher than Brinell 321 or equivalent.

5.1.3 Flats: Hot finished, solution heat treated, and descaled, having hardness not higher than Brinell 269 or equivalent.

5.2 Forgings:

Unless otherwise specified, solution treated at $1950\text{ F} \pm 25$ and water quenched, having hardness not higher than Brinell 321 or equivalent.

5.3 Forging Stock:

As ordered by the forging manufacturer.

6. TECHNICAL REQUIREMENTS:

6.1 Properties After Transformation and Precipitation Hardening:

Material shall conform to the following requirements after heating to $1400\text{ F} \pm 25$, holding at heat 90 min., cooling to $55\text{ F} \pm 5$ within 1 hr, holding at this temperature for not less than 30 min., heating to $1050\text{ F} \pm 10$, holding at heat for 90 min., and cooling in air.

6.1.1 Bars:

6.1.1.1 Tensile Properties: Applicable to sizes 6 in. and under in diameter or distance between parallel sides.

Tensile Strength, psi	180,000 min
Yield Strength at 0.2% Offset or at 0.0150 in. in 2 in. Extension Under Load ($E = 29,000,000$), psi	160,000 min
Elongation, % in 4D	8 min
Reduction of Area, %	25 min

6.1.1.1.1 Tensile test specimens shall be taken parallel to the direction of rolling and midway between center and surface where size permits.

6.1.1.2 Hardness: Not lower than Brinell 375 or equivalent.

6.1.2 Forgings:

6.1.2.1 Hardness: Not lower than Brinell 375 or equivalent.

6.2 Properties After Austenite Conditioning, Sub-Zero Transformation and Precipitation Hardening:

Material shall conform to the following requirements after heating to 1750 F ± 15, holding at heat for 10 min., and rapidly cooling to room temperature, cooling within 24 hr to -100 F ± 10, holding at this temperature for not less than 8 hr, warming in air to room temperature, heating to 950 F ± 10, holding at heat for 1 hr, and cooling in air.

6.2.1 Bars:

6.2.1.1 Tensile Properties: Applicable to sizes 6 in. and under in diameter or distance between parallel sides.

Tensile Strength, psi	200,000 min
Yield Strength at 0.2% Offset or at 0.0161 in. in 2 in. Extension Under Load (E = 29,000,000), psi	175,000 min
Elongation, % in 4D	7 min
Reduction of Area, %	25 min

6.2.1.1.1 Tensile test specimens shall be taken parallel to the direction of rolling and midway between center and surface where size permits.

6.2.1.2 Hardness: Not lower than Brinell 415 or equivalent.

6.2.2 Forgings:

6.2.2.1 Hardness: Not lower than Brinell 415 or equivalent.

7. QUALITY:

Material shall be uniform in quality and condition, clean, sound, and free from foreign materials and from internal and external imperfections detrimental to fabrication or to performance of parts.

8. TOLERANCES:

Unless otherwise specified, tolerances shall conform to the latest issue of AMS 2241 as applicable; diameter, thickness, and width tolerances shall be as specified below:

8.1 Rounds and Hexagons:

Table I.