



400 Commonwealth Drive, Warrendale, PA 15096-0001

AEROSPACE MATERIAL SPECIFICATION



AMS 5664D

Issued SEP 1965
Revised JUL 1994

Superseding AMS 5664C

Submitted for recognition as an American National Standard

NICKEL ALLOY, CORROSION AND HEAT RESISTANT, BARS, FORGINGS, AND RINGS

52.5Ni - 19Cr - 3.0Mo - 5.1Cb - 0.90Ti - 0.50Al - 18Fe

Consumable Electrode or Vacuum Induction Melted

1950 °F (1066 °C) Solution Heat Treated, Precipitation Hardenable

UNS N07718

1. SCOPE:

1.1 Form:

This specification covers a corrosion and heat resistant nickel alloy in the form of bars, forgings, flash welded rings, and stock for forging or flash welded rings.

1.2 Application: (R)

These products have been used typically for rotating and structural parts requiring high strength at cryogenic temperatures and for short-time service up to 1000 °F (538 °C) and oxidation resistance up to 1800 °F (982 °C), but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

- AMS 2261 Tolerances, Nickel, Nickel Alloy, and Cobalt Alloy Bars, Rods, and Wire
- MAM 2261 Tolerances, Metric, Nickel, Nickel Alloy, and Cobalt Alloy Bars, Rods, and Wire
- AMS 2269 Chemical Check Analysis Limits, Wrought Nickel Alloys and Cobalt Alloys

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

AMS 5664D

SAE

AMS 5664D

2.1 (Continued)

- AMS 2371 Quality Assurance Sampling and Testing, Corrosion and Heat Resistant Steels and Alloys, Wrought Products and Forging Stock
- AMS 2374 Quality Assurance Sampling and Testing, Corrosion and Heat Resistant Steel and Alloy Forgings
- AMS 2806 Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Corrosion and Heat Resistant Steels and Alloys
- AMS 2808 Identification, Forgings
- AMS 7490 Rings, Flash Welded, Corrosion and Heat Resistant Austenitic Steels and Austenitic-Type Alloys, or Precipitation Hardenable Alloys

2.2 ASTM Publications:

Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

- ASTM E 8 Tension Testing of Metallic Materials
- ASTM E 8M Tension Testing of Metallic Materials (Metric)
- ASTM E 10 Brinell Hardness of Metallic Materials
- ASTM E 112 Determining the Average Grain Size
- ASTM E 354 Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys

2.3 U.S. Government Publications:

Available from DODSSP, Subscription Services Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.

MIL-STD-163 Steel Mill Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

3.1 Composition:
(R)

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 354, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

AMS 5664D

SAE

AMS 5664D

TABLE 1 - Composition

Element	min	max
Carbon	--	0.08
Manganese	--	0.35
Silicon	--	0.35
Phosphorus	--	0.015
Sulfur	--	0.015
Chromium	17.00	21.00
Nickel	50.00	55.00
Molybdenum	2.80	3.30
Columbium	4.75	5.50
Titanium	0.65	1.15
Aluminum	0.20	0.80
Cobalt	--	1.00
Tantalum (3.1.1)	--	0.05
Boron	--	0.006
Copper	--	0.30
Iron	remainder	

3.1.1 Determination not required for routine acceptance.
(R)

3.1.2 Check Analysis: Composition variations shall meet the requirements of AMS 2269.

3.2 Melting Practice:

Alloy shall be produced by multiple melting using consumable electrode practice in the remelt cycle or shall be induction melted under vacuum. If consumable electrode remelting is not performed in vacuum, electrodes which have been produced by vacuum induction melting shall be used.

3.3 Condition:

The product shall be supplied in the following condition:

3.3.1 Bars, Forgings, and Flash Welded Rings: Solution heat treated.

3.3.1.1 Bars shall be hot finished; round bars shall be ground or turned.

3.3.1.2 Forgings shall be rough machined or descaled.

3.3.1.3 Flash welded rings shall not be supplied unless specified or permitted on purchaser's part drawing. When supplied, rings shall be manufactured in accordance with AMS 7490.

3.3.2 Stock for Forging or Flash Welded Rings: As ordered by the forging or flash welded ring manufacturer.

AMS 5664D

SAE

AMS 5664D

3.4 Heat Treatment:

Bars, forgings, and flash welded rings shall be solution heat treated to meet the requirements of 3.5.1. No specific heat treating instructions are specified but it is recommended that the product be solution heat treated by heating in a suitable protective atmosphere to $1950^{\circ}\text{F} \pm 25$ ($1066^{\circ}\text{C} \pm 14$) but in no case lower than 1900°F (1038°C), holding at heat for a time commensurate with cross-sectional thickness, and cooling at a rate equivalent to an air cool or faster.

3.5 Properties:

The product shall conform to the following requirements:

3.5.1 Bars, Forgings, and Flash Welded Rings:

3.5.1.1 As Solution Heat Treated:

3.5.1.1.1 Hardness: Shall be as follows; determined in accordance with ASTM E 10 (See 8.2):

3.5.1.1.1.1 Bars: Not higher than the following, determined approximately midway between the outer surface and center (mid-radius):

3.5.1.1.1.1.1 Up to 3.0 Inches (76 mm), Exclusive, in Nominal Diameter or Distance Between Parallel Sides: Shall be 248 HB, or equivalent.

3.5.1.1.1.1.2 3.0 to 5.0 Inches (76 to 127 mm), Exclusive, in Nominal Diameter or Distance Between Parallel Sides: Shall be 285 HB, or equivalent.

3.5.1.1.1.1.3 5.0 to 10.0 Inches (127 to 254 mm), Exclusive, in Nominal Diameter or Distance Between Parallel Sides: Shall be 321 HB, or equivalent.

3.5.1.1.1.1.4 10 Inches (254 mm) and Over in Nominal Diameter or Distance Between Parallel Sides: As agreed upon by purchaser and vendor.

3.5.1.1.1.2 Forgings and Flash Welded Rings: Not higher than 248 HB, or equivalent.

3.5.1.1.2 Average Grain Size: Shall be as follows, determined in accordance with ASTM E 112 and the following:

3.5.1.1.2.1 Determination shall be made at 1 to 3X magnification on the rough-machined surface of the product after suitably etching to reveal the macro-grain structure. Acceptance shall be based on correlation of the macro-grain structure with the micro-grain structure that will satisfy the requirements of 3.5.1.1.2.2 or 3.5.1.1.2.3 as applicable.

AMS 5664D

SAE

AMS 5664D

- 3.5.1.1.2.2 Bars, Hammer Forgings, and Flash Welded Rings: Structure shall consist of recrystallized grains of ASTM No. 4 or finer for product (R) under 4.5 inches (114 mm) in nominal thickness. Occasional grains as coarse as ASTM No. 2 are permissible but shall not exceed 10% of any field examined at 100X magnification.
- 3.5.1.1.2.3 Extrusions and Press Forgings: Structure shall consist of partially recrystallized grains consisting of 60% or more of ASTM No. 3 or finer and 40% or less of grains ASTM No. 1 or finer. A uniform structure of ASTM No. 3 or finer recrystallized grains is acceptable.
- 3.5.1.2 After Precipitation Heat Treatment: The product shall have the following properties after being precipitation heat treated by heating to $1400^{\circ}\text{F} \pm 15$ ($760^{\circ}\text{C} \pm 8$), holding at heat for 10 hours ± 0.5 , furnace cooling to $1200^{\circ}\text{F} \pm 15$ ($649^{\circ}\text{C} \pm 8$), holding at $1200^{\circ}\text{F} \pm 15$ ($649^{\circ}\text{C} \pm 8$) until a total precipitation heat treatment time of 20 hours has been reached, and cooled. The product shall also meet the following requirements after being re-solution heat treated by heating to $1950^{\circ}\text{F} \pm 25$ ($1066^{\circ}\text{C} \pm 14$) in a suitable protective atmosphere, holding at heat for 1 to 2 hours, and cooling at a rate equivalent to an air cool or faster and then precipitation heat treated as previously stated.
- 3.5.1.2.1 Tensile Properties: Product 10 inches (254 mm) and under in least nominal cross-sectional dimension shall have the properties shown in Table 2 and Table 3, determined in accordance with ASTM E 8 or ASTM E 8M.
- 3.5.1.2.1.1 Bars: Shall be as shown in Table 2.

TABLE 2 - Minimum Tensile Properties

Property	Value
Tensile Strength	180 ksi (1241 MPa)
Yield Strength at 0.2% Offset	150 ksi (1034 MPa)
Elongation in 4D	10%
Reduction of Area	12%

AMS 5664D

SAE

AMS 5664D

3.5.1.2.1.2 Forgings and Flash Welded Rings: Shall be as shown in Table 3.

TABLE 3 - Minimum Tensile Properties

Property	Value
Tensile Strength	180 ksi (1241 MPa)
Yield Strength at 0.2% Offset	150 ksi (1034 MPa)
Elongation in 4D	12%
Reduction of Area	15%

3.5.1.2.2 Hardness: Shall be not lower than 341 HB, or equivalent (See 8.2),
(R) determined in accordance with ASTM E 10, but the product shall not be rejected on the basis of hardness if the tensile property requirements of 3.5.1.2.1.1 and 3.5.1.2.1.2 are met.

3.5.2 Forging Stock: When a sample of stock is forged to a test coupon and solution and precipitation heat treated as in 3.4 and 3.5.1.2, specimens taken from the heat treated coupon shall conform to the requirements of 3.5.1.2.1.2 and 3.5.1.2.2. If specimens taken from the stock after heat treatment as in 3.4 and 3.5.1.2 conform to the requirements of 3.5.1.2.1.2 and 3.5.1.2.2, the tests shall be accepted as equivalent to tests of a forged coupon.

3.5.3 Stock for Flash Welded Rings: Specimens taken from the stock after solution and precipitation heat treatment as in 3.4 and 3.5.1.2 shall conform to the requirements of 3.5.1.2.1.2 and 3.5.1.2.2.

3.6 Quality:

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.6.1 Grain flow of die forgings, except in areas which contain flash-line end grain, shall follow the general contour of the forgings showing no evidence of re-entrant grain flow.

3.7 Tolerances:

Bars shall conform to all applicable requirements of AMS 2261 or MAM 2261.

AMS 5664D

SAE

AMS 5664D

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests for the following requirements are acceptance tests and shall be performed on each heat or lot as applicable:

4.2.1.1 Composition (3.1) of each heat.

4.2.1.2 Hardness (3.5.1.1.1) and grain size (3.5.1.1.2) of each lot of bars, forgings, and flash welded rings as solution heat treated.

4.2.1.3 Tensile properties (3.5.1.2.1) and hardness (3.5.1.2.2) of each lot of bars, forgings, and flash welded rings after precipitation heat treatment.

4.2.1.4 Tolerances (3.7) of bars.

4.2.2 Periodic Tests: Tests for the following requirements are periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser:

4.2.2.1 Tensile properties (3.5.1.2.1) and hardness (3.5.1.2.2) of bars, forgings, and flash welded rings after re-solution and precipitation heat treatment as in 3.5.1.2.

4.2.2.2 Ability of forging stock (3.5.2) or stock for flash welded rings (3.5.3) to develop required properties.

4.2.2.3 Grain flow (3.6.1) of die forgings.
(R)

4.3 Sampling and Testing:

Shall be in accordance with the following:

4.3.1 Bars, Flash Welded Rings, and Stock for Forgings or Flash Welded Rings: AMS 2371 and the following:

4.3.1.1 Specimens for tensile tests of bars (3.5.1.2.1.1) shall be taken with the axis in the short-transverse direction except that if the short-transverse direction is under 2-1/2 inches (63.5 mm), specimens shall be taken in the long-transverse direction. If both transverse directions are under 2-1/2 inches (63.5 mm), specimens shall be taken with the axis in the longitudinal direction.

AMS 5664D

SAE

AMS 5664D

4.3.1.2 Specimens for tensile testing of flash welded rings (3.5.1.2.1.2) shall be taken with the axis of the specimen in the circumferential direction.

4.3.2 Forgings: AMS 2374 and the following:

4.3.2.1 Except as specified in 4.3.2.2, specimens for tensile testing of forgings (3.5.1.2.1.2) shall be taken with the axis in the transverse direction except that if the forging is under 2-1/2 inches (63.5 mm) in the transverse direction, specimens shall be taken with the axis in the longitudinal direction.

4.3.2.2 Specimens for tensile tests of disk forgings shall be cut from any plane perpendicular to the axis of the forging with axis of specimen in the selected plane perpendicular to a radius. When size and shape permit, additional specimens shall be cut with the axis of specimen approximately parallel to the axis of the forging. Size, location, and number of specimens shall be agreed upon by purchaser and vendor.

4.4 Reports:

4.4.1 The vendor of bars, forgings, and flash welded rings shall furnish with (R) each shipment a report showing the results of tests for chemical composition of each heat and the results of tests on each lot to determine conformance to the other acceptance tests requirements and, when performed, to the periodic test requirements. This report shall include the purchase order number, heat and lot number, AMS 5664D, size, and quantity. If forgings are supplied, the part number and the size and melt source of stock used to make the forgings shall also be included.

4.4.2 The vendor of stock for forging or flash welded rings shall furnish with each shipment a report showing the results of tests for chemical composition of each heat. This report shall include the purchase order number, heat number, AMS 5664D, size, and quantity.

4.5 Resampling and Retesting:

Shall be as follows:

4.5.1 Bars, Flash Welded Rings, and Stock for Forgings or Flash Welded Rings: In accordance with AMS 2371.

4.5.2 Forgings: In accordance with AMS 2374.

5. PREPARATION FOR DELIVERY:

5.1 Sizes:

Except when exact lengths or multiples of exact lengths are ordered, straight bars will be acceptable in mill lengths of 6 to 24 feet (1.8 to 7.3 m) but not more than 25% of any shipment shall be supplied in lengths of 6 to 9 feet (1.8 to 2.7 m) except that for bars weighing over 25 pounds per foot (37 kg/m), short lengths down to 2 feet (610 mm) may be supplied.