

AERONAUTICAL MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
29 West 39th Street
New York City

AMS 5685C

Issued 12-4-39

Revised 2-15-52

STEEL WIRE, CORROSION RESISTANT
18Cr - 11Ni (SAE 30305)
Solution Heat Treated

1. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. APPLICATION: Primarily for safety wire.
3. COMPOSITION:

Check Analysis
Under Min or Over Max.

Carbon	0.08 max	--	0.01
Manganese	2.00 max	--	0.04
Silicon	1.00 max	--	0.05
Phosphorus	0.040 max	--	0.005
Sulfur	0.030 max	--	0.005
Chromium	17.00 - 19.00	0.20	0.20
Nickel	10.00 - 13.00	0.15	0.15
Copper	0.50 max	--	0.03

4. CONDITION: Solution heat treated and bright pickled, unless otherwise specified.

5. TECHNICAL REQUIREMENTS:

- 5.1 Tensile Properties:

	Coils	Straight Lengths
Tensile Strength, psi	110,000 max	120,000 max

- 5.2 Bending: Wire shall withstand, without cracking, bending at room temperature flat on itself.

6. QUALITY:

- 6.1 Wire shall be uniform in quality and condition, cylindrical, clean, and free from kinks, twists, scrapes, splits, cold shuts and other injurious defects.
- 6.2 The surface shall have a bright, smooth finish, free from pits, abrasions and other surface imperfections.

7. TOLERANCES: The following variations in diameter are permissible:

Nominal Diameter, Inch	Tolerance, Inch, Plus and Minus
0.023 and under	0.0004
Over 0.023 to 0.032, incl	0.0005
Over 0.032 to 0.043, incl	0.0008
Over 0.043 to 5/16, incl	0.001

Section 7C of the SAE Technical Board rules provides that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."