

AEROSPACE MATERIAL SPECIFICATION

AMS 5689D

Issued 11-1-52
Revised 10-1-89

Superseding AMS 5689C

Submitted for recognition as an American National Standard

STEEL WIRE, CORROSION AND HEAT RESISTANT
18Cr - 10.5Ni - 0.40Ti (SAE 30321)
Solution Heat Treated

UNS S32100

1. SCOPE:

1.1 Form: This specification covers a corrosion and heat resistant steel in the form of wire.

1.2 Application: Primarily for screening and stitching applications requiring good corrosion resistance and which may be subjected to elevated temperatures during fabrication or in service. Wire has satisfactory oxidation resistance up to 1500°F (816°C) but is useful at that temperature only when stresses are low.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2241 - Tolerances, Corrosion and Heat Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Bars and Wire

MAM 2241 - Tolerances, Metric, Corrosion and Heat Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Bars and Wire

AMS 2248 - Chemical Check Analysis Limits, Wrought Corrosion and Heat Resistant Steels and Alloys, Maraging and Other Highly-Alloyed Steels, and Iron Alloys

AMS 2350 - Standards and Test Methods

AMS 2371 - Quality Assurance Sampling of Corrosion and Heat Resistant Steels and Alloys, Wrought Products Except Forgings and Forging Stock

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

2.2 ASTM Publications: Available from ASTM, 1916 Race Street, Philadelphia, PA 19103.

ASTM E 8 - Tension Testing of Metallic Materials
ASTM E 8M - Tension Testing of Metallic Materials (Metric)
ASTM E 353 - Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys

2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Military Standards:

MIL-STD-163 - Steel Mill Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E 353, by spectrochemical methods, or by other analytical methods acceptable to purchaser:

	min	max
Carbon	--	0.08
Manganese	--	2.00
Silicon	0.40 -	1.00
Phosphorus	--	0.040
Sulfur	--	0.030
Chromium	17.00 -	19.00
Nickel	9.00 -	12.00
Titanium	5x(C+N) -	0.70
Molybdenum	--	0.75
Copper	--	0.75
Nitrogen	--	0.10

3.1.1 Check Analysis: Composition variations shall meet the requirements of AMS 2248.

3.2 Condition: Solution heat treated free from continuous carbide network and bright finished.

3.3 Properties: Wire shall conform to the following requirements:

- 3.3.1 Tensile Strength: Shall be as specified in Table I, determined in accordance with ASTM E 8 or ASTM E 8M.

TABLE I

Nominal Diameter Inch	Tensile Strength, psi, max	
	Coils	Straight Lengths
0.010 to 0.020, incl	125,000	135,000
Over 0.020 to 0.125, incl	115,000	125,000
Over 0.125 to 0.250, incl	105,000	115,000

TABLE I (SI)

Nominal Diameter Millimetres	Tensile Strength, MPa, max	
	Coils	Straight Lengths
0.25 to 0.51, incl	862	931
Over 0.51 to 3.18, incl	793	862
Over 3.18 to 6.35, incl	724	793

- 3.3.1.1 Tensile strength requirements for wire under 0.010 inch (0.25 mm) or over 0.250 inch (6.35 mm) in nominal diameter shall be as agreed upon by purchaser and vendor.

- 3.3.2 Bending: Wire shall withstand, without cracking, bending at room temperature flat on itself.

- 3.4 Quality: Wire, as received by purchaser, shall be uniform in quality and condition, cylindrical, and free from kinks, twists, scrapes, splits, cold shuts, pits, and other imperfections detrimental to usage of the wire.

- 3.5 Tolerances: Shall conform to all applicable requirements of AMS 2241 or MAM 2241.

4. QUALITY ASSURANCE PROVISIONS:

- 4.1 Responsibility for Inspection: The vendor of wire shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the wire conforms to the requirements of this specification.

- 4.2 Classification of Tests: Tests for all technical requirements are acceptance tests and shall be performed on each heat or lot as applicable.

4.3 Sampling and Testing: Shall be in accordance with AMS 2371; the number of $\emptyset$ specimens to be sampled shall be the minimum number of specimens tested.

4.4 Reports: The vendor of wire shall furnish with each shipment a report showing the results of tests for chemical composition of each lot and for tensile and bending properties of each lot. This report shall include the purchase order number, lot number, AMS 5689D, nominal size, and quantity.

4.5 Resampling and Retesting: Shall be in accordance with AMS 2371.

5. PREPARATION FOR DELIVERY:

5.1 Wire shall be supplied in coils, on reels, or in straight lengths, as ordered.

5.2 Identification: Coils or reels of wire shall each be identified by a durable tag marked with not less than the purchase order number, AMS 5689D, lot number, nominal size, quantity, and manufacturer's identification. Straight lengths shall be bundled or boxed and shall have attached to each bundle or box a tag marked as above.

5.3 Packaging:

5.3.1 Wire shall be prepared for shipment in accordance with commercial practice and in compliance with applicable rules and regulations pertaining to the handling, packaging, and transportation of the wire to ensure carrier acceptance and safe delivery. Packaging shall conform to carrier rules and regulations applicable to the mode of transportation.

5.3.2 For direct U.S. Military procurement, packaging shall be in accordance with MIL-STD-163, Level A or Level C, as specified in the request for procurement. Commercial packaging as in 5.3.1 will be acceptable if it meets the requirements of Level C.

6. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.

7. REJECTIONS: Wire not conforming to this specification, or to modifications authorized by purchaser, will be subject to rejection.

8. NOTES:

8.1 Marginal Indicia: The phi ($\emptyset$) symbol is used to indicate technical changes from the previous issue of this specification.

8.2 Dimensions and properties in inch/pound units are primary; dimensions and properties in SI units are shown as the approximate equivalents of the primary units and are presented only for information.