

ALLOY BARS AND FORGINGS, CORROSION AND HEAT RESISTANT
58Ni - 19.5Cr - 13.5Co - 4.3Mo - 3.0Ti - 1.4Al - 0.05Zr - 0.006B
Consumable Electrode or Vacuum Induction Melted
1975°F (1079°C) Solution, Stabilization, and Precipitation Heat Treated
UNS N07001

1. SCOPE:

1.1 Form: This specification covers a corrosion and heat resistant nickel alloy in the form of bars, forgings, and forging stock.

1.2 Application: Primarily for parts, such as pins, nuts, and turbine blades, requiring high strength up to 1500°F (816°C) and oxidation resistance up to 1750°F (954°C).

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

2.1.1 Aerospace Material Specifications:

- AMS 2261 - Tolerances, Nickel, Nickel Alloy, and Cobalt Alloy Bars and Forging Stock
- MAM 2261 - Tolerances, Metric, Nickel, Nickel Alloy, and Cobalt Alloy Bars and Forging Stock
- AMS 2269 - Chemical Check Analysis Limits, Wrought Nickel Alloys and Cobalt Alloys
- AMS 2350 - Standards and Test Methods
- AMS 2371 - Quality Assurance Sampling of Corrosion and Heat Resistant Steels and Alloys, Wrought Products Except Forgings and Forging Stock
- AMS 2374 - Quality Assurance Sampling of Corrosion and Heat Resistant Steels and Alloys, Forgings and Forging Stock
- AMS 2375 - Control of Forgings Requiring First Article Approval
- AMS 2806 - Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Corrosion and Heat Resistant Steels and Alloys
- AMS 2808 - Identification, Forgings

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

- ASTM E18 - Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials
- ASTM E139 - Conducting Creep, Creep-Rupture, and Stress-Rupture Tests of Metallic Materials
- ASTM E354 - Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys

2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Military Specifications:

- MIL-STU-163 - Steel Mill Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

- 3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E354, by spectrochemical methods, or by other analytical methods acceptable to purchaser:

	min	max
Carbon	0.02	0.10
Manganese	-	0.10
Silicon	-	0.15
Phosphorus	-	0.015
Sulfur	-	0.015
Chromium	18.00	21.00
Cobalt	12.00	15.00
Molybdenum	3.50	5.00
Titanium	2.75	3.25
Aluminum	1.20	1.60
Zirconium	0.02	0.08
Boron	0.003	0.010
Iron	-	2.00
Copper	-	0.10
Lead	-	0.0005 (5 ppm)
Bismuth	-	0.00003 (0.3 ppm)
Selenium	-	0.0003 (3 ppm)
Nickel	remainder	

- 3.1.1 Check Analysis: Composition variations shall meet the applicable requirements of AMS 2269.

- 3.2 Condition: The product shall be supplied in the following condition:

- 3.2.1 Bars: Solution, stabilization, and precipitation heat treated and descaled.

- 3.2.1.1 Bars shall be hot rolled or extruded; round bars shall be ground or turned.

- 3.2.2 Forgings: Solution, stabilization, and precipitation heat treated.

- 3.2.3 Forging Stock: As ordered by the forging manufacturer.

- 3.3 Heat Treatment: Bars and forgings shall be heat treated as follows:

- 3.3.1 Solution: Heat to $1975^{\circ}\text{F} \pm 25$ ($1079^{\circ}\text{C} \pm 14$), hold at heat for 4 hours ± 0.5 , and cool at a rate equivalent to air cool or faster.

- 3.3.2 Stabilization: Heat to $1550^{\circ}\text{F} \pm 15$ ($843^{\circ}\text{C} \pm 8$), hold at heat for 4 hours ± 0.5 , except that blade forgings shall be held at heat for 24 hours ± 1 , and cool in air.

- 3.3.3 Precipitation: Heat to $1400^{\circ}\text{F} \pm 15$ ($760^{\circ}\text{C} \pm 8$), hold at heat for 16 hours ± 1 , and cool in air.

3.4 Properties: The product shall conform to the following requirements:

3.4.1 Bars and Forgings:

3.4.1.1 Hardness: Shall be 32 - 42 HRC, or equivalent, determined in accordance with ASTM E18.

3.4.1.2 Grain Size: Shall be substantially uniform without pronounced segregation of fine and coarse grain areas. Clusters of large germinated grains are not acceptable. Standards for acceptance shall be as agreed upon by purchaser and vendor.

3.4.1.3 Stress-Rupture Properties at 1500°F (816°C): A tensile specimen, maintained at $1500^{\circ}\text{F} + 3$ ($816^{\circ}\text{C} + 2$) while a load sufficient to produce an initial axial stress of 47,500 psi (328 MPa) is applied continuously, shall not rupture in less than 23 hours. The test shall be continued to rupture without change of load. Elongation after rupture, measured at room temperature, shall be not lower than 8% in 40. Tests shall be conducted in accordance with ASTM E139.

3.4.1.3.1 The test of 3.4.1.3 may be conducted using a load higher than required to produce an initial axial stress of 47,500 psi (328 MPa) but load shall not be changed while test is in progress. Time to rupture and elongation requirements shall be as specified in 3.4.1.3.

3.4.1.3.2 When permitted by purchaser, the test of 3.4.1.3 may be conducted using incremental loading. In such case, the load required to produce an initial axial stress of 47,500 psi (328 MPa) shall be used to rupture or for 23 hours, whichever occurs first. After the 23 hours and at intervals of 8 - 16 hours, preferably 8 - 10 hours, thereafter, the stress shall be increased in increments of 5,000 psi (34 MPa). Time to rupture and elongation requirements shall be as specified in 3.4.1.3.

3.4.2 Forging Stock: When a sample of stock is forged to a test coupon and heat treated as in 3.3, specimens taken from the heat treated coupon shall conform to the requirements of 3.4.1.1, 3.4.1.2, and 3.4.1.3. If specimens taken from the stock after heat treatment as in 3.3 conform to the requirements of 3.4.1.1, and 3.4.1.2, and 3.4.1.3, the tests shall be accepted as equivalent to tests of a forged coupon.

3.5 Quality:

3.5.1 Alloy shall be produced by multiple melting using consumable electrode practice in the remelt cycle or shall be induction melted under vacuum.

3.5.2 The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.5.2.1 Forgings shall have substantially uniform macrostructure. Standards for acceptance shall be as agreed upon by purchaser and vendor.

3.5.2.2 Grain flow of die forgings, except in areas which contain flash-line end grain, shall follow the general contour of the forgings showing no evidence of re-entrant grain flow.

3.6 Sizes: Except when exact lengths or multiples of exact lengths are ordered, straight bars will be acceptable in mill lengths of 6 - 24 feet (1.8 - 7.3 m) but not more than 25% of any shipment shall be supplied in lengths of 6 - 9 feet (1.8 - 2.7 m) except that for bars weighing over 25 pounds/foot (37.2 kg/m), short lengths down to 2 feet (610 mm) may be supplied.

3.7 Tolerances: Bars and forging stock shall conform to all applicable requirements of AMS 2261 or MAM 2261.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.5. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests to determine conformance to the following requirements are classified as acceptance tests and shall be performed on each heat or lot as applicable:

4.2.1.1 Composition (3.1) of each heat.

4.2.1.2 Hardness (3.4.1.1), grain size (3.4.1.2), and stress-rupture properties (3.4.1.3) of each lot of bars and forgings.

4.2.1.3 Tolerances (3.7) of bars and forging stock.

4.2.2 Periodic Tests: Tests of forging stock (3.4.2) to demonstrate ability to develop required properties are classified as periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.2.3 Preproduction Tests: Tests of forgings to determine conformance to all applicable technical requirements of this specification when AMS 2375 is specified are classified as preproduction tests and shall be performed prior to or on the first-article shipment of a forging to a purchaser, when a change in material, processing, or both requires reapproval as in 4.4, and when purchaser deems confirmatory testing to be required.

4.2.3.1 For direct U.S. Military procurement of forgings, substantiating test data and, when requested, preproduction forgings shall be submitted to the cognizant agency as directed by the procuring activity, contracting officer, or request for procurement.