



AEROSPACE MATERIAL

Society of Automotive Engineers, Inc.
TWO PENNSYLVANIA PLAZA, NEW YORK, N. Y. 10001

AMS 5715

Issued 5-15-72
Revised

ALLOY BARS, FORGINGS, AND RINGS, CORROSION AND HEAT RESISTANT Nickel Base - 23Cr - 14Fe - 1.35Al

1. SCOPE:

1.1 Form: This specification covers a corrosion and heat resistant nickel-base alloy in the form of bars, forgings, flash welded rings, and stock for forging or flash welded rings.

1.2 Application: Primarily for parts and assemblies requiring corrosion and oxidation resistance at temperatures up to 2200 F (1204 C) and where such parts may require welding during fabrication.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from Society of Automotive Engineers, Inc., Two Pennsylvania Plaza, New York, New York 10001.

2.1.1 Aerospace Material Specifications:

AMS 2261 - Tolerances, Nickel, Nickel Base, and Cobalt Base Alloy
Bars and Forging Stock

AMS 2269 - Chemical Check Analysis Limits, Wrought Nickel and
Nickel Base Alloys

AMS 2350 - Standards and Test Methods

AMS 2371 - Quality Assurance Sampling of Corrosion and Heat Resistant
Alloys, Wrought Products Except Forgings

AMS 2375 - Approval and Control of Critical Forgings

AMS 2808 - Identification, Forgings

AMS 7490 - Rings, Flash Welded, Corrosion and Heat Resistant Austenitic
Steels and Austenitic-Type Alloys

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, Pennsylvania 19103.

ASTM E8 - Tension Testing of Metallic Materials

ASTM E354 - Chemical Analysis of High-Temperature, Electrical, Magnetic and
Other Similar Iron, Nickel, and Cobalt-Base Alloys

2.3 Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, Pennsylvania 19120.

2.3.1 Federal Standards:

Federal Test Method Standard No. 151 - Metals; Test Methods

3. TECHNICAL REQUIREMENTS:

3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E354, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other approved analytical methods.

	min	max
Carbon	--	0.10
Manganese	--	1.00
Silicon	--	0.50
Sulfur	--	0.015
Chromium	21.00 - 25.00	
Nickel	58.00 - 63.00	
Aluminum	1.00 - 1.70	
Titanium	--	0.60
Boron	--	0.006
Copper	--	1.00
Iron	remainder	

3.1.1 Check Analysis: Composition variations shall meet the requirements of AMS 2269.

3.2 Condition: The product shall be supplied in the following condition:

3.2.1 Bars: Hot finished and annealed; round bars shall be ground or turned.

3.2.2 Forgings and Flash Welded Rings: Annealed. Surface finish shall be as agreed upon by purchaser and the forging or flash welded ring manufacturer.

3.2.2.1 Flash welded rings shall not be supplied unless specified or permitted on purchaser's part drawing. When supplied, they shall be manufactured in accordance with AMS 7490.

3.2.3 Stock for Forging or Flash Welded Rings: As ordered by the forging or flash welded ring manufacturer.

3.3 Properties: Tensile properties of bars, forgings, and flash welded rings shall be as follows, determined in accordance with ASTM E8:

Tensile Strength, min	80,000 psi (552 MPa)
Yield Strength at 0.2% Offset, min	30,000 psi (207 MPa)
Elongation in 2 in. (50.8 mm) or 4D, min	35%

3.4 Quality: The product shall be uniform in quality and condition, clean, sound, and free from foreign materials and from internal and external imperfections detrimental to fabrication or to performance of parts. Forgings shall have substantially uniform macrostructure and grain flow.

3.5 Tolerances: Unless otherwise specified, tolerances for bars and forging stock shall conform to all applicable requirements of AMS 2261.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor shall supply all samples and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.5. Purchaser reserves the right to perform such confirmatory testing as he deems necessary to assure that the product conforms to the requirements of this specification.

4.2 Classification of Tests: Tests to determine conformance to all technical requirements of this specification are classified as acceptance or routine control tests.

4.3 Sampling: Bars, flash welded rings, and stock for forging and flash welded rings shall be sampled in accordance with AMS 2371; forging stock shall be sampled for composition only. Forgings shall be sampled as agreed upon by purchaser and vendor.

4.4 Approval: When specified, approval and control of critical forgings shall be in accordance with AMS 2375.

4.5 Reports:

- 4.5.1 The vendor of the product shall furnish with each shipment three copies of a report of the results of tests for chemical composition of each heat in the shipment and the results of tests on each size from each heat to determine conformance to the tensile property requirements of this specification. This report shall include the purchase order number, material specification number, heat number, annealing temperature used, size, and quantity from each heat. If forgings are supplied, the part number and the size and melt source of stock used to make the forgings shall also be included.
- 4.5.2 The vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, material specification number, contractor or other direct supplier of material, part number, and quantity. When material for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of material to determine conformance to the requirements of this specification, and shall include in the report a statement that the material conforms, or shall include copies of laboratory reports showing the results of tests to determine conformance.
- 4.6 Resampling and Retesting: If any specimen used in the above tests fails to meet the specified requirements, disposition of the product may be based on the results of testing three additional specimens for each original nonconforming specimen. Failure of any retest specimen to meet the specified requirements shall be cause for rejection of the product represented and no additional testing shall be permitted. Results of all tests shall be reported.

5. PREPARATION FOR DELIVERY:

5.1 Identification: The product shall be identified as follows:

5.1.1 Bars:

- 5.1.1.1 Each straight bar 0.500 in. (12.70 mm) and over in diameter or least width of flat surface shall be marked in a row of characters recurring at intervals not greater than 3 ft (914 mm) with AMS 5715, heat number, and manufacturer's identification. The characters shall be of such size as to be clearly legible, shall be applied using a suitable marking fluid, and shall be capable of being removed in hot alkaline cleaning solution without rubbing. The markings shall have no deleterious effect on the material or its performance and shall be sufficiently stable to withstand normal handling.
- 5.1.1.2 Straight bars less than 0.500 in. (12.70 mm) in diameter or least width of flat surface shall be securely bundled and identified by a metal or plastic tag embossed with the purchase order number, AMS 5715, heat number, nominal size, and manufacturer's identification and attached to each bundle or shall be boxed and the box marked with the same information.
- 5.1.1.3 Coiled bars shall be securely bundled and identified by a metal or plastic tag embossed with the purchase order number, AMS 5715, heat number, nominal size, and manufacturer's identification and attached to each coil or shall be boxed and the box marked with the same information.

5.1.2 Forgings: In accordance with AMS 2808.

5.1.3 Flash Welded Rings and Stock for Forging or Flash Welded Rings: As agreed upon by purchaser and vendor.

5.2 Packaging: The product shall be prepared for shipment in accordance with commercial practice to assure carrier acceptance and safe transportation to the point of delivery. Packaging shall conform to carrier rules and regulations applicable to the mode of transportation.