

AERONAUTICAL MATERIAL SPECIFICATIONS

AMS 5741

SOCIETY OF AUTOMOTIVE ENGINEERS, Inc. 485 Lexington Ave., New York 17, N.Y.

Issued 6-15-59

Revised

STEEL, CORROSION AND HEAT RESISTANT

13.5Cr - 26Ni - 1.75Mo - 3Ti

Consumable Electrode Vacuum Melted

1. ACKNOWLEDGMENT: A vendor shall mention this specification number in all quotations and when acknowledging purchase orders.
2. FORM: Bars, forgings, forging stock, and heading stock.
3. APPLICATION: Primarily for parts, such as turbine discs and rotors, shafts, buckets or blades, vanes, bolts, dowels, flanges, and fittings, requiring high strength up to 1350 F and oxidation resistance up to 1500 F.
4. COMPOSITION:

		Check Analysis	
		Under Min	Over Max
Carbon	0.08 max	--	0.01
Manganese	1.25 - 2.00	0.04	0.04
Silicon	0.10 - 0.80	0.05	0.05
Phosphorus	0.040 max	--	0.005
Sulfur	0.030 max	--	0.005
Chromium	12.00 - 15.00	0.15	0.15
Nickel	24.00 - 28.00	0.20	0.20
Molybdenum	1.25 - 2.25	0.05	0.05
Titanium	2.70 - 3.30	0.05	0.05
Boron	0.025 - 0.12	0.005	0.01
Aluminum	0.25 max	--	0.05
Copper	0.25 max	--	0.03

5. CONDITION:
 - 5.1 Bars: Solution and precipitation heat treated, unless otherwise specified. Bars 2.75 in. and less in diameter or distance between parallel sides shall be cold finished.
 - 5.2 Forgings: Solution and precipitation heat treated and descaled, unless otherwise specified.
 - 5.3 Stock for Forging or Headings: As ordered by the forging or heading manufacturer.

6. TECHNICAL REQUIREMENTS:

6.1 Bars and Forgings:

- 6.1.1 Heat Treatment: The product shall be solution heat treated by heating to not lower than 1900 F but not higher than 2100 F, holding at heat for not less than 1 hr, and quenching in oil or water. It shall then be precipitation heat treated by heating to not lower than 1300 F but not higher than 1425 F, holding at heat for not less than 5 hr, cooling to 1200 F $\pm$ 15, holding at heat for not less than 20 hr, and cooling in air.

6.1.1.1 Bars 0.25 in. and less in diameter may be air cooled from the solution heat treating temperature.

6.1.2 Tensile Properties: Tensile test specimens cut from the product and tested at room temperature shall conform to the following requirements:

Tensile Strength, psi	155,000 min
Yield Strength at 0.2% Offset or at 0.0122 in. in 2 in. Extension Under Load ($E = 29,100,000$), psi	120,000 min
Elongation, % in 4D	12 min
Reduction of Area, %	15 min

6.1.2.1 When radial tensile test specimens are machined tangentially from approximately the center of large disc forgings (over 50 sq in. in cross sectional area), the elongation may be as low as 10% and the reduction of area as low as 12%. Specimens machined in other directions from this location are not required.

6.1.2.2 When a dispute occurs between purchaser and vendor over the yield strength value, yield strength determined by the offset method shall apply.

6.1.3 Hardness: Shall be Brinell 311 - 375 or equivalent.

6.1.4 Stress Rupture Test at 1300 F: A combination smooth and notched test specimen machined to the dimensions shown in Figure 1 and Table I, maintained at $1300\text{ F} + 3$ while an axial stress of 65,000 psi is applied continuously, shall not rupture in less than 23 hours. The test shall be continued to rupture, either maintaining the same stress or increasing the stress in 5000 psi increments after 48 hr and at intervals of not less than 8 hr thereafter. Rupture shall occur in the smooth section and elongation of this section after rupture, measured at room temperature, shall be not less than 5% in 4D if the specimen ruptures in 48 hr or less and not less than 3% in 4D if the specimen ruptures in more than 48 hours.

6.1.4.1 As an alternate procedure, separate smooth and notched test specimens, machined from adjacent sections of the same piece, with gage sections conforming to the respective dimensions of Table I may be tested individually under the above conditions, including increase of stress after 48 hours. The smooth specimen shall not rupture in less than 23 hr and elongation after rupture, measured at room temperature, shall be as specified above. The notched specimen need not be tested to rupture but shall not rupture in less time than the companion smooth specimen.

6.2 Stock for Forging or Heading: When a sample of stock is forged to a test coupon and heat treated as in 6.1.1, specimens taken from the heat treated coupon shall conform to the requirements of 6.1.2, 6.1.3, and 6.1.4. If specimens taken from the stock after heat treatment as in 6.1.1 conform to the requirements of 6.1.2, 6.1.3, and 6.1.4, the tests shall be accepted as equivalent to tests of the forged coupon.

7. QUALITY: Material shall be multiple melted using consumable electrode practice in the remelt cycle, unless otherwise permitted, and shall be uniform in quality and condition, clean, sound, and free from foreign materials and from internal and external imperfections detrimental to fabrication or to performance of parts.

8. TOLERANCES: Unless otherwise specified, tolerances shall conform to the latest issue of AMS 2241 as applicable and as specified below: