

Issued 1977-07
Revised 2006-08
Reaffirmed 2012-02

Superseding AMS5747C

Nickel Alloy, Corrosion and Heat-Resistant, Bars, Forgings, and Rings
72Ni - 15.5Cr - 0.95Cb(Nb) - 2.5Ti - 0.70Al - 7.0Fe
Solution Heat Treated, Precipitation Hardenable
(Composition similar to UNS N07750)

RATIONALE

AMS5747D has been reaffirmed to comply with the SAE five-year review policy.

1. SCOPE

1.1 Form

This specification covers a corrosion and heat-resistant nickel alloy in the form of bars, forgings, flash welded rings, and stock for forging or flash welded rings.

1.2 Application

These products have been used typically for parts requiring high strength in the range 800 to 1100 °F (427 to 593 °C), but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order form a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or 724-776-4970 (outside USA), or www.sae.org.

AMS 2261	Tolerances, Nickel, Nickel Alloy, and Cobalt Alloy Bars, Rods, and Wire
AMS 2269	Chemical Check Analysis Limits, Nickel, Nickel Alloys and Cobalt Alloys
AMS 2371	Quality Assurance Sampling and Testing, Corrosion and Heat-Resistant Steels and Alloys, Wrought Products and Forging Stock
AMS 2374	Quality Assurance Sampling and Testing, Corrosion and Heat-Resistant Steel and Alloy Forgings
AMS 2806	Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Corrosion and Heat-Resistant Steels and Alloys
AMS 2808	Identification, Forgings
AMS 7490	Rings, Flash Welded, Corrosion and Heat-Resistant Austenitic Steels, Austenitic-Type Iron, Nickel or Cobalt Alloys, or Precipitation-Hardenable Alloys

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2012 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
SAE WEB ADDRESS: <http://www.sae.org>

**SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS5747D>**

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, or www.astm.org.

ASTM E 8	Tension Testing of Metallic Materials
ASTM E 10	Brinell Hardness of Metallic Materials
ASTM E 354	Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 354, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - COMPOSITION

Element	min	max
Carbon	--	0.08
Manganese	--	1.00
Silicon	--	0.50
Phosphorus (3.1.1)	--	0.015
Sulfur	--	0.010
Chromium	14.00	17.00
Nickel	70.00	--
Columbium (Niobium)	0.70	1.20
Titanium	2.25	2.75
Aluminum	0.40	1.00
Iron	5.00	9.00
Cobalt (3.1.1)	--	1.00
Copper	--	0.50

3.1.1 Determination not required for routine acceptance.

3.1.2 Check Analysis

Composition variations shall meet the applicable requirements of AMS 2269.

3.2 Condition

The product shall be supplied in the following condition:

3.2.1 Bars

Hot finished, solution heat treated, and descaled.

3.2.1.1 Round bars shall be ground or turned except that bars under 0.50 inch (12.7 mm) in nominal diameter shall be cold drawn when so ordered.

3.2.2 Forgings and Flash Welded Rings

Solution heat treated.

3.2.2.1 Flash welded rings shall not be supplied unless specified or permitted on purchaser's part drawing. When supplied, rings shall be manufactured in accordance with AMS 7490.

3.2.3 Stock for Forging or Flash Welded Rings

As ordered by the forging or flash welded ring manufacturer.

3.3 Heat Treatment

Bars, forgings, and flash welded rings shall be solution treated by heating to $1800^{\circ}\text{F} \pm 25$ ($982^{\circ}\text{C} \pm 14$), holding at heat for a time commensurate with cross-sectional thickness, and cooling at a rate equivalent to an air cool or faster.

3.4 Properties

The product shall conform to the following requirements:

3.4.1 Bars, Forgings, and Flash Welded Rings

3.4.1.1 As Solution Heat Treated

3.4.1.1.1 Hardness

Shall be not higher than 321 HB, or equivalent (See 8.2), determined in accordance with ASTM E 10.

3.4.1.2 After Precipitation Heat Treatment

The product shall have the following properties after being precipitation heat treated by heating to $1350^{\circ}\text{F} \pm 15$ ($732^{\circ}\text{C} \pm 8$), holding at heat for 8 hours ± 0.5 , cooling at a rate of $100^{\circ}\text{F} \pm 15$ ($56^{\circ}\text{C} \pm 8$) degrees per hour to $1150^{\circ}\text{F} \pm 15$ ($621^{\circ}\text{C} \pm 8$), holding at $1150^{\circ}\text{F} \pm 15$ ($621^{\circ}\text{C} \pm 8$) for 8 hours ± 1 , and cooling in air. Instead of the 100°F (56°C) degrees per hour cooling rate to $1150^{\circ}\text{F} \pm 15$ ($621^{\circ}\text{C} \pm 8$), the product may be furnace cooled at any rate provided the time at $1150^{\circ}\text{F} \pm 15$ ($621^{\circ}\text{C} \pm 8$) is adjusted to give a total precipitation heat treatment time of 18 hours.

3.4.1.2.1 Tensile Properties

Shall be as shown in Table 2 for product up to 4.00 inches (101.6 mm) in nominal diameter or least distance between parallel sides, determined in accordance with ASTM E 8; properties apply to specimens taken with the axis approximately parallel to the grain flow and to specimens taken in the radial direction and in the tangential direction at the rim of disc forgings.

TABLE 2A - MINIMUM TENSILE PROPERTIES, INCH/POUND UNITS

Nominal Diameter or Least Distance Between Parallel Sides Inches	Tensile Strength ksi	Yield Strength at 0.2% Offset ksi	Elongation in 4D %	Reduction of Area %
Up to 2.50, excl	170.0	115.0	18	18
2.50 to 4.00, excl	170.0	115.0	15	15

TABLE 2B - MINIMUM TENSILE PROPERTIES, SI UNITS

Nominal Diameter or Least Distance Between Parallel Sides Millimeters	Tensile Strength MPa	Yield Strength at 0.2% Offset MPa	Elongation in 4D %	Reduction of Area %
Up to 63.5, excl	1172	793	18	18
63.5 to 101.6, excl	1172	793	15	15

3.4.1.2.2 Hardness

Shall be 302 to 388 HB, or equivalent (See 8.2), determined in accordance with ASTM E 10.

3.4.2 Forging Stock

When a sample of stock is forged to a test coupon and heat treated as in 3.3 and 3.4.1.2, specimens taken from the heat treated coupon shall conform to the requirements of 3.4.1.2.1 and 3.4.1.2.2. If specimens taken from the stock after heat treatment as in 3.3 and 3.4.1.2 conform to the requirements of 3.4.1.2.1 and 3.4.1.2.2, the tests shall be accepted as equivalent to tests of a forged coupon.

3.4.3 Stock for Flash Welded Rings

Specimens taken from the stock after heat treatment as in 3.3 and 3.4.1.2 shall conform to the requirements of 3.4.1.2.1 and 3.4.1.2.2.

3.5 Quality

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.5.1 Grain flow of die forgings, except in areas that contain flash-line end grain, shall follow the general contour of the forgings showing no evidence of reentrant grain flow.

3.6 Tolerances

Bars shall conform to all applicable requirements of AMS 2261.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.

4.2 Classification of Tests

4.2.1 Acceptance Tests

The following requirements are acceptance tests and shall be performed on each heat or lot as applicable:

4.2.1.1 Composition (3.1) of each heat (See 3.1.1).

4.2.1.2 Hardness (3.4.1.1.1) of each lot of bars, forgings, and flash welded rings as solution heat treated.

4.2.1.3 Tensile properties (3.4.1.2.1) and hardness (3.4.1.2.2) of each lot of bars, forgings, and flash welded rings after precipitation heat treatment.

4.2.1.4 Tolerances (3.6) of bars and forging stock.

4.2.2 Periodic Tests

Forging stock (3.4.2) and of stock for flash welded rings (3.4.3) to demonstrate ability to develop required properties and grain flow of die forgings (3.5.1) are periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.