



AEROSPACE MATERIAL SPECIFICATION

AMS5769**REV. F**

Issued 1960-06
Revised 2003-10
Reaffirmed 2014-10

Superseding AMS5769E

Alloy, Corrosion and Heat-Resistant, Bars, Forgings, and Rings,
21Cr - 20Ni - 20Co - 3.0Mo - 2.5W - 1.0(Cb+Ta) - 0.15N - 32Fe
Solution Heat Treated
(Composition similar to UNS R30155)

RATIONALE

AMS5769F has been reaffirmed to comply with the SAE five year review policy.

1. SCOPE:

1.1 Form:

This specification covers a corrosion and heat-resistant alloy in the form of bars, forgings, flash welded rings, and stock for forging, flash welded rings, or heading.

1.2 Application:

These products have been used typically for parts, such as turbine rotors, shafts, blades, and bolts, requiring high strength up to 1350 °F (732 °C) and oxidation resistance up to 1800 °F (982 °C), but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS:

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent supplied herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001 or www.sae.org.

AMS 2248	Chemical Check Analysis Limits, Corrosion and Heat-Resistant Steels and Alloys, Maraging and Other Highly-Alloyed Steels, and Iron Alloys
AMS 2261	Tolerances, Nickel, Nickel Alloy, and Cobalt Alloy Bars, Rods, and Wire
AMS 2371	Quality Assurance Sampling and Testing, Corrosion and Heat-Resistant Steels and Alloys, Wrought Products and Forging Stock
AMS 2374	Quality Assurance Sampling and Testing, Corrosion and Heat-Resistant Steel and Alloy Forgings

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2014 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

**SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS5769F>**

2.1 (Continued):

AMS 2806	Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Corrosion and Heat-Resistant Steels and Alloys
AMS 2808	Identification, Forgings
AMS 7490	Rings, Flash Welded, Corrosion and Heat-Resistant Austenitic Steels, Austenitic- Type Alloys, Nickel or Cobalt Alloys, or Precipitation-Hardenable Alloys

2.2 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959 or www.astm.org.

ASTM E 10	Brinell Hardness of Metallic Materials
ASTM E 139	Conducting Creep, Creep-Rupture, and Stress-Rupture Tests of Metallic Materials
ASTM E 353	Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 353, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

Element	min	max
Carbon	0.08	0.16
Manganese	1.00	2.00
Silicon	--	1.00
Phosphorus	--	0.040
Sulfur	--	0.030
Chromium	20.00	22.50
Nickel	19.00	21.00
Cobalt	18.50	21.00
Molybdenum	2.50	3.50
Tungsten	2.00	3.00
Columbium	0.75	1.25
Nitrogen	0.10	0.20
Iron	remainder	

3.1.1 Check Analysis: Composition variations shall meet the applicable requirements of AMS 2248.

3.2 Condition:

The product shall be supplied in the following condition:

3.2.1 Bars, Forgings, and Flash Welded Rings: Solution heat treated. Forgings shall be descaled.

3.2.1.1 Flash welded rings shall not be supplied unless specified or permitted on purchaser's part drawing. When supplied, rings shall be manufactured in accordance with AMS 7490.

3.2.2 Stock for Forging, Flash Welded Rings, or Heading: As ordered by the forging, flash welded ring, or heading manufacturer.

3.3 Heat Treatment:

Bars, forgings, and flash welded rings shall be solution heat treated by heating to $2150^{\circ}\text{F} \pm 25$ ($1177^{\circ}\text{C} \pm 14$), holding at heat for not less than 1 hour, and quenching in water.

3.4 Properties:

The product shall conform to the following requirements:

3.4.1 Bars, Forgings, and Flash Welded Rings:

3.4.1.1 Hardness: Shall be as follows, determined in accordance with ASTM E 10:

3.4.1.1.1 Bars and Forgings: 156 to 217 HB, or equivalent (See 8.2).

3.4.1.1.2 Flash Welded Rings: 156 to 241 HB, or equivalent (See 8.2).

3.4.1.2 Stress-Rupture Properties at 1350°F (732°C): A tensile specimen, maintained at $1350^{\circ}\text{F} \pm 3$ ($732^{\circ}\text{C} \pm 2$) while a load sufficient to produce an initial axial stress of 32.0 ksi (221 MPa) or higher is applied continuously, shall not rupture in less than 23 hours. The test shall be continued to rupture without change of load. Elongation after rupture, measured at room temperature, shall be not less than 10% in 4D. Test shall be conducted in accordance with ASTM E 139.

3.4.1.2.1 The test of 3.4.1.2 may be conducted using incremental loading. In such case, the load required to produce an initial axial stress of 32.0 ksi (221 MPa) or higher shall be used to rupture or for 23 hours, whichever occurs first. After the 23 hours and at intervals of 8 to 16 hours thereafter, the stress shall be increased in increments of 2.0 ksi (14 MPa). Time to rupture and elongation requirements shall be as specified in 3.4.1.2.

3.4.2 Forging Stock: When a sample of stock is forged to a test coupon and heat treated as in 3.3, specimens taken from the heat treated coupon shall conform to the requirements of 3.4.1.1 and 3.4.1.2. If specimens taken from the stock, after heat treatment as in 3.3, conform to the requirements of 3.4.1.1 and 3.4.1.2, the tests shall be accepted as equivalent to tests of a forged coupon.

3.4.3 Stock for Flash Welded Rings or Heading: Specimens taken from the stock, after heat treatment as in 3.3, shall conform to the requirements of 3.4.1.1 and 3.4.1.2.

3.5 Quality:

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.5.1 Grain flow of die forgings, except in areas which contain flash-line end grain, shall follow the general contour of the forgings showing no evidence of reentrant grain flow.

3.6 Tolerances:

Bars shall conform to all applicable requirements of AMS 2261.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: The following requirements are acceptance tests and shall be performed on each heat or lot as applicable:

4.2.1.1 Composition (3.1) of each heat.

4.2.1.2 Hardness (3.4.1.1) and stress-rupture properties (3.4.1.2) of each lot of bars, forgings, and flash welded rings.

4.2.1.3 Tolerances (3.6) of bars.

4.2.2 Periodic Tests: Tests of forging stock (3.4.2) and of stock for flash welded rings or heading (3.4.3) to demonstrate ability to develop required properties and grain flow of die forgings (3.5.1) are periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.