

AEROSPACE MATERIAL SPECIFICATION

Submitted for recognition as an American National Standard



AMS 5785F

Issued	JUL 1948
Revised	JAN 1987
Noncurrent	AUG 1992
Cancelled	MAR 1999

Superseding AMS 5785E

Steel Welding Electrode, Covered, Corrosion and Heat Resistant
28.5Cr - 9.5Ni

UNS S64299/W31310

CANCELLATION NOTICE

This specification has been declared "CANCELLED" by the Aerospace Materials Division, SAE, as of March 1999, and has been superseded by AWS A5.4 E312. The requirements of the latest issue of AWS A5.4 E312 shall be fulfilled whenever reference is made to the cancelled AMS 5785. By this action, this document will remain listed in the Numerical Section of the Index of Aerospace Material Specifications noting that it is superseded by AWS A5.4 E312.

SAENORM.COM : Click to view the full PDF of AMS 5785F

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 1999 Society of Automotive Engineers, Inc.
All rights reserved.

QUESTIONS REGARDING THIS DOCUMENT:
TO PLACE A DOCUMENT ORDER:
SAE WEB ADDRESS:

(724) 772-7161
(724) 776-4970
<http://www.sae.org>

FAX: (724) 776-0243
FAX: (724) 776-0790

Printed in U S A



Reproduced By GLOBAL
ENGINEERING DOCUMENTS
With The Permission Of SAE
Under Royalty Agreement

1. SCOPE:**1.1 Form:**

This specification covers a corrosion and heat resistant steel in the form of covered welding electrodes.

1.2 Application:

Primarily for shielded-metal-arc welding of parts fabricated from material of similar or dissimilar composition, particularly when the weld zone is required to have corrosion and heat resistance comparable to that of the parent metal.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications:

Available from Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2350 Standards and Test Methods

2.2 ASTM Publications:

Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM E353 Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys

2.3 Government Publications:

Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Federal Standards:

Federal Test Method Standard No. 151 - Metals; Test Methods

2.3.2 Military Specifications:

MIL-W-10430 - Welding Rods and Electrodes; Preparation for Delivery of

2.4 AWS Publications:

Available from American Welding Society, Inc., 2501 North West 7th Street, Miami, FL 33125.

AWS A5.4 - Corrosion-Resisting Chromium and Chromium-Nickel Steel Covered Welding Electrodes

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Weld metal deposited from electrodes shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E353, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other analytical methods approved by purchaser.

	min	max
Carbon	0.08	0.15
Manganese	1.00	2.50
Silicon	--	0.75
Phosphorus	--	0.04
Sulfur	--	0.03
Chromium	26.00	31.00
Nickel	8.50	10.50
Molybdenum	--	0.50
Copper	--	0.50

- 3.1.1 Weld Pads for Chemical Analysis: The referee procedure for making pads of weld metal and removing samples for chemical analysis shall be AWS A5.4.

3.2 Type:

Coverings shall be suitable for the following usability characteristics:

Type Designation	AWS Designation	Weld Position	Current
A	-15	Flat, Vertical, Overhead, and Horizontal	DC
B	-16	Flat, Vertical, Overhead, and Horizontal	DC - AC
C	-15	Horizontal Fillets, Flat	DC
D	-16	Horizontal Fillets, Flat	DC - AC

3.2.1 When DC is specified, reverse polarity (electrode positive) is required.

3.2.2 Lime type coverings are required for Types A and C electrodes, unless otherwise specified.

3.2.3 Type A electrodes shall be supplied, unless otherwise specified.

3.3 Properties:

Electrodes shall conform to the following requirements:

3.3.1 Weldability: Electrodes shall demonstrate good weldability and shall flow smoothly and evenly when used under the conditions specified in 3.2.

3.3.2 Burn-Off: The covering shall be consumed uniformly all around and shall not burn back from the core wire under proper welding conditions. Heating of the electrodes during welding shall not cause injurious blistering of the covering within the ranges of current values recommended by the manufacturer.

3.3.3 Grip Portion and Arc Ends: A portion of the electrode 0.75 - 1.25 in. (20 - 30 mm) long on end-grip rods and 1.5 - 2.0 in. (40 - 50 mm) long on center-grip rods shall be bare to permit good electrical contact with the electrode holder. The arc end of the electrodes shall be sufficiently bare to permit easy striking of the arc but the length of this bare section, measured from the end of the electrode to the point where the full cross-section of the covering begins, shall not exceed the diameter of the bare wire, and in no case shall it exceed 1/8 in. (3 mm).

3.3.4 Cleaning: Slag produced during welding shall be readily removable with hand tools.

3.4 Quality:

- 3.4.1 Core Wire: Shall be uniform in quality and condition, cylindrical, clean, sound, and free from foreign materials and from imperfections detrimental to weld quality.
- 3.4.2 Covering: Shall be uniform in quality, tightly adherent, and free from abnormal scabs, blisters, pockmarks, bruises, and other surface defects and shall withstand normal handling without damage. It shall not be harmfully hygroscopic and shall not adversely affect weld quality.

3.5 Standard Sizes and Lengths:

The sizes and lengths in Table I are standard.

TABLE I

Nominal Diameter of Core Wire Inch	Length Inches
1/16, 5/64	9 and 18
3/32	9, 12, and 18
1/8, 5/32, 3/16, 1/4	14

TABLE I (SI)

Nominal Diameter of Core Wire Millimetres	Length Millimetres
1.5, 2.0	230 and 455
2.5	230, 305, and 455
3.0, 4.0, 5.0, 6.5	355

- 3.5.1 End-grip electrodes shall be supplied in all lengths except 18 in. (455 mm) where center-grip electrodes are required, unless otherwise specified.

3.6 Tolerances:

Shall be as follows, unless otherwise specified:

- 3.6.1 Electrodes shall not vary in length more than $\pm 1/4$ in. (± 6.5 mm) from the length ordered.
- 3.6.2 Electrode core wire shall not vary in diameter more than ± 0.002 in. (± 0.05 mm) from the size ordered.

- 3.6.3 Overall diameter of the covered electrodes shall not vary more than 4% from that of the approved sample.
- 3.6.4 Covering shall be concentric with the core wire to the extent that the maximum core-plus-one-covering dimension shall not exceed the minimum core-plus-one-covering dimension by more than 5 % of the minimum core-plus-one-covering dimension.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of electrodes shall supply all samples and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.5. Purchaser reserves the right to perform such confirmatory testing as he deems necessary to ensure that the electrodes conform to the requirements of this specification.

4.2 Classification of Tests:

- 4.2.1 Acceptance Tests: Tests to determine conformance to requirements for composition (3.1), grip portion and arc ends (3.3.3), sizes (3.5), and tolerances (3.6) are classified as acceptance tests and shall be performed on each control number of electrodes.
- 4.2.2 Periodic Tests: Tests to determine conformance to requirements for weldability (3.3.1), burn-off (3.3.2), and cleaning (3.3.4) are classified as periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.
- 4.2.3 Preproduction Tests: Tests to determine conformance to all technical requirements of this specification are classified as preproduction tests and shall be performed on the first-article shipment of electrodes to a purchaser, when a change in material or processing requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.
- 4.2.3.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, the contracting officer, or the request for procurement.

4.3 Sampling:

Shall be as agreed upon by purchaser and vendor; a control number shall be a designation indicating batch processing and core wire heat number.

4.4 Approval:

- 4.4.1 Sample electrodes shall be approved by purchaser before electrodes for production use are supplied, unless such approval be waived.

4.4.2 Vendor shall use materials, manufacturing and methods of inspection on production electrodes which are essentially the same as those used on the approved sample electrodes. If necessary to make any change in covering formulation or in manufacturing procedures, processes, or methods of inspection, vendor shall submit for reapproval a statement of the proposed changes in material and processing and, when requested, sample electrodes. Production electrodes incorporating the revised procedures shall not be shipped prior to receipt of reapproval.

4.5 Reports:

4.5.1 The vendor of electrodes shall furnish with each shipment three copies of a report stating that the electrodes conform to the technical requirements of this specification. This report shall include the purchase order number, material specification number and its revision letter, control number, size, and quantity. When requested by purchaser, the vendor shall also include in the report the composition of the deposited weld metal for each heat in the shipment.

4.5.2 When assemblies requiring use of these electrodes are supplied, the assembly manufacturer shall inspect each lot of electrodes to determine conformance to the technical requirements of this specification and shall furnish with each shipment three copies of a report stating that the electrodes conform. This report shall include the purchase order number, material specification number and its revision letter, assembly number, and quantity.

4.6 Resampling and Retesting:

If any specimen used in the above tests fails to meet the specified requirements, disposition of the electrodes may be based on the results of testing three additional specimens for each original nonconforming specimen. Failure of any retest specimen to meet the specified requirements shall be cause for rejection of the electrodes represented and no additional testing shall be permitted. Results of all tests shall be reported.

5. PREPARATION FOR DELIVERY:

5.1 Identification:

5.1.1 Individual Electrodes:

5.1.1.1 At least one legible imprint of the AWS classification shall be applied to the electrode covering as near as practical to the grip of the core wire and within 2-1/2 in. (65 mm) of the grip end. In the case of center-grip electrodes, the imprint shall be applied to the electrode covering as above and upon both sides of the center-grip (bare core wire) area. The prefix letter "E" in the electrode classification may be omitted from the imprint on the electrode covering.

5.1.1.2 The number of the imprinted electrode classification shall be of bold block type and of sufficient size and color contrast to be legible before and after normal welding applications.