

**AEROSPACE
MATERIAL
SPECIFICATION**

Submitted for recognition as an American National Standard

SAE AMS 5793

Issued 1-1-86

**POWDER, PLASMA SPRAY
95Ni - 5Al**

1. SCOPE:

1.1 Form: This specification covers a nickel-aluminum aggregate in the form of powder.

1.2 Application: Primarily used as an undercoat for plasma spray coatings, as a constituent in plasma spray powders, or for dimensional buildup.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2350 - Standards and Test Methods

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM B214 - Sieve Analysis of Granular Metal Powders

ASTM C117 - Material Finer Than 75- μ m (No. 200) Sieve in Mineral Aggregates by Washing

2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Military Standards:

MIL-STD-794 - Parts and Equipment, Procedures for Packaging and Packing of

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

3. TECHNICAL REQUIREMENTS:

- 3.1 Composition: Powder shall consist of an aggregate of nickel and aluminum particles. Composition of the aggregate shall conform to the following percentages by weight, determined by spectrographic or other analytical methods approved by purchaser:

	min	max
Aluminum	4.0	5.5
Impurities, Total (3.1.1)	--	2.50
Nickel		remainder

- 3.1.1 If determined, present as volatile phenolic binder.

- 3.2 Properties: Powder shall conform to the following requirements:

- 3.2.1 Particle Size Determination: Powder shall be supplied with the following particle size distribution. Sieve analysis shall be conducted in accordance with ASTM B214 or ASTM C117; the method of testing used shall be reported.

U.S. Sieve Size	% by weight, min	
	min	max
Retained on No. 140 (106 μm)	--	0.5
Retained on No. 170 (90 μm)	--	5.0
Retained on No. 325 (45 μm)	90	--

- 3.2.2 Flowability: Powder shall be visually examined for free flowing through a suitable powder feeder and spray gun. The powder stream shall allow the flow to be consistent and without excessive pulsation.

- 3.2.3 Plasma Spraying: Powder shall produce acceptable plasma spray coatings; standards for acceptance and method of test shall be as agreed upon by purchaser and vendor.

- 3.3 Quality: Powder, as received by purchaser, shall be thoroughly blended, uniform in color and quality, dry, and free from foreign materials and from imperfections detrimental to its spraying qualities.

4. QUALITY ASSURANCE PROVISIONS:

- 4.1 Responsibility for Inspection: The vendor of powder shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.5. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the powder conforms to the requirements of this specification.

4.2 Classification of Tests: Tests to determine conformance to all technical requirements of this specification are classified as acceptance tests and as preproduction tests and shall be performed prior to or on the initial shipment of powder to a purchaser, on each lot, when a change in material, processing, or both requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.

4.2.1 For direct U. S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, the contracting officer, or the request for procurement.

4.3 Sampling: Shall be as follows:

4.3.1 For Acceptance Tests: Sufficient powder shall be taken at random from each lot to perform all required tests. The number of determinations for each requirement shall be as specified in the applicable test procedure or, if not specified therein, not less than three.

4.3.1.1 A lot shall be all powder produced in a single production run from the same batch of raw materials under the same fixed conditions and presented for vendor's inspection at one time. A lot may be packaged in small quantities and delivered separately under the basic lot approval provided lot identification is maintained.

4.3.1.2 When a statistical sampling plan and acceptance quality level (AQL) have been agreed upon by purchaser and vendor, sampling shall be in accordance with such plan in lieu of sampling as in 4.3.1 and the report of 4.5.1 shall state that such plan was used.

4.3.2 For Preproduction Tests: As agreed upon by purchaser and vendor.

4.4 Approval:

4.4.1 Sample powder shall be approved by purchaser before powder for production use is supplied, unless such approval be waived by purchaser. Results of tests on production powder shall be essentially equivalent to those on the approved sample powder.

4.4.2 Vendor shall use ingredients, manufacturing procedures, processes, and methods of inspection on production powder which are essentially the same as those used on the approved sample powder. If necessary to make any change in ingredients, in type of equipment for processing, or in manufacturing procedures, vendor shall submit for reapproval a statement of the proposed changes in material, processing, or both and, when requested, sample powder. Production powder made by the revised procedure shall not be shipped prior to receipt of reapproval.

4.5 Reports:

- 4.5.1 The vendor of powder shall furnish with each shipment a report showing the results of tests to determine conformance to the acceptance test requirements and stating that the powder conforms to the other technical requirements of this specification. This report shall include the purchase order number, AMS 5793, vendor's powder designation, lot number, and quantity.
- 4.5.2 The vendor of finished or semi-finished parts shall furnish with each shipment a report showing the purchase order number, AMS 5793, contractor or other direct supplier of powder, supplier's powder identification, part number, and quantity. When powder for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of powder to determine conformance to the requirements of this specification and shall include in the report either a statement that the powder conforms or copies of laboratory reports showing the results of tests to determine conformance.
- 4.6 Resampling and Retesting: If any specimen used in the above tests fails to meet the specified requirements, disposition of the powder may be based on the results of testing three additional specimens for each original nonconforming specimen. Failure of any retest specimen to meet the specified requirements shall be cause for rejection of the powder represented and no additional testing shall be permitted. Results of all tests shall be reported.

5. PREPARATION FOR DELIVERY:

5.1 Identification:

- 5.1.1 Each container shall be permanently and legibly marked with not less than the following information:

POWDER, PLASMA SPRAY

AMS 5793

MANUFACTURER'S IDENTIFICATION _____

MANUFACTURER'S MATERIAL DESIGNATION _____

LOT NUMBER _____

QUANTITY _____

- 5.1.2 Each exterior container shall be legibly marked with not less than the following information in such a manner that the markings will not smear or be obliterated during normal handling or use:

POWDER, PLASMA SPRAY

AMS 5793

MANUFACTURER'S IDENTIFICATION _____

MANUFACTURER'S MATERIAL DESIGNATION _____

PURCHASE ORDER NUMBER _____

LOT NUMBER _____

QUANTITY _____