



AEROSPACE MATERIAL SPECIFICATION

AMS5795™**REV. G**

Issued	1949-11
Revised	1993-04
Noncurrent	1999-03
Reaf. Nonc.	2012-04
Stabilized	2017-04

Superseding AMS5795F

Iron Alloy, Corrosion and Heat Resistant, Covered, Welding Electrodes
31Fe - 21Cr - 20Ni - 20Co - 3.0Mo - 2.5W - 1.0 (Cb + Ta)

W73155

RATIONALE

AMS5795G stabilizes this document because it contains mature technology that is not expected to change and thus no further revisions are anticipated.

STABILIZED NOTICE

AMS5795G has been declared "STABILIZED" by the SAE AMS F Corrosion Heat Resistant Alloys Committee. This document was stabilized because this document contains mature technology that is not expected to change and thus no further revisions are anticipated. Previously this document was non-current. The last technical update of this document occurred in April, 1993. Users of this document should refer to the cognizant engineering organization for disposition of any issues with reports/certifications to this specification; including exceptions listed on the certification.

NOTE: In many cases, the purchaser may represent a sub tier supplier and not the cognizant engineering organization.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2017 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
<http://www.sae.org>

SAE WEB ADDRESS:

**SAE values your input. To provide feedback on this
Technical Report, please visit**
<http://standards.sae.org/AMS5795G>

1. SCOPE:

1.1 Form:

This specification covers a corrosion and heat resistant iron alloy in the form of covered welding electrodes.

1.2 Application:

Primarily for shielded-metal-arc welding of parts fabricated from material of similar or dissimilar composition, particularly when the weld zone is required to have corrosion and heat resistance comparable to that of the parent metal.

1.3 Classification:

The electrodes covered by this specification are classified as follows:

Type A - DC	(AWS -15)
Type B - DC - AC	(AWS -16)
Type C - DC	(AWS -15)
Type D - DC - AC	(AWS -16)

1.3.1 When DC is specified, reverse polarity (electrode positive) is required.

1.3.2 If no type is specified, Type A shall be supplied.

1.3.3 Lime type coverings are required for Types A and C electrodes.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2350 Standards and Test Methods

2.2 ASTM Publications:

Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM E354 Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys

2.3 U.S. Government Publications:

Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Military Specifications:

MIL-W-10430 Welding Rods and Electrodes; Preparation for Delivery of

2.4 AWS Publications:

Available from American Welding Society, Inc., P.O. Box 351050, Miami, FL 33135.

AWS A5.4 Corrosion-Resisting Chromium and Chromium-Nickel Steel Covered Welding Electrodes

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Weld metal deposited from electrodes shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E354 or by spectrographic or other analytical methods approved by purchaser:

	min	max
Carbon	--	0.10
Manganese	1.00	2.50
Silicon	--	1.00
Phosphorus	--	0.04
Sulfur	--	0.03
Chromium	20.00	22.50
Nickel	19.00	21.00
Cobalt	18.50	21.00
Molybdenum	2.50	3.50
Tungsten	2.00	3.00
Columbium + Tantalum	0.75	1.25
Iron	remainder	

- 3.1.1 Weld Pads for Chemical Analysis: The referee procedure for making pads of weld metal and removing samples for chemical analysis shall be AWS A5.4.

3.2 Properties:

Electrodes shall conform to the following requirements:

- 3.2.1 Weldability: Electrodes shall flow smoothly and evenly under the conditions shown in 1.3 and shall produce acceptable welds, determined by a procedure agreed upon by purchaser and vendor.
- 3.2.2 Burn-Off: The covering shall be consumed uniformly all around and shall not burn back from the core wire under proper welding conditions. Heating of the electrodes during welding shall not cause injurious blistering of the covering within the ranges of current values recommended by the manufacturer.
- 3.2.3 Grip Portion and Arc Ends: A portion of the electrode 0.75 - 1.25 in. (20 - 30 mm) long on end-grip rods and 1.5 - 2.0 in. (40 - 50 mm) long on center-grip rods shall be bare to permit good electrical contact with the electrode holder. The arc end of the electrodes shall be sufficiently bare to permit easy striking of the arc but the length of this bare section, measured from the end of the electrode to the point where the full cross-section of the covering begins, shall not exceed the diameter of the bare wire and in no case shall it exceed 1/8 in. (3 mm).
- 3.2.4 Cleaning: Slag produced during welding shall be readily removable with hand tools.

3.3 Quality:

- 3.3.1 Core Wire: Shall be uniform in quality and condition, cylindrical, sound, and free from foreign materials and from imperfections detrimental to weld quality.
- 3.3.2 Covering: Shall be uniform in quality, tightly adherent, and free from abnormal scabs, blisters, pockmarks, bruises, and other surface defects and shall withstand normal handling without damage. It shall not be harmfully hygroscopic and shall not adversely affect weld quality.

3.4 Standard Sizes and Lengths:

The sizes and lengths in Table I are standard.

TABLE I

Nominal Diameter of Core Wire Inch	Length Inches
1/16, 5/64	9 and 8
3/32	9, 12, and 18
1/8, 5/32, 3/16, 1/4	14

TABLE I (SI)

Nominal Diameter of Core Wire Millimetres	Length Millimetres
1.5, 2.0	225 and 450
2.5	225, 300, and 450
3.0, 4.0, 5.0, 6.0	350

- 3.4.1 End-grip electrodes shall be supplied in all lengths except 18 in. (450 mm) where center-grip electrodes are required.

3.5 Tolerances:

Shall be as follows:

- 3.5.1 Electrodes shall not vary in length more than $\pm 1/4$ in. (± 6 mm) from the length ordered.
- 3.5.2 Electrode core wire shall not vary in diameter more than ± 0.002 in. (± 0.05 mm) from the size ordered.

- 3.5.3 Overall diameter of the covered electrodes shall not vary more than 4% from that of the approved sample.
- 3.5.4 Covering shall be concentric with the core wire to the extent that the maximum core-plus-one-covering dimension shall not exceed the minimum core-plus-one-covering dimension by more than 5% of the minimum core-plus-one-covering dimension.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of electrodes shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.5. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the electrodes conform to the requirements of this specification.

4.2 Classification of Tests:

- 4.2.1 Acceptance Tests: Tests to determine conformance to requirements for composition (3.1), grip portion and arc ends (3.2.3), sizes (3.4), and tolerances (3.5) are classified as acceptance tests and shall be performed to represent each control number of electrodes.
- 4.2.2 Periodic Tests: Tests to determine conformance to requirements for weldability (3.2.1), burn-off (3.2.2), and cleaning (3.2.4) are classified as periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.
- 4.2.3 Preproduction Tests: Tests to determine conformance to all technical requirements of this specification are classified as preproduction tests and shall be performed prior to or on the first-article shipment of electrodes to a purchaser, when a change in material, processing, or both requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.
 - 4.2.3.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, the contracting officer, or the request for procurement.

4.3 Sampling:

Shall be as agreed upon by purchaser and vendor; a control number shall be a designation indicating batch processing and core wire heat number.

4.4 Approval:

- 4.4.1 Sample electrodes shall be approved by purchaser before electrodes for production use are supplied, unless such approval be waived by purchaser.

4.4.2 Vendor shall use materials, manufacturing procedures, processes, and methods of inspection on production electrodes which are essentially the same as those used on the approved sample electrodes. If necessary to make any change in covering formulation or in manufacturing procedures, processes, or methods of inspection, vendor shall submit for reapproval a statement of the proposed changes in material, processing, or both and, when requested, sample electrodes. Production electrodes incorporating the revised procedures shall not be shipped prior to receipt of reapproval.

4.5 Reports:

4.5.1 The vendor of electrodes shall furnish with each shipment a report stating that the electrodes conform to the technical requirements of this specification. This report shall include the purchase order number, AMS 5795G, control number, size, and quantity. When requested by purchaser, the vendor shall also include in the report the composition of the deposited weld metal for each heat in the shipment.

4.5.2 When assemblies requiring use of these electrodes are supplied, the assembly manufacturer shall inspect each lot of electrodes to determine conformance to the technical requirements of this specification and shall furnish with each shipment a report stating that the electrodes conform. This report shall include the purchase order number, AMS 5795G, assembly number, and quantity.

4.6 Resampling and Retesting:

If any specimen used in the above tests fails to meet the specified requirements, disposition of the electrodes may be based on the results of testing three additional specimens for each original nonconforming specimen. Failure of any retest specimen to meet the specified requirements shall be cause for rejection of the electrodes represented and no additional testing shall be permitted. Results of all tests shall be reported.

5. PREPARATION FOR DELIVERY:

5.1 Identification:

5.1.1 Individual Electrodes:

5.1.1.1 At least one legible imprint of the AWS classification shall be applied to the electrode covering as near as practical to the grip end of the core wire and within 2-1/2 in. (65 mm) of the grip end. In the case of center-grip electrodes, the imprint shall be applied to the electrode covering as above and upon both sides of the center-grip (bare core wire) area. The prefix letter "E" in the electrode classification may be omitted from the imprint on the electrode covering.

5.1.1.2 The numbers of the imprinted electrode classification shall be of bold block type and of sufficient size and color contrast to be legible before and after normal welding applications.