

AEROSPACE MATERIAL SPECIFICATION

Submitted for recognition as an American National Standard

SAE AMS 5801B

Issued 5-15-71

Revised 1-1-86

Superseding AMS 5801A

ALLOY WELDING WIRE, CORROSION AND HEAT RESISTANT
39Co - 22Cr - 22Ni - 14.5W - 0.07La

UNS R30188

1. SCOPE:

1.1 Form: This specification covers a corrosion and heat resistant cobalt alloy in the form of welding wire.

1.2 Application: Primarily for use as filler metal for gas-tungsten-arc or gas-metal-arc welding of parts fabricated from alloys of similar composition.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2269 - Chemical Check Analysis Limits, Wrought Nickel Alloys and Cobalt Alloys

AMS 2350 - Standards and Test Methods

AMS 2371 - Quality Assurance Sampling of Corrosion and Heat Resistant Steels and Alloys, Wrought Products Except Forgings and Forging Stock

AMS 2813 - Packaging of Welding Wire, Standard Method

AMS 2815 - Identification, Welding Wire, Line Code System

AMS 2816 - Identification, Welding Wire, Color Code System

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM E354 - Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

3. TECHNICAL REQUIREMENTS:

- 3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E354 or by spectrographic or other analytical methods approved by purchaser:

Ø	min	max
Carbon	0.05 -	0.15
Manganese	--	1.25
Silicon	0.20 -	0.50
Phosphorus	--	0.020
Sulfur	--	0.015
Chromium	20.00 -	24.00
Nickel	20.00 -	24.00
Tungsten	13.00 -	16.00
Lanthanum	0.02 -	0.12
Boron	--	0.015
Iron	--	3.00
Cobalt	remainder	

- 3.1.1 Check Analysis: Composition variations shall meet the requirements of AMS 2269.

- 3.2 Condition: Cold finished, bright finish, in a temper which will provide proper feeding of the wire in machine welding equipment.

- 3.2.1 Wire shall be furnished on disposable spools for machine welding or in cut lengths for manual welding, as ordered.

- 3.2.2 In-process annealing between cold rolling or drawing operations shall be performed in a suitable protective atmosphere.

- 3.2.3 Drawing compounds, oxides, dirt, and oil shall be removed by cleaning processes which will neither result in pitting nor cause gas absorption by the wire or deposition of substances harmful to welding operations.

- 3.3 Properties: Wire shall conform to the following requirements:

- 3.3.1 Weldability: Melted wire shall flow smoothly and evenly during welding and shall produce acceptable welds, determined by a procedure agreed upon by purchaser and vendor.

- 3.3.2 Spooled Wire: Shall conform to 3.3.2.1 and 3.3.2.2.

- 3.3.2.1 Cast: Wire wound on standard 12-in. (300-mm) diameter spools shall have imparted to it a curvature such that a specimen sufficient in length, 4 - 8 ft (1.2 - 2.4 m), to form one loop, when cut from the spool and laid on flat surface, shall form a circle not less than 15 in. (375 mm) and not greater than 30 in. (750 mm) in diameter.

3.3.2.2 Helix: The specimen on which cast was determined, when laid on a flat surface and measured between adjacent turns, shall show a vertical separation not greater than 1 in. (25 mm).

3.4 Quality: Wire, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to welding operations, operation of welding equipment, or properties of the deposited weld metal.

3.5 Sizes and Tolerances: Wire shall be supplied in the sizes and to the tolerances shown in 3.5.1 and 3.5.2.

3.5.1 Diameter:

TABLE I

Form	Nominal Diameter Inch	Tolerance, Inch	
		Plus	Minus
Cut Lengths	0.030, 0.045, 0.062, 0.078	0.002	0.002
Cut Lengths	0.094, 0.125, 0.156, 0.188	0.003	0.003
Spools	0.007, 0.010, 0.015, 0.020	0.0005	0.0005
Spools	0.030, 0.035, 0.045	0.001	0.002
Spools	0.062, 0.078, 0.094	0.002	0.002

TABLE I (SI)

Form	Nominal Diameter Millimetres	Tolerance, Millimetre	
		Plus	Minus
Cut Lengths	0.75, 1.15, 1.55, 2.00	0.05	0.05
Cut Lengths	2.35, 3.10, 4.00, 4.75	0.08	0.08
Spools	0.20, 0.25, 0.40, 0.50	0.015	0.015
Spools	0.75, 0.90, 1.15	0.02	0.05
Spools	1.55, 2.00, 2.35	0.05	0.05

3.5.2 Length: Cut lengths shall be furnished in 18, 27, or 36 in. (450, 675, or 900 mm) lengths, as ordered, and shall not vary more than +0, -0.5 in. (-12 mm) from the length ordered.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of wire shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the wire conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests to determine conformance to requirements for composition (3.1) and sizes and tolerances (3.5) are classified as acceptance tests and shall be performed on each heat or lot as applicable.

4.2.2 Periodic Tests: Tests to determine conformance to requirements for weldability (3.3.1), cast (3.3.2.1), and helix (3.3.2.2) are classified as periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.3 Sampling: Shall be in accordance with AMS 2371 and as specified herein.

4.4 Reports:

4.4.1 The vendor of wire shall furnish with each shipment a report showing the results of tests for chemical composition of each heat and stating that the wire conforms to the other technical requirements of this specification. This report shall include the purchase order number, heat number, AMS 5801B, nominal size, and quantity from each heat.

4.4.2 When parts made of this wire or assemblies requiring use of this welding wire are supplied, the part or assembly manufacturer shall inspect each lot of wire to determine conformance to the requirements of this specification and shall furnish with each shipment a report stating that the wire conforms. This report shall include the purchase order number, AMS 5801B, part or assembly number, and quantity.

4.5 Resampling and Retesting: Shall be in accordance with AMS 2371.

5. PREPARATION FOR DELIVERY:

5.1 Layer Winding: Wire furnished on spools shall be closely wound in layers but adjacent turns within a layer need not necessarily be touching; shall be wound so as to avoid producing kinks, waves, and sharp bends; and shall be free to unwind without restriction caused by overlapping or wedging. The outside end of the spooled wire shall be so treated that it may be readily located. An 8-in. (200-mm) length of wire shall be accessible at both ends of each spool for alloy verification.

5.2 Heat: Wire on each spool shall be of one continuous length from the same heat of alloy. Butt welding is permissible providing both ends to be joined are verified and the weld will not interfere with uniform, uninterrupted feeding of the wire in machine welding equipment. Packages of cut lengths shall not contain wire from more than one heat of alloy.

5.3 Identification: Wire shall be identified in accordance with AMS 2816 unless identification in accordance with AMS 2815 is specified by purchaser. Tab marking of cut lengths is permissible.