

NOTICE OF
ADOPTION

ADOPTION NOTICE 1
23 April 1993 for
AMS 5802A
1 January 1993

AMS 5802A was adopted on 23 April 1993 and is approved for use by the Department of Defense (DoD). The Society of Automotive Engineers prepared the document. SAE has furnished clearances required by existing regulations. Copies of the document should be ordered from Standardization Documents Order Desk, Bldg 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094 for issue to DoD activities only. All others desiring copies must obtain them from:

SAE
400 Commonwealth Drive
Warrendale, PA 15096

Title of Document: Iron-Nickel Alloy, Corrosion and Heat Resistant, Welding
Wire
41Fe - 37.5Ni - 14Co - 4.8(Cb + Ta) - 1.5Ti
Vacuum Melted, Low Expansion

Date of Specific Issue Adopted: 1 January 1993

Releasing Non-Government Standards Body: SAE

Custodians:
Army - MR
Navy - AS
Air Force - 11

Military Coordinating Activity:
Army - MR
Project 3439-0834

DISTRIBUTION STATEMENT A Approved for public release; distribution unlimited.

FSC 3439

SAE The Engineering Society
For Advancing Mobility
Land Sea Air and Space®
INTERNATIONAL

400 Commonwealth Drive, Warrendale, PA 15096-0001

AEROSPACE MATERIAL SPECIFICATION

SAE

AMS 5802A

Issued 1 OCT 1987

Revised 1 JAN 1993

Superseding AMS 5802

Submitted for recognition as an American National Standard

IRON-NICKEL ALLOY, CORROSION AND HEAT RESISTANT, WELDING WIRE
41Fe - 37.5Ni - 14Co - 4.8(Cb + Ta) - 1.5Ti
Vacuum Melted, Low Expansion

UNS N19907

1. SCOPE:

1.1 Form:

This specification covers a corrosion and heat resistant iron-nickel alloy in the form of welding wire.

1.2 Application:

This wire has been used typically as filler metal for gas-tungsten-arc or gas-metal-arc welding of alloys of similar composition requiring joints with strength and corrosion resistance comparable to those of the basis metal, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. the applicable issue of other publications shall be the issue in effect on the date of the purchase order.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15094-0001.

AMS 2248 Chemical Check Analysis Limits, Wrought Corrosion and Heat Resistant Steels and Alloys, Maraging and Other Highly-Alloyed Steels, and Iron Alloys

AMS 2371 Quality Assurance Sampling and Testing, Corrosion and Heat Resistant Steels and Alloys, Wrought Products and Forging Stock

AMS 2813 Packaging and Marking of Packages of Welding Wire, Standard Method

AMS 2814 Packaging and Marking of Packages of Welding Wire, Premium Quality

AMS 2816 Identification, Welding Wire, Color Code System

ARP1876 Weldability Test for Weld Filler Metal Wire

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

AMS 5802A

SAE

AMS 5802A

2.2 ASTM Publications:

Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

ASTM E 354 Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys

3. TECHNICAL REQUIREMENTS:**3.1 Composition:****(R)**

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 354, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

Element	min	max
Carbon	--	0.06
Manganese	--	1.00
Silicon	0.25	0.50
Sulfur	--	0.010
Phosphorus	--	0.015
Nickel	35.00	40.00
Cobalt	12.00	16.00
Columbium + Tantalum	4.30	5.20
Titanium	1.30	1.80
Chromium	--	1.00
Aluminum	--	0.20
Boron	--	0.012
Copper	--	0.50
Iron	remainder	

3.1.1 Check Analysis: Composition variations shall meet the requirements of AMS 2248.

3.2 Melting Practice:

Alloy shall be multiple melted using consumable electrode practice in the remelt cycle or shall be vacuum induction melted. If consumable electrode remelting is not performed in vacuum, electrodes which have been produced by vacuum induction melting shall be used for remelting.

AMS 5802A

SAE

AMS 5802A

3.3 Condition:

(R)

Cold worked, bright finished, in a temper and with a surface finish which will provide proper feeding of the wire in machine welding equipment.

3.3.1 Wire shall be furnished on disposable spools for machine welding or in cut lengths for manual welding, as ordered.

3.3.2 Drawing compounds, oxides, dirt, oil, and other foreign materials shall be removed by cleaning processes which will neither result in pitting nor cause gas absorption by the wire or deposition of substances harmful to welding operations.

3.3.2.1 If pickling is necessary to remove surface contamination or scaling, only a light pickle shall be used followed by vacuum degassing.

3.4 Properties:

Wire shall conform to the following requirements:

3.4.1 Weldability: Melted wire shall flow smoothly and evenly during welding and shall produce acceptable welds. ARP1876 may be used to resolve disputes.

3.4.2 Spooled Wire: Shall conform to 3.4.2.1 and 3.4.2.2.

3.4.2.1 Cast: Wire, wound on standard 12-inch (305-mm) diameter spools, shall have imparted to it a curvature such that a specimen sufficient in length to form one loop with a 1-inch (25-mm) overlap, when cut from the spool and laid on a flat surface, shall form a circle 15 to 50 inches (381 to 1270 mm) in diameter.

3.4.2.2 Helix: The specimen on which cast was determined, when laid on a flat surface and measured between adjacent turns, shall show a vertical separation not greater than 1 inch (25 mm).

3.5 Quality:

Wire, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to welding operations, operation of welding equipment, or properties of the deposited weld metal.

3.6 Sizes and Tolerances:

Wire shall be supplied in the standard sizes and to the tolerances shown in 3.6.1 and 3.6.2.

AMS 5802A

SAE

AMS 5802A

3.6.1 Diameter:

TABLE 2A - Sizes and Tolerances, Inch/Pound Units

Form	Nominal Diameter Inch	Tolerance Inch plus	Tolerance Inch minus
Cut lengths	0.030, 0.045, 0.062, 0.078	0.002	0.002
Cut lengths	0.094, 0.125, 0.156, 0.188	0.003	0.003
Spools	0.007, 0.010, 0.015, 0.020	0.0005	0.0005
Spools	0.030, 0.035, 0.045	0.001	0.002
Spools	0.062, 0.078, 0.094	0.002	0.002

TABLE 2B - Sizes and Tolerances, SI Units

Form	Nominal Diameter Millimeters	Tolerance Millimeter plus	Tolerance Millimeter minus
Cut Lengths	0.76, 0.14, 1.57, 1.98	0.05	0.05
Cut Lengths	2.39, 3.18, 3.96, 4.78	0.08	0.08
Spools	0.18, 0.25, 0.38, 0.51	0.014	0.014
Spools	0.76, 0.89, 1.14	0.025	0.05
Spools	1.57, 1.98, 2.39	0.05	0.05

3.6.2 Length: Cut lengths shall be furnished in 18, 27, or 36 inch (457, 686, or 914 mm) lengths, as ordered, and shall not vary more than +0, -0.5 inch (-13 mm) from the length ordered.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

(R)

The vendor of wire shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the wire conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests for composition (3.1), sizes and tolerances (3.6), and alloy verification (5.2.1) are acceptance tests and shall be performed on each heat or lot as applicable.