

Submitted for recognition as an American National Standard

STEEL WELDING WIRE, CORROSION AND MODERATE HEAT RESISTANT
16.2Cr - 4.8Ni - 0.22(Cb + Ta) - 3.5Cu
Vacuum Melted

1. SCOPE:

- 1.1 Form: This specification covers a corrosion and moderate heat resistant steel in the form of welding wire.
- 1.2 Application: Primarily for use as filler metal for gas-tungsten-arc or gas-metal-arc welding of steels of similar composition requiring joints with strength and corrosion resistance comparable to those of the basis metal.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

- 2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

- AMS 2248 - Chemical Check Analysis Limits, Wrought Corrosion and Heat Resistant Steels and Alloys, Maraging and Other Highly-Alloyed Steels, and Iron Alloys
- AMS 2350 - Standards and Test Methods
- AMS 2371 - Quality Assurance Sampling of Corrosion and Heat Resistant Steels and Alloys, Wrought Products Except Forgings and Forging Stock
- AMS 2813 - Packaging of Welding Wire, Standard Method
- AMS 2815 - Identification, Welding Wire, Line Code System
- AMS 2816 - Identification, Welding Wire, Color Code System
- AMS 5643 - Steel Bars, Forgings, Tubing, and Rings, Corrosion Resistant, 16Cr - 4.0Ni - 0.30(Cb + Ta) - 4.0Cu, Solution Heat Treated

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM E18 - Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials

ASTM E353 - Chemical Analysis of Stainless, Heat-Resisting, Maraging and Other Similar Chromium-Nickel-Iron Alloys

3. TECHNICAL REQUIREMENTS:

3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E353 or by spectrochemical or other analytical methods approved by purchaser:

	min	max
Carbon	--	0.05
Manganese	0.50 -	0.75
Silicon	--	0.50
Phosphorus	--	0.015
Sulfur	--	0.008
Chromium	15.75 -	16.75
Nickel	4.50 -	5.00
Columbium + Tantalum	0.15 -	0.30
Copper	3.25 -	3.75
Aluminum	--	0.05
Tin	--	0.0005 (5 ppm)
Lead	--	0.001 (100 ppm)
Boron	--	0.001 (100 ppm)
Nitrogen	--	0.0150 (150 ppm)
Oxygen	--	0.0050 (50 ppm)
Hydrogen (3.1.1)	--	0.0005 (5 ppm)

3.1.1 Shall be determined on finished wire.

3.1.2 Check Analysis: Composition variations shall meet the requirements of AMS 2248.

3.2 Condition: Bright finished in a temper which will provide proper feeding of the wire in machine welding equipment.

3.2.1 Wire shall be furnished on disposable spools for machine welding or in cut lengths for manual welding, as ordered.

3.2.2 Drawing compounds, oxides, dirt, and oil shall be removed by cleaning processes which will neither result in pitting nor cause gas absorption by the wire or deposition of substances harmful to welding operations.

3.2.2.1 If pickling is necessary to remove surface contamination or scaling, only a light pickle shall be used followed by vacuum degassing.

3.3 Properties: Wire shall conform to the following requirements:

- 3.3.1 Weldability: Melted wire shall flow smoothly and evenly during welding and shall produce acceptable welds, determined by a procedure agreed upon by purchaser and vendor.
- 3.3.2 Response to Heat Treatment: When specified, weld metal deposits approximately 1/4 in. (6 mm) in thickness, deposited on AMS 5643 steel, shall attain hardness not lower than 38 HRC, or equivalent, determined in accordance with ASTM E18, after being solution heat treated by heating to 1900°F + 25 (1040°C + 15), holding at heat for not less than 30 min., and cooling to below 60°F (15°C) and precipitation heat treated by heating to 900°F + 10 (480°C + 5), holding at heat for 60 min. + 5, and cooling in air.
- 3.3.3 Spooled Wire: Shall conform to 3.3.3.1 and 3.3.3.2.
- 3.3.3.1 Cast: Wire wound on standard 12-in. (300-mm) diameter spools shall have imparted to it a curvature such that a specimen sufficient in length, 4 to 8 ft (1200 - 2400 mm), to form one loop, when cut from the spool and laid on a flat surface, shall form a circle 15 - 30 in. (375 - 750 mm) in diameter.
- 3.3.3.2 Helix: The specimen on which cast was determined, when laid on a flat surface and measured between adjacent turns, shall show a vertical separation not greater than 1 in. (25 mm).
- 3.4 Quality:
- 3.4.1 Steel shall be multiple melted using consumable electrode practice in the remelt cycle or shall be vacuum induction melted.
- 3.4.2 Wire, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to welding operations, operation of welding equipment, or properties of the deposited weld metal.
- 3.5 Sizes and Tolerances: Wire shall be supplied in the sizes and to the tolerances shown in 3.5.1 and 3.5.2.
- 3.5.1 Diameter:

TABLE I

Form	Nominal Diameter, Inch	Tolerance, Inch	
		plus	minus
Cut Lengths	0.030, 0.045, 0.062, 0.078	0.002	0.002
Cut Lengths	0.094, 0.125, 0.156, 0.188	0.003	0.003
Spools	0.007, 0.010, 0.015, 0.020	0.0005	0.0005
Spools	0.030, 0.035, 0.045	0.001	0.002
Spools	0.062, 0.078, 0.094	0.002	0.002

TABLE I (SI)

Form	Nominal Diameter Millimetres	Tolerance, Millimetre	
		plus	minus
Cut Lengths	0.75, 1.15, 1.55, 2.00	0.05	0.05
Cut Lengths	2.35, 3.10, 4.00, 4.75	0.08	0.08
Spools	0.20, 0.25, 0.40, 0.50	0.015	0.015
Spools	0.75, 0.90, 1.15	0.02	0.05
Spools	1.55, 2.00, 2.35	0.05	0.05

3.5.2 Length: Cut lengths shall be furnished in 18, 27, or 36 in. (450, 675, or 900 mm) lengths, as ordered, and shall not vary more than +0, -0.5 in. (-12 mm) from the length ordered.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of wire shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the wire conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests to determine conformance to requirements for composition (3.1), response to heat treatment when specified (3.3.2), and sizes and tolerances (3.5) are classified as acceptance tests and shall be performed on each heat or lot as applicable.

4.2.2 Periodic Tests: Tests to determine conformance to requirements for weldability (3.3.1), cast (3.3.2.1), and helix (3.3.2.2) are classified as periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.3 Sampling: Shall be in accordance with AMS 2371 and as specified herein.

4.4 Reports:

4.4.1 The vendor of wire shall furnish with each shipment a report showing the results of tests for chemical composition of each heat and stating that the wire conforms to the other technical requirements of this specification. This report shall include the purchase order number, heat number, AMS 5803, nominal size, and quantity.

4.4.2 When parts made of this wire or assemblies requiring use of this welding wire are supplied, the part or assembly manufacturer shall inspect each lot of wire to determine conformance to the technical requirements of this specification and shall furnish with each shipment a report stating that the wire conforms. This report shall include the purchase order number, AMS 5803, part or assembly number, and quantity.