

**AEROSPACE  
MATERIAL  
SPECIFICATION**

**AMS 5829A**  
Superseding AMS 5829

Issued 12-1-73  
Revised 7-1-82

UNS N07090

ALLOY WIRE, WELDING, CORROSION AND HEAT RESISTANT  
56Ni - 19.5Cr - 18Co - 2.5Ti - 1.5Al  
Vacuum Induction Melted

1. SCOPE:

1.1 Form: This specification covers a corrosion and heat resistant nickel alloy in the form of welding wire.

1.2 Application: Primarily as filler metal for gas-tungsten-arc or gas-metal-arc welding nickel alloys of similar composition requiring joints with strength and corrosion resistance comparable to those of the basis metal.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2269 - Chemical Check Analysis Limits, Wrought Nickel Alloys and Cobalt Alloys

AMS 2350 - Standards and Test Methods

AMS 2371 - Quality Assurance Sampling of Corrosion and Heat Resistant Steels and Alloys, Wrought Products Except Forgings and Forging Stock

AMS 2813 - Packaging of Welding Wire, Standard Method

AMS 2815 - Identification, Welding Wire, Line Code System

AMS 2816 - Identification, Welding Wire, Color Code System

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade or their use by governmental agencies is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

- 2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM E354 - Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys

- 2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Federal Standards:

Federal Test Method Standard No. 151 - Metals, Test Methods

3. TECHNICAL REQUIREMENTS:

- 3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E354, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other analytical methods approved by purchaser:

|           | min       | max            |
|-----------|-----------|----------------|
| Carbon    | --        | 0.13           |
| Manganese | --        | 1.00           |
| Silicon   | --        | 1.00           |
| Sulfur    | --        | 0.015          |
| Chromium  | 18.00 -   | 21.00          |
| Cobalt    | 15.00 -   | 21.00          |
| Titanium  | 2.00 -    | 3.00           |
| Aluminum  | 1.00 -    | 2.00           |
| Iron      | --        | 1.50           |
| Copper    | --        | 0.20           |
| Zirconium | --        | 0.15           |
| Boron     | --        | 0.02           |
| Lead      | --        | 0.002 (20 ppm) |
| Silver    | --        | 0.0005 (5 ppm) |
| Bismuth   | --        | 0.0001 (1 ppm) |
| Nickel    | remainder |                |

- 3.1.1 Check Analysis: Composition variations shall meet the requirements of AMS 2269.

- 3.2 Condition: Cold finished, bright finish, in a temper which will provide proper feeding of the wire in machine welding equipment.

- 3.2.1 Wire shall be furnished on disposable spools for machine welding or in cut lengths for manual welding, as ordered.

- 3.2.2 In-process annealing between cold rolling or drawing operations shall be performed in a suitable protective atmosphere.

3.2.3 Oxides, dirt, and drawing compounds shall be removed by processes which will neither result in pitting nor cause gas absorption by the wire or deposition of substances harmful to welding operations.

3.3 Properties: Wire shall conform to the following requirements:

3.3.1 Weldability: Melted wire shall flow smoothly and evenly during welding and shall produce acceptable welds, determined by a procedure agreed upon by purchaser and vendor.

3.3.2 Spooled Wire: Shall conform to 3.3.2.1 and 3.3.2.2, unless otherwise agreed upon by purchaser and vendor.

3.3.2.1 Cast: Wire wound on standard 12-in. (300-mm) diameter spools shall have imparted to it a curvature such that a specimen sufficient in length  
 Ø (4 - 8 ft (1.2 - 2.4 m)) to form one loop, when cut from the spool and laid on a flat surface, shall form a circle not less than 15 in. (375 mm) and not greater than 30 in. (750 mm) in diameter.

3.3.2.2 Helix: The specimen on which cast was determined, when laid on a flat surface and measured between adjacent turns, shall show a vertical separation not greater than 1 in. (25 mm).

3.4 Quality:

3.4.1 Alloy shall be produced by vacuum induction melting; it may be remelted  
 Ø using consumable electrode vacuum process but remelting is not required.

3.4.2 Wire, as received by purchaser, shall be uniform in quality and condition,  
 Ø sound, and free from foreign materials and from internal and external imperfections detrimental to welding operations, operation of welding equipment, or properties of the deposited weld metal.

3.5 Sizes and Tolerances: Unless otherwise specified, wire shall be supplied in the sizes and to the tolerances shown in 3.5.1 and 3.5.2:

3.5.1 Diameter:

TABLE I

| Form        | Nominal Diameter<br>Inch   | Tolerance, Inch |        |
|-------------|----------------------------|-----------------|--------|
|             |                            | plus            | minus  |
| Cut Lengths | 0.030, 0.045, 0.062, 0.078 | 0.002           | 0.002  |
| Cut Lengths | 0.094, 0.125, 0.156, 0.188 | 0.003           | 0.003  |
| Spools      | 0.007, 0.010, 0.015, 0.020 | 0.0005          | 0.0005 |
| Spools      | 0.030, 0.035, 0.045        | 0.001           | 0.002  |
| Spools      | 0.062, 0.078, 0.094        | 0.002           | 0.002  |

TABLE I (SI)

| Form        | Nominal Diameter<br>Millimetres | Tolerance, Millimetre |       |
|-------------|---------------------------------|-----------------------|-------|
|             |                                 | plus                  | minus |
| Cut Lengths | 0.75, 1.15, 1.55, 2.00          | 0.05                  | 0.05  |
| Cut Lengths | 2.35, 3.10, 4.00, 4.75          | 0.08                  | 0.08  |
| Spools      | 0.20, 0.25, 0.40, 0.50          | 0.015                 | 0.015 |
| Spools      | 0.75, 0.90, 1.15                | 0.02                  | 0.05  |
| Spools      | 1.55, 2.00, 2.35                | 0.05                  | 0.05  |

- 3.5.2 Length: Cut lengths shall be furnished in 18, 27, or 36 in. (450, 675, or 900 mm) lengths, as ordered, and shall not vary more than +0, -0.5 in. (-13 mm) from the length ordered.

#### 4. QUALITY ASSURANCE PROVISIONS:

- 4.1 Responsibility for Inspection: The vendor of wire shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the wire conforms to the requirements of this specification.

#### 4.2 Classification of Tests:

- 4.2.1 Acceptance Tests: Tests to determine conformance to requirements for composition (3.1) and tolerances (3.5) are classified as acceptance tests and shall be performed on each heat or lot as applicable.
- 4.2.2 Periodic Tests: Tests to determine conformance to requirements for weldability (3.3.1), cast (3.3.2.1), and helix (3.3.2.2) are classified as periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

- 4.3 Sampling: Shall be in accordance with AMS 2371 and as specified herein.

#### 4.4 Reports:

- 4.4.1 The vendor of wire shall furnish with each shipment three copies of a report showing the results of tests for chemical composition of each heat and stating that the wire conforms to the other technical requirements of this specification. This report shall include the purchase order number, heat number, AMS 5829A, nominal size, and quantity from each heat.
- 4.4.2 When parts made of this wire or assemblies requiring use of this welding wire are supplied, the part or assembly manufacturer shall inspect each lot of wire to determine conformance to the technical requirements of this specification and shall furnish with each shipment three copies of a report stating that the wire conforms. This report shall include the purchase order number, AMS 5829A, part or assembly number, and quantity.