

**AEROSPACE  
MATERIAL  
SPECIFICATION**

**AMS 5852A**

Superseding AMS 5852

Issued 9-15-77  
Revised 7-1-83

**ALLOY BILLETS AND PREFORMS, CORROSION AND HEAT RESISTANT  
55Ni - 15Cr - 17Co - 5.0Mo - 3.5Ti - 4.0Al - 0.025B  
Powder Metallurgy Product, Hot Isostatically Pressed**

**1. SCOPE:**

- 1.1 Form: This specification covers a corrosion and heat resistant nickel alloy powder-metallurgy product in the form of billets and preforms.
- 1.2 Application: Primarily for highly-stressed parts, such as rotating parts of gas turbine engines, requiring high strength and corrosion and oxidation resistance up to 1400°F (760°C).

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) and Aerospace Recommended Practices (ARP) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

- 2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2261 - Tolerances, Nickel, Nickel Alloy, and Cobalt Alloy Bars and Forging Stock  
AMS 2269 - Chemical Check Analysis Limits, Wrought Nickel Alloys and Cobalt Alloys  
AMS 2350 - Standards and Test Methods  
AMS 2374 - Quality Assurance Sampling of Corrosion and Heat Resistant Steels and Alloys, Forgings and Forging Stock  
AMS 2630 - Ultrasonic Inspection, Product Over 0.5 In. (12.5 mm) Thick  
AMS 5851 - Alloy Powder, Corrosion and Heat Resistant, 55Ni - 15Cr - 17Co - 5.0Mo - 3.5Ti - 4.0Al - 0.025B

2.1.2 Aerospace Recommended Practices:

ARP 1313 - Determination of Trace Elements in High Temperature Alloys

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade or their use by governmental agencies is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

- 2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM E8 - Tension Testing of Metallic Materials  
ASTM E10 - Brinell Hardness of Metallic Materials  
ASTM E21 - Elevated Temperature Tension Tests of Metallic Materials  
ASTM E112 - Estimating the Average Grain Size of Metals  
ASTM E139 - Conducting Creep, Creep-Rupture, and Stress-Rupture Tests of Metallic Materials  
ASTM E292 - Conducting Time-For-Rupture Notch Tension Tests of Materials  
ASTM E354 - Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys

- 2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Federal Standards:

Federal Test Method Standard No. 151 - Metals, Test Methods

2.3.2 Military Standards:

MIL-STD-163 - Steel Mill Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

- 3.1 Material: Billets and preforms shall be produced by compaction of AMS 5851 powder by hot isostatic pressing to produce products meeting the requirements of 3.5 and 3.6.

- 3.2 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E354, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other analytical methods approved by purchaser except that lead and bismuth shall be determined in accordance with ARP 1313 and oxygen and nitrogen shall be determined by Leco Gas Analyzer or equivalent:

|            | min       | max               |
|------------|-----------|-------------------|
| Carbon     | 0.02      | - 0.06            |
| Manganese  | --        | 0.15              |
| Silicon    | --        | 0.20              |
| Phosphorus | --        | 0.015             |
| Sulfur     | --        | 0.015             |
| Chromium   | 14.00     | - 16.00           |
| Cobalt     | 16.00     | - 18.00           |
| Molybdenum | 4.50      | - 5.50            |
| Titanium   | 3.35      | - 3.65            |
| Aluminum   | 3.85      | - 4.15            |
| Boron      | 0.020     | - 0.030           |
| Tungsten   | --        | 0.05              |
| Iron       | --        | 0.50              |
| Copper     | --        | 0.10              |
| Zirconium  | --        | 0.06              |
| Lead       | --        | 0.0002 (2 ppm)    |
| Bismuth    | --        | 0.00005 (0.5 ppm) |
| Oxygen     | --        | 0.010 (100 ppm)   |
| Nitrogen   | --        | 0.0050 (50 ppm)   |
| Nickel     | remainder |                   |

- 3.2.1 Check Analysis: Composition variations shall meet the requirements of AMS 2269; no variation over maximum will be permitted for lead, bismuth, oxygen, and nitrogen.

- 3.3 Condition: As hot isostatically pressed (HIP).

- 3.4 Heat Treatment: When specified, the product shall be heat treated as follows:

- 3.4.1 Solution Heat Treatment: Heat to a temperature within the range 1975° - 2075°F (1080° - 1135°C), hold at the selected temperature within +15°F (+8°C) for 4 hr  $\pm$  0.25, and cool at a rate equivalent to air cool or faster.
- 3.4.2 Stabilization Heat Treatment: Heat to 1600°F  $\pm$  15 (870°C  $\pm$  8), hold at heat for 8 hr  $\pm$  0.5, and cool to room temperature at a rate equivalent to an air cool; reheat to 1800°F  $\pm$  15 (980°C  $\pm$  8), hold at heat for 4 hr  $\pm$  0.25, and cool at a rate equivalent to an air cool.

3.4.3 Precipitation Heat Treatment: Heat to  $1200^{\circ}\text{F} \pm 15$  ( $650^{\circ}\text{C} \pm 8$ ), hold at heat for  $24 \text{ hr} \pm 0.5$ , and air cool to room temperature; reheat to  $1400^{\circ}\text{F} \pm 15$  ( $760^{\circ}\text{C} \pm 8$ ), hold at heat for  $8 \text{ hr} \pm 0.25$ , and cool in air.

3.5 Properties: The product shall conform to the following requirements:

3.5.1 As Hot Isostatically Pressed:

3.5.1.1 Microstructure: Shall show complete bonding between powder particles and shall meet standards agreed upon by purchaser and vendor for incipient melting, hollow powder particles, and nonmetallic inclusions, determined by microscopic examination of polished specimens etched in Kalling's reagent and examined at 100X magnification for bonding and at 400X magnification for incipient melting, hollow powder particles, and nonmetallic inclusions.

3.5.1.2 Thermally-Induced Porosity (TIP): Shall be no greater than permitted by standards agreed upon by purchaser and vendor, determined as follows:

3.5.1.2.1 A sample having one surface approximately 5 sq in. ( $30 \text{ cm}^2$ ) in area shall be heated in air to a temperature within the range  $2200^{\circ} - 2225^{\circ}\text{F}$  ( $1205^{\circ} - 1220^{\circ}\text{C}$ ), held at the selected temperature within  $\pm 15^{\circ}\text{F}$  ( $\pm 8^{\circ}\text{C}$ ) for  $4 \text{ hr} \pm 0.25$ , and cooled to room temperature. Specimens approximately 0.5 sq in. ( $3 \text{ cm}^2$ ) in surface area shall be cut from the sample, polished, etched, and examined as in 3.5.1.1.

3.5.2 After Heat Treatment: When a billet or preform is forged to a test coupon and heat treated as in 3.4, specimens taken from the heat treated coupon shall conform to the requirements of 3.5.2.1 through 3.5.2.5. If specimens taken from the billets or preforms after heat treatment as in 3.4 conform to the requirements of 3.5.2.1 through 3.5.2.5, the tests shall be accepted as equivalent to tests of a forged coupon.

3.5.2.1 Grain Size: Predominantly 4 or finer with occasional grains as large as 1 permissible, determined by comparison of a polished and etched specimen with the chart in ASTM E112.

3.5.2.2 Tensile Properties: Shall be as follows for product 4.0 in. (100 mm) and under in nominal cross-section, determined in either the longitudinal or transverse direction except that testing in the transverse direction applies only to product from which a tensile specimen not less than 2.50 in. (62.5 mm) in length can be obtained; testing in the longitudinal direction is not required on product tested in the transverse direction. Tensile property requirements for product over 4.0 in. (100 mm) in nominal cross-section shall be as agreed upon by purchaser and vendor.

- 3.5.2.2.1 At Room Temperature: Shall be as follows, determined in accordance with ASTM E8:

|                                    |                        |
|------------------------------------|------------------------|
| Tensile Strength, min              | 195,000 psi (1345 MPa) |
| Yield Strength at 0.2% Offset, min | 140,000 psi ( 965 MPa) |
| Elongation in 4D, min              | 16%                    |
| Reduction of Area, min             | 18%                    |

- 3.5.2.2.2 At 1400°F (760°C): Shall be as follows, determined in accordance with ASTM E21 on specimens heated to 1400°F  $\pm$  10 (760°C  $\pm$  6), held at heat for 20 to 30 min. before testing, and tested at 1400°F  $\pm$  10 (760°C  $\pm$  6):

|                                    |                        |
|------------------------------------|------------------------|
| Tensile Strength, min              | 150,000 psi (1035 MPa) |
| Yield Strength at 0.2% Offset, min | 125,000 psi ( 860 MPa) |
| Elongation in 4D, min              | 20%                    |
| Reduction of Area, min             | 30%                    |

- 3.5.2.3 Hardness: Should be 311 - 401 HB or equivalent, determined in accordance with ASTM E10, but the product shall not be rejected on the basis of hardness if the tensile property requirements of 3.5.2.2.1 are met.

- 3.5.2.4 Stress-Rupture Properties at 1400°F (760°C): Shall be as follows; testing of notched specimens and of combination smooth-and-notched specimens shall be performed in accordance with ASTM E292 and of smooth specimens in accordance with ASTM E139:

- 3.5.2.4.1 A combination smooth-and-notched specimen machined to the dimensions shown in Fig. 1 and Table I, maintained at 1400°F  $\pm$  3 (760°C  $\pm$  2) while a load sufficient to produce an initial axial stress of 85,000 psi (585 MPa) is applied continuously, shall not rupture in less than 15 hours. The test shall be continued to rupture without change of load. Rupture shall occur in the smooth section and elongation of this section after rupture, measured at room temperature, shall be not less than 12% in 4D.

- 3.5.2.4.2 As an alternate procedure, separate smooth and notched specimens, machined from adjacent sections of the same piece with gage sections conforming to the respective dimensions of Table I, may be tested individually under the conditions of 3.5.2.4.1. The smooth specimen shall not rupture in less than 15 hr and elongation after rupture, measured at room temperature, shall be not less than 12% in 4D. The notched specimen shall not rupture in less time than the companion smooth specimen but need not be tested to rupture.

- 3.5.2.4.3 The tests of 3.5.2.4.1 and 3.5.2.4.2 may be conducted using a load higher than required to produce an initial axial stress of 85,000 psi (585 MPa) but load shall not be changed while test is in progress. Time to rupture, rupture location, and elongation requirements shall be as specified in 3.5.2.4.1.

4.2.2.2 Tensile properties at 1100°F (593°C) (3.4.2.1.2), hardness (3.4.2.2), and stress-rupture properties (3.4.2.3) after aging.

4.3 Sampling: Shall be in accordance with AMS 2371 and the following; a heat shall be the consumable electrode remelted ingots produced from alloy originally melted as a single furnace charge:

4.3.1 Specimens for tensile and smooth-bar stress-rupture testing shall be of standard proportions in accordance with ASTM E8 with either 0.250 in. (6.25 mm) diameter at the reduced parallel gage section or smaller specimens proportional to the standard when required. Other stress-rupture specimens shall be as specified in 3.4.2.3. All specimens shall be machined from the center of bars 0.800 in. (20.00 mm) and under in nominal diameter or distance between parallel sides and from mid-radius of larger size bars.

4.4 Reports:

4.4.1 The vendor of bars shall furnish with each shipment three copies of a report showing the results of tests for chemical composition of each heat and of tests on each lot to determine conformance to the other acceptance test requirements, and, when performed, to the periodic test requirements. This report shall include the purchase order number, heat number, AMS 5842A, size, and quantity from each heat, and a statement of record of specific temperature and time used in determining conformance to 3.4.2.

4.4.2 The vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, AMS 5842A, contractor or other direct supplier of bars, part number, and quantity. When bars for making parts are produced or purchased by the parts vendor, that vendor shall inspect each lot of bars to determine conformance to the requirements of this specification and shall include in the report either a statement that the bars conform or copies of laboratory reports showing the results of tests to determine conformance.

4.5 Resampling and Retesting: Shall be in accordance with AMS 2371.

5. PREPARATION FOR DELIVERY:

5.1 Identification: Shall be in accordance with AMS 2806.

5.2 Packaging:

5.2.1 Bars shall be prepared for shipment in accordance with commercial practice and in compliance with applicable rules and regulations pertaining to the handling, packaging, and transportation of the bars to ensure carrier acceptance and safe delivery. Packaging shall conform to carrier rules and regulations applicable to the mode of transportation.

5.2.2 For direct U.S. Military procurement, packaging shall be in accordance with MIL-STD-163, Level A or Level C, as specified in the request for procurement. Commercial packaging as in 5.2.1 will be acceptable if it meets the requirements of Level C.

6. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.

7. REJECTIONS: Bars not conforming to this specification or to modifications authorized by purchaser will be subject to rejection.

8. NOTES:

8.1 Marginal Indicia: The phi ( $\phi$ ) symbol is used to indicate technical changes from the previous issue of this specification.

8.2 This alloy depends on combinations of cold working and aging to attain a variety of combinations of strength and ductility. Mill capabilities currently are limited to cold drawing bars of 1-3/4 in. (45 mm) and under in nominal diameter to attain the properties specified in 3.4.2.1.

8.3 For direct U.S. Military procurement, purchase documents should specify not less than the following:

Title, number, and date of this specification  
Size of bars desired  
Quantity of bars desired  
Applicable level of packaging (See 5.2.2)

8.4 Bars meeting the requirements of this specification have been classified under Federal Supply Classification (FSC) 9530.

This specification is under the jurisdiction of AMS Committee "F".



- 4.4.2.1 Control factors for producing the product include, but are not limited to, the following:

- Source of metallurgical powder
- Type of compaction equipment
- Processing sequence or number of operations, including thermal operations that would result in different cross-sectional structure
- Protective atmosphere
- Cleaning operations (e.g., chemical descaling or mechanical cleaning)
- Inspection and testing

- 4.4.2.1.1 Any of the above process control factors for which parameters are considered proprietary by the vendor may be assigned a code designation. Each variation in such factors shall be assigned a modified code designation. The vendor shall maintain complete records of all proprietary processes and parameters.

## 4.5 Reports:

- 4.5.1 The vendor of the product shall furnish with each shipment three copies of a report showing the results of tests for chemical composition of each lot and, when specified, the results of tests to determine conformance to the other technical requirements of this specification. This report shall include the purchase order number, lot number, AMS 5852A, size of billet or part number of preform, quantity, and the source and lot number of powder used to make the billets or preforms.
- 4.5.2 The vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, AMS 5852A, contractor or other direct supplier of material, part number, and quantity. When material for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of material to determine conformance to the requirements of this specification and shall include in the report either a statement that the material conforms or copies of laboratory reports showing the results of tests to determine conformance.

- 4.6 Resampling and Retesting: Shall be in accordance with AMS 2374.

## 5. PREPARATION FOR DELIVERY:

- 5.1 Identification: Shall be as agreed upon by purchaser and vendor.

### 5.2 Packaging:

- 5.2.1 The product shall be prepared for shipment in accordance with commercial practice and in compliance with applicable rules and regulations pertaining to the handling, packaging, and transportation of the product to ensure carrier acceptance and safe delivery. Packaging shall conform to carrier rules and regulations applicable to the mode of transportation.