

AEROSPACE MATERIAL SPECIFICATION

AMS 5870D

Issued MAY 1972
Reaffirmed AUG 2000
Revised MAY 2006
Superseding AMS 5870C

Nickel Alloy, Corrosion and Heat-Resistant, Sheet, Strip, and Plate
60.5Ni - 23Cr - 14Fe - 0.35Ti - 1.4Al
Solution Heat Treated

(Composition similar to UNS N06601)

RATIONALE

AMS 5870D is a Five Year Review involving prior general agreements (See 4.1 & 4.4) and other editorial text changes.

1. SCOPE

1.1 Form

This specification covers a corrosion and heat-resistant nickel alloy in the form of sheet, strip, and plate.

1.2 Application

These products have been used typically for parts requiring corrosion and oxidation resistance up to 2200 °F (1204 °C), particularly where such parts may require welding during fabrication, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or 724-776-4970 (outside USA), www.sae.org.

AMS 2262	Tolerances, Nickel, Nickel Alloy, and Cobalt Alloy Sheet, Strip, and Plate
AMS 2269	Chemical Check Analysis Limits, Nickel, Nickel Alloys, and Cobalt Alloys
AMS 2371	Quality Assurance Sampling and Testing, Corrosion and Heat-Resistant Steels and Alloys, Wrought Products and Forging Stock
AMS 2807	Identification, Carbon and Low-Alloy Steels, Corrosion and Heat-Resistant Steels and Alloys, Sheet, Strip, Plate, and Aircraft Tubing
AS4194	Sheet and Strip Surface Finish Nomenclature

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2006 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
SAE WEB ADDRESS: <http://www.sae.org>

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM A 480/A 480M	Flat-Rolled Stainless and Heat Resisting Steel Plate, Sheet, and Strip
ASTM E 8	Tension Testing of Metallic Materials
ASTM E 8M	Tension Testing of Metallic Materials (Metric)
ASTM E 290	Semi-Guided Bend Test for Ductility of Metallic Materials
ASTM E 354	Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 354, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - COMPOSITION

Element	min	max
Carbon	--	0.10
Manganese	--	1.00
Silicon	--	0.50
Sulfur	--	0.015
Chromium	21.00	25.00
Nickel	58.00	63.00
Titanium	0.10	0.60
Aluminum	1.00	1.70
Boron	--	0.006
Copper	--	1.00
Iron	remainder	

3.1.1 Check Analysis

Composition variations shall meet the applicable requirements of AMS 2269.

3.2 Condition

The product shall be supplied in the following condition:

3.2.1 Sheet and Strip

Cold rolled, solution heat treated, and, unless solution heat treatment is performed in an atmosphere yielding a bright finish, descaled having a surface appearance in accordance with ASTM A 480/A 480M and AS4194 comparable to 3.2.1.1 or 3.2.1.2 as applicable.

3.2.1.1 Sheet

No. 2D finish.

3.2.1.2 Strip

No. 1 strip finish.

3.2.2 Plate

Hot rolled and solution heat treated.

3.2.2.1 Surface finish shall be as hot rolled unless plate is ordered descaled.

3.3 Properties

The product shall conform to the following requirements:

3.3.1 Tensile Properties

Shall be as shown in Table 2 for product 0.010 to 2.000 inches (0.25 to 50.80 mm), inclusive, in nominal thickness, determined in accordance with ASTM E 8 or ASTM E 8M.

TABLE 2 - MINIMUM TENSILE PROPERTIES

Property	Value
Tensile Strength	80 ksi (552 MPa)
Yield Strength at 0.2% Offset	30.0 ksi (207 MPa)
Elongation in 2 Inches (50.8 mm) or 4D	35%

3.3.2 Bending

Product, 0.250-inch (6.35-mm) and under in nominal thickness, shall withstand, without cracking, bending in accordance with ASTM E 290 at room temperature through an angle of 180 degrees around a diameter equal to the bend factor shown in Table 3 times the nominal thickness of the product, with axis of bend parallel to the direction of rolling.

TABLE 3 - BENDING PARAMETERS

Nominal Thickness Inch	Nominal Thickness Millimeters	Bend Factor
Up to 0.050, incl	Up to 1.27, incl	1
Over 0.050 to 0.250, incl	Over 1.27 to 6.35, incl	2

3.4 Quality

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.5 Tolerances

Shall conform to all applicable requirements of AMS 2262.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.

4.2 Classification of Tests

All technical requirements are acceptance tests and shall be performed on each heat or lot as applicable.