

AEROSPACE MATERIAL SPECIFICATION

Submitted for recognition as an American National Standard

Issued DEC 1973
Revised AUG 1996

Superseding AMS 5873B

NICKEL ALLOY, CORROSION AND HEAT RESISTANT, SHEET, STRIP, AND PLATE
65Ni - 15.8Cr - 15.2Mo - 0.30Al - 0.05La.
Consumable Electrode Melted, Solution Heat Treated

UNS N06635

1. SCOPE:

1.1 Form:

This specification covers a corrosion and heat resistant nickel alloy in the form of sheet, strip, and plate.

1.2 Application:

These products have been used typically for formed and drawn parts, such as turbine seals, burner liners, exhaust cone assemblies, and nozzle diaphragm vanes, requiring relatively high strength up to 1800 °F (982 °C) and oxidation resistance up to 2000 °F (1093 °C), but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

AMS 2262 Tolerances, Nickel, Nickel Alloy, and Cobalt Alloy Sheet, Strip, and Plate

MAM 2262 Tolerances, Metric, Nickel, Nickel Alloy, and Cobalt Alloy Sheet, Strip, and Plate

AMS 2269 Chemical Check Analysis Limits, Nickel, Nickel Alloys, and Cobalt Alloys

AMS 2371 Quality Assurance Sampling and Testing, Corrosion and Heat Resistant Steels and Alloys, Wrought Products and Forging Stock

AMS 2807 Identification, Carbon and Low-Alloy Steels, Corrosion and Heat Resistant Steels and Alloys, Sheet, Strip, Plate, and Aircraft Tubing

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 1996 Society of Automotive Engineers, Inc.
All rights reserved.

Printed in U.S.A.

2.2 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959.

ASTM E 8	Tension Testing of Metallic Materials
ASTM E 8M	Tension Testing of Metallic Materials (Metric)
ASTM E 112	Determining the Average Grain Size
ASTM E 139	Conducting Creep, Creep-Rupture, and Stress-Rupture Tests of Metallic Materials
ASTM E 290	Semi-Guided Bend Test for Ductility of Metallic Materials
ASTM E 354	Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys

2.3 U.S. Government Publications:

Available from DODSSP, Subscription Services Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.

MIL-STD-163 Steel Mill Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

- 3.1 Composition: Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 354, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

Element	min	max
Carbon	--	0.02
Manganese	0.30	1.00
Silicon	0.20	0.75
Phosphorus	--	0.020
Sulfur	--	0.015
Chromium	14.50	17.00
Molybdenum	14.00	16.50
Aluminum	0.10	0.50
Lanthanum	0.01	0.10
Cobalt	--	2.00
Tungsten	--	1.00
Boron	--	0.015
Iron	--	3.00
Copper	--	0.35
Nickel	remainder	

3.1.1 Check Analysis: Composition variations shall meet the requirements of AMS 2269.

3.2 Melting Practice:

Alloy shall be multiple melted using consumable electrode practice in the remelt cycle.

3.3 Condition:

The product shall be supplied in the following condition:

3.3.1 Sheet and Strip: Hot or cold rolled, solution heat treated, and, unless solution heat treatment is performed in an atmosphere yielding a bright finish, descaled having a surface appearance comparable to the following commercial corrosion-resistant steel finishes as applicable (See 8.2):

3.3.1.1 Sheet: No. 2D finish.

3.3.1.2 Strip: No. 1 strip finish.

3.3.2 Plate: Hot rolled, solution heat treated, and descaled.

3.4 Heat Treatment:

The product shall be solution heat treated by heating to $1950^{\circ}\text{F} \pm 25$ ($1066^{\circ}\text{C} \pm 14$), holding at heat for a time commensurate with section thickness, and cooling rapidly in air.

3.5 Properties:

The product shall conform to the following requirements:

3.5.1 Average Grain Size: Shall be ASTM No. 4 or finer, determined in accordance with ASTM E 112 (R) (See 8.3).

3.5.2 Tensile Properties: Shall be as shown in Table 2, determined in accordance with ASTM E 8 or ASTM E 8M.

TABLE 2 - Minimum Tensile Properties

Property	Value
Tensile Strength	105 ksi (724 MPa)
Yield Strength at 0.2% Offset	45.0 ksi (310 MPa)
Elongation in 2 Inches (50.8 mm) or 4D	40%

- 3.5.3 Bending: Product 0.1874 inch (4.760 mm) and under in nominal thickness shall withstand, without cracking, bending at room temperature in accordance with ASTM E 290 through an angle of 180-degrees around a diameter equal to two times the nominal thickness of the product with axis of bend parallel to the direction of rolling.
- 3.5.4 Stress-Rupture Properties at 1500 °F (816 °C): A tensile specimen, maintained at 1500 °F $\pm$ 3 (816 °C $\pm$ 2) while a load sufficient to produce an initial axial stress of 15.0 ksi (103 MPa) or higher is applied continuously, shall not rupture in less than 23 hours. The test shall be continued to rupture without change of load. Elongation after rupture, measured at room temperature, shall be not less than 10% in 4D. Tests shall be conducted in accordance with ASTM E 139.
- 3.5.4.1 The test of 3.5.4 may be conducted using incremental loading. In such case, the load (R) required to produce an initial axial stress of 15.0 ksi (103 MPa) or higher shall be used to rupture or for 23 hours, whichever occurs first. After the 23 hours and at intervals of 8 to 16 hours thereafter, the stress shall be increased in increments of 2.0 ksi (14 MPa). Time to rupture and elongation requirements shall be as specified in 3.5.4.
- 3.6 Quality:
- The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.
- 3.7 Tolerances:
- Shall conform to all applicable requirements of AMS 2262 or MAM 2262.
4. QUALITY ASSURANCE PROVISIONS:
- 4.1 Responsibility for Inspection:
- The vendor of the product shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.
- 4.2 Classification of Tests:
- All technical requirements are acceptance tests and shall be performed on each heat or lot as applicable.
- 4.3 Sampling and Testing:
- (R) Shall be in accordance with AMS 2371.