



AEROSPACE MATERIAL SPECIFICATION

AMS5873**REV. F**Issued 1973-12
Revised 2014-12

Superseding AMS5837E

Nickel Alloy, Corrosion and Heat-Resistant, Sheet, Strip, and Plate
65Ni - 15.8Cr - 15.2Mo - 0.30Al - 0.05La
Consumable Electrode Remelted, Solution Heat Treated
(Composition similar to UNS N06635)

RATIONALE

AMS5873F revises Heat Treatment (3.4), and Reports (4.4), and is a Five Year Review and update of this specification.

1. SCOPE

1.1 Form

This specification covers a corrosion and heat-resistant nickel alloy in the form of sheet, strip, and plate.

1.2 Application

These products have been used typically for formed and drawn parts, such as turbine seals, burner liners, exhaust cone assemblies, and nozzle diaphragm vanes, requiring relatively high strength up to 1800 °F (982 °C) and oxidation resistance up to 2000 °F (1093 °C), but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or 724-776-4970 (outside USA), www.sae.org.

AMS2262 Tolerances, Nickel, Nickel Alloy, and Cobalt Alloy Sheet, Strip, and Plate

AMS2269 Chemical Check Analysis Limits, Nickel, Nickel Alloys, and Cobalt Alloys

AMS2371 Quality Assurance Sampling and Testing, Corrosion and Heat-Resistant Steels and Alloys, Wrought Products and Forging Stock

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2014 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
<http://www.sae.org>

SAE WEB ADDRESS:

**SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS5873F>**

AMS2807 Identification, Carbon and Low-Alloy Steels, Corrosion and Heat-Resistant Steels and Alloys, Sheet, Strip, Plate, and Aircraft Tubing

AS4194 Sheet and Strip Surface Finish Nomenclature

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM A 480/A 480M Flat-Rolled Stainless and Heat-Resisting Steel Plate, Sheet, and Strip

ASTM E 8/E 8M Tension Testing of Metallic Materials

ASTM E 112 Determining Average Grain Size

ASTM E 139 Conducting Creep, Creep-Rupture, and Stress-Rupture Tests of Metallic Materials

ASTM E 290 Bend Test of Materials for Ductility

ASTM E 354 Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 354, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

Element	min	max
Carbon	--	0.02
Manganese	0.30	1.00
Silicon	0.20	0.75
Phosphorus	--	0.020
Sulfur	--	0.015
Chromium	14.50	17.00
Molybdenum	14.00	16.50
Aluminum	0.10	0.50
Lanthanum	0.01	0.10
Cobalt	--	2.00
Tungsten	--	1.00
Boron	--	0.015
Iron	--	3.00
Copper	--	0.35
Nickel	remainder	

3.1.1 Check Analysis

Composition variations shall meet the applicable requirements of AMS2269.

3.2 Melting Practice

Alloy shall be multiple melted using consumable electrode practice in the remelt cycle.

3.3 Condition

The product shall be supplied in the following condition:

3.3.1 Sheet and Strip

Hot or cold rolled, solution heat treated, and, unless solution heat treatment is performed in an atmosphere yielding a bright finish, descaled having a surface appearance comparable to the following commercial corrosion resistant steel finishes as described in ASTM A 480/A 480M and AS4194 and 3.3.1.1 or 3.3.1.2 as applicable.

3.3.1.1 Sheet

No. 2D finish.

3.3.1.2 Strip

No. 1 strip finish.

3.3.2 Plate

Hot rolled, solution heat treated, and descaled.

3.4 Heat Treatment

Pyrometry shall be in accordance with AMS2750. Except as specified in 3.4.1, the product shall be solution heat treated by heating to $1950^{\circ}\text{F} \pm 25$ ($1066^{\circ}\text{C} \pm 14$), holding at heat for a time commensurate with section thickness, and cooling rapidly.

3.4.1 Continuous Heat Treating

Process parameters (e.g., furnace temperature set points, heat input, travel rate, etc.) for continuous heat treating lines shall be established by the material producer and validated by testing of product to the other requirements of this specification.

3.5 Properties

The product shall conform to the following requirements:

3.5.1 Average Grain Size

Shall be ASTM No. 4 or finer, determined in accordance with ASTM E 112.

3.5.2 Tensile Properties

Shall be as shown in Table 2, determined in accordance with ASTM E 8/E 8M.

TABLE 2 - Minimum Tensile Properties

Property	Value
Tensile Strength	105 ksi (724 MPa)
Yield Strength at 0.2% Offset	45.0 ksi (310 MPa)
Elongation in 2 Inches (50.8 mm) or 4D	40%

3.5.3 Bending

Product 0.1874 inch (4.760 mm) and under in nominal thickness shall be tested in accordance with ASTM E 290 using a sample prepared nominally 0.75 inch (19.0 mm) in width, with its axis of bending parallel to the direction of rolling, and shall withstand, without cracking, bending at room temperature through an angle of 180-degrees around a diameter equal to two times the nominal thickness of the product. In case of dispute, the results of tests using the guided bend test of ASTM E 290 shall govern.

3.5.4 Stress-Rupture Properties at 1500 °F (816 °C)

A tensile specimen, maintained at 1500 °F $\pm$ 3 (816 °C $\pm$ 2) while a load sufficient to produce an initial axial stress of 15.0 ksi (103 MPa) or higher is applied continuously, shall not rupture in less than 23 hours. The test shall be continued to rupture without change of load. Elongation after rupture, measured at room temperature, shall be not less than 10% in 4D. Tests shall be conducted in accordance with ASTM E 139.

3.5.4.1 The test of 3.5.4 may be conducted using incremental loading. In such case, the load required to produce an initial axial stress of 15.0 ksi (103 MPa) or higher shall be used to rupture or for 23 hours, whichever occurs first. After the 23 hours and at intervals of 8 hours minimum thereafter, the stress shall be increased in increments of 2.0 ksi (14 MPa). Time to rupture and elongation requirements shall be as specified in 3.5.4.

3.6 Quality

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.7 Tolerances

Shall conform to all applicable requirements of AMS2262.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.

4.2 Classification of Tests

All technical requirements are acceptance tests and shall be performed on each heat or lot as applicable.

4.3 Sampling and Testing

Shall be in accordance with AMS2371.

4.4 Reports

The vendor of the product shall furnish with each shipment a report showing the vendor's name and country where the metal was melted (e.g., final melt in the case of metal processed by multiple melting operations) and the following results of tests and relevant information:

4.4.1 For each heat

Composition.