

**AEROSPACE
MATERIAL
SPECIFICATION**

Submitted for recognition as an American National Standard

AMS 5875A

Issued 10-1-84
Revised 7-1-87

Superseding AMS 5875

ALLOY STRIP, CORROSION AND HEAT RESISTANT
20Cr - 15Ni - 40Co - 7.0Mo - 16Fe
Solution Heat Treated, Cold Rolled, and Aged

UNS R30003

1. SCOPE:

- 1.1 Form: This specification covers a high-strength, corrosion and heat resistant cobalt alloy in the form of strip 0.100 in. (2.50 mm) and under in specified thickness and 4.000 in. (100.00 mm) and under in specified width.
- 1.2 Application: Primarily for springs requiring a combination of high strength up to 800°F (425°C), excellent corrosion resistance, and good fatigue properties. Alloy is nonmagnetic.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

- 2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

- AMS 2269 - Chemical Check Analysis Limits, Wrought Nickel Alloys and Cobalt Alloys
- AMS 2350 - Standards and Test Methods
- AMS 2371 - Quality Assurance Sampling of Corrosion and Heat Resistant Steels and Alloys, Wrought Products Except Forgings and Forging Stock

10/91 **REAFFIRMED**

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM E8 - Tension Testing of Metallic Materials

ASTM E18 - Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials

ASTM E354 - Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel and Cobalt Alloys

2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Military Standards:

MIL-STD-163 - Steel Mill Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E354 or by spectrochemical or other analytical methods approved by purchaser:

	min	max
Carbon	--	0.15
Manganese	1.5 -	2.5
Silicon	--	1.20
Phosphorus	--	0.015
Sulfur	--	0.015
Chromium	19.0 -	21.0
Nickel	14.0 -	16.0
Cobalt	39.0 -	41.0
Molybdenum	6.0 -	8.0
Beryllium	--	0.10
Other Elements, total	--	1.00
Iron	remainder	

3.1.1 Check Analysis: Composition variations shall meet the requirements of AMS 2269.

3.2 Condition: Solution heat treated, cold rolled, and aged.

3.3 Heat Treatment: Strip shall be solution heat treated by heating to $2150^{\circ}\text{F} + 25$ ($1175^{\circ}\text{C} + 15$), holding at heat for a time commensurate with section thickness, and cooling as required. After cold rolling, the strip shall be aged by heating to a temperature within the range $850^{\circ} - 950^{\circ}\text{F}$ ($455^{\circ} - 510^{\circ}\text{C}$), holding at the selected temperature within $\pm 25^{\circ}\text{F}$ (15°C) for 5 - 5-1/2 hr, and cooling in air to room temperature.

3.4 Properties: Strip shall conform to the following requirements:

3.4.1 Tensile Properties: Shall be as specified in Table I, determined in accordance with ASTM E8.

TABLE I

Specified Thickness Inch	Tensile Strength psi, min	Yield Strength at 0.2% Offset, psi, min	Elongation in 2 in. %, min
Up to 0.0043, incl	325,000	250,000	-
Over 0.0043 to 0.01875, incl	315,000	225,000	-
Over 0.01875 to 0.025, incl	300,000	225,000	1
Over 0.025 to 0.047, incl	275,000	225,000	1
Over 0.047 to 0.075, incl	225,000	160,000	3
Over 0.075 to 0.100, incl	170,000	100,000	17

TABLE I (SI)

Specified Thickness Millimetres	Tensile Strength MPa, min	Yield Strength at 0.2% Offset, MPa, min	Elongation in 50 mm %, min
Up to 0.110, incl	2240	1725	-
Over 0.110 to 0.4688, incl	2170	1550	-
Over 0.4688 to 0.62, incl	2070	1550	1
Over 0.62 to 1.18, incl	1895	1550	1
Over 1.18 to 1.88, incl	1550	1105	3
Over 1.88 to 2.50, incl	1170	690	17

3.4.1 Elongation requirements do not apply to strip 0.01875 in. (0.4688 mm) and under in specified thickness.

3.4.2 Hardness: Should be not lower than 46 HRC, or equivalent, determined in accordance with ASTM E18, but strip shall not be rejected on the basis of hardness if the tensile property requirements are met.

3.5 Quality:

3.5.1 Alloy shall be produced by multiple melting using vacuum induction
Ø followed by vacuum consumable electrode or electroslog melting practices.

3.5.2 Strip, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the strip.

3.6 Tolerances: Width and thickness tolerances shall be in accordance with Tables II and III, respectively.

3.6.1 Width:

TABLE II

Specified Width Inches	Tolerance, inch plus and minus
Up to 0.3755, incl	0.0030
Over 0.3755 to 0.4999, incl	0.0040
Over 0.4999 to 4.0000, incl	0.0050

TABLE II (SI)

Specified Width Millimetres	Tolerance, millimetre plus and minus
Up to 9.500, incl	0.075
Over 9.500 to 12.500, incl	0.100
Over 12.500 to 100.000, incl	0.125

3.6.2 Thickness:

TABLE III

Specified Thickness Inch	Tolerance, Inch plus and minus
0.001 to 0.002, incl	0.00015
Over 0.002 to 0.004, incl	0.0002
Over 0.004 to 0.006, incl	0.0003
Over 0.006 to 0.009, incl	0.0004
Over 0.009 to 0.012, incl	0.0005
Over 0.012 to 0.015, incl	0.00065
Over 0.015 to 0.020, incl	0.00075
Over 0.020 to 0.025, incl	0.0010
Over 0.025 to 0.030, incl	0.00125
Over 0.030 to 0.050, incl	0.0015
Over 0.050 to 0.070, incl	0.00175
Over 0.070 to 0.100, incl	0.002

TABLE III (SI)

Specified Thickness Millimetres	Tolerance, Millimetre plus and minus
0.02 to 0.05, incl	0.0038
Over 0.05 to 0.10, incl	0.005
Over 0.10 to 0.15, incl	0.008
Over 0.15 to 0.22, incl	0.010
Over 0.22 to 0.30, incl	0.012
Over 0.30 to 0.38, incl	0.0162
Over 0.38 to 0.50, incl	0.0188
Over 0.50 to 0.62, incl	0.025
Over 0.62 to 0.75, incl	0.0312
Over 0.75 to 1.25, incl	0.038
Over 1.25 to 1.75, incl	0.0438
Over 1.75 to 2.50, incl	0.050

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of strip shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the strip conforms to the requirements of this specification.

4.2 Classification of Tests: Tests to determine conformance to all technical requirements of this specification are classified as acceptance tests and shall be performed on each heat or lot as applicable.

4.3 Sampling: Shall be in accordance with AMS 2371; a heat shall be the
 Ø remelted ingots produced from alloy originally melted as a single furnace charge.

4.4 Reports:

4.4.1 The vendor of strip shall furnish with each shipment a report showing the
 Ø results of tests for composition of each heat and for tensile properties and hardness of each lot. This report shall include the purchase order number, heat number, AMS 5875A, size, and quantity.

4.4.2 The vendor of finished or semi-finished parts shall furnish with each shipment a report showing the purchase order number, AMS 5875A, contractor or other direct supplier of strip, part number, and quantity. When strip for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of strip to determine conformance to the requirements of this specification and shall include in the report either a statement that the strip conforms or copies of laboratory reports showing the results of tests to determine conformance.