

AEROSPACE MATERIAL SPECIFICATION



AMS 5886B

Issued JUL 1986
Revised OCT 2003
Reaffirmed MAY 2008

Superseding AMS 5886A

Alloy, Corrosion and Heat-Resistant, Bars, Forgings, and Rings
50Ni - 20Cr - 20Co - 5.8Mo - 2.2Ti - 0.45Al
Consumable Electrode or Vacuum Induction Melted
2100 °F (1149 °C) Solution Heat Treated
(Composition similar to UNS N07263)

1. SCOPE:

1.1 Form:

This specification covers a corrosion and heat-resistant nickel alloy in the form of bars, forgings, flash welded rings, and stock for forging or flash welded rings.

1.2 Application:

These products have been used typically for parts requiring high strength up to 1500 °F (816 °C) and oxidation resistance up to 2000 °F (1093 °C), particularly those parts which are formed or welded and then heat treated to develop required properties, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS:

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent supplied herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001 or www.sae.org.

AMS 2261	Tolerances, Nickel, Nickel Alloy, and Cobalt Alloy Bars, Rods, and Wire
AMS 2269	Chemical Check Analysis Limits, Nickel, Nickel Alloys and Cobalt Alloys
AMS 2371	Quality Assurance Sampling and Testing, Corrosion and Heat-Resistant Steels and Alloys, Wrought Products and Forging Stock

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2008 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: 724-776-4970 (outside USA)

Fax: 724-776-0790

Email: CustomerService@sae.org

SAE WEB ADDRESS: <http://www.sae.org>

2.1 (Continued):

AMS 2374	Quality Assurance Sampling and Testing, Corrosion and Heat-Resistant Steel and Alloy Forgings
AMS 2806	Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Corrosion and Heat-Resistant Steels and Alloys
AMS 2808	Identification, Forgings
AMS 7490	Rings, Flash Welded, Corrosion and Heat-Resistant Austenitic Steels, Austenitic-Type Iron, Nickel, or Cobalt Alloys, or Precipitation Hardenable Alloys

2.2 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959 or www.astm.org.

ASTM E 10	Brinell Hardness of Metallic Materials
ASTM E 21	Elevated Temperature Tests of Metallic Materials
ASTM E 139	Conducting Creep, Creep-Rupture, and Stress-Rupture Tests of Metallic Materials
ASTM E 354	Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 354, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

Element	min	max
Carbon	0.04	0.08
Manganese	--	0.60
Silicon	--	0.40
Phosphorus	--	0.015
Sulfur	--	0.007
Chromium	19.00	21.00
Cobalt	19.00	21.00
Molybdenum	5.60	6.10
Titanium	1.90	2.40
Aluminum	0.30	0.60
Titanium + Aluminum	2.40	2.80
Boron	--	0.005
Iron	--	0.70
Copper	--	0.20
Nickel	remainder	

3.1.1 Check Analysis: Composition variations shall meet the applicable requirements of AMS 2269.

3.2 Melting Practice:

The alloy shall be produced by multiple melting using consumable electrode practice in the remelt cycle or shall be induction melted under vacuum.

3.3 Condition:

The product shall be supplied in the following condition:

3.3.1 Bars: Solution heat treated and descaled.

3.3.1.1 Bars shall be hot rolled or extruded; round bars shall be ground or turned.

3.3.2 Forgings and Flash Welded Rings: Solution heat treated.

3.3.2.1 Flash welded rings shall not be supplied unless specified or permitted on purchaser's part drawing. When supplied, rings shall be manufactured in accordance with AMS 7490.

3.3.3 Stock for Forging or Flash Welded Rings: As ordered by the forging or flash welded ring manufacturer.

3.4 Heat Treatment:

Bars, forgings, and flash welded rings shall be solution heat treated by heating to a temperature within the range 1900 to 2125 °F (1038 to 1163 °C) holding at the selected temperature within ± 25 °F (± 14 °C) for a time commensurate with cross-sectional thickness, and cooling at a rate equivalent to an air cool or faster.

3.5 Properties:

The product shall conform to the following requirements:

3.5.1 Bars, Forgings, and Flash Welded Rings:

3.5.1.1 As Solution Heat Treated:

3.5.1.1.1 Hardness: Shall be not higher than 248 HB, or equivalent (See 8.2), determined in accordance with ASTM E 10.

3.5.1.2 After Precipitation Heat Treatment: Product 3.25 inches (82.6 mm) and under in nominal diameter or least distance between parallel sides shall have the following properties after being precipitation heat treated by heating to 1475 °F ± 15 (802 °C ± 8), holding at heat for 8 hours ± 0.5 , and cooling in air; product over 3.25 inches (82.6 mm) in nominal diameter or least distance between parallel sides shall have properties as agreed upon by purchaser and vendor:

3.5.1.2.1 Tensile Properties at 1435 °F (779 °C): Shall be as shown in Table 2, determined in accordance with ASTM E 21 on specimens heated to 1435 °F ± 10 (779 °C ± 6) held at heat for 20 to 30 minutes before testing, and tested at 1435 °F ± 10 (779 °C ± 6).

TABLE 2 - Minimum Tensile Properties

Property	Value
Tensile Strength	78.5 ksi (541 MPa)
Yield Strength at 0.2% Offset	58.5 ksi (403 MPa)
Elongation in 4D	12%

3.5.1.2.2 Creep Properties at 1435 °F (779 °C): A tensile specimen, maintained at 1435 °F ± 3 (779 °C ± 2) while a load sufficient to produce an initial axial stress 17.4 ksi (120 MPa) is applied continuously, shall not exceed 0.1% total plastic strain in 50 hours. Test shall be conducted in accordance with ASTM E 139.

3.5.2 Forging Stock: When a sample of stock is forged to a test coupon and heat treated as in 3.4 and 3.5.1.2, specimens taken from the heat treated coupon shall conform to the requirements of 3.5.1.2.1 and 3.5.1.2.2. If specimens taken from stock after heat treatment as in 3.4 and 3.5.1.2 conform to the requirements of 3.5.1.2.1 and 3.5.1.2.2, the tests shall be accepted as equivalent to tests of a forged coupon.

3.5.3 Stock for Flash Welded Rings: Specimens taken from the stock after heat treatment as in 3.4 and 3.5.1.2 shall conform to the requirements of 3.5.1.2.1 and 3.5.1.2.2.

3.6 Quality:

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.6.1 Grain flow, except in areas of die forgings which contain flash-line end grain, shall follow the general contour of the forgings showing no evidence of re-entrant grain flow.

3.7 Tolerances:

Bars shall conform to all applicable requirements of AMS 2261.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: The following requirements are acceptance tests and shall be performed on each heat or lot as applicable.

4.2.1.1 Composition (3.1) of each heat.

4.2.1.2 Hardness (3.5.1.1.1) of each lot of bars, forgings, and flash welded rings as solution heat treated.

4.2.1.3 Tensile properties (3.5.1.2.1) and creep properties (3.5.1.2.2) of each lot of bars, forgings, and flash welded rings after precipitation heat treatment.

4.2.1.4 Tolerances of bars (3.7).

4.2.2 Periodic Tests: Tests of forging stock (3.5.2) and of stock for flash welded rings (3.5.3) to demonstrate ability to develop required properties, and grain flow of forgings (3.6.1) are periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.3 Sampling and Testing:

Shall be as follows:

4.3.1 Bars, Flash Welded Rings, and Stock for Forging or Flash Welded Rings: In accordance with AMS 2371.

4.3.2 Forgings: In accordance with AMS 2374.

4.4 Reports:

The vendor of the product shall furnish with each shipment a report showing the following results of tests and relevant information:

4.4.1 For each heat:

Composition.

4.4.2 For each lot of bars, forgings, and flash welded rings:

Hardness solution heat treated

Tensile properties after precipitation heat treated

Creep properties after precipitation heat treated

4.4.3 A statement that the product conforms to the other technical requirements.

4.4.4 Purchase order number

Heat and lot numbers

AMS 5886B

Size

Quantity

The specific solution heat treatment temperature used.

4.4.5 If forgings are supplied, the size and melt source of stock used to make the forgings

4.5 Resampling and Retesting:

Shall be as follows:

4.5.1 Bars, Flash Welded Rings, and Stock for Forging or Flash Welded Rings: In accordance with AMS 2371.

4.5.2 Forgings: In accordance with AMS 2374.