

SAE The Engineering Society
For Advancing Mobility
Land Sea Air and Space®
INTERNATIONAL

400 Commonwealth Drive, Warrendale, PA 15096-0001

AEROSPACE MATERIAL SPECIFICATION

SAE

AMS 5893

Issued 1 APR 1992

Submitted for recognition as an American National Standard

IRON-NICKEL ALLOY, BARS, FORGINGS, AND RINGS
42Fe - 37.5Ni - 14Co - 4.8(Cb + Ta) - 1.6Ti
Solution Heat Treated, Short-Time Precipitation Hardenable
Multiple Melted, High Temperature, Low Expansion

UNS N19909

1. SCOPE:

1.1 Form:

This specification covers an iron-nickel alloy in the form of bars, forgings, flash welded rings, and stock for forging, flash welded rings, or heading.

1.2 Application:

These products have been used typically for parts requiring a combination of high strength and low expansion properties up to 1200 °F (649 °C), but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

AMS 2261 Tolerances, Nickel, Nickel Alloy, and Cobalt Alloy Bars, Rods, and Wire

MAM 2261 Tolerances, Metric, Nickel, Nickel Alloy, and Cobalt Alloy Bars, Rods, and Wire

AMS 2269 Chemical Check Analysis Limits, Wrought Nickel Alloys and Cobalt Alloys

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

AMS 5893

SAE

AMS 5893

2.1 SAE Publications (Continued):

- AMS 2371 Quality Assurance Sampling and Testing, Corrosion and Heat Resistant Steels and Alloys, Wrought Products and Forging Stock
- AMS 2374 Quality Assurance Sampling and Testing, Corrosion and Heat Resistant Steel and Alloy Forgings
- AMS 2750 Pyrometry
- AMS 2806 Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels, Corrosion and Heat Resistant Steels and Alloys
- AMS 2808 Identification, Forgings
- AMS 7490 Rings, Flash Welded, Corrosion and Heat Resistant Austenitic Steels and Austenitic-Type Alloys or Precipitation Hardenable Alloys

2.2 ASTM Publications:

Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

- ASTM E 8 Tension Testing of Metallic Materials
- ASTM E 8M Tension Testing of Metallic Materials (Metric)
- ASTM E 10 Brinell Hardness of Metallic Materials
- ASTM E 21 Elevated Temperature Tension Tests of Metallic Materials
- ASTM E 103 Rapid Indentation Hardness Testing of Metallic Materials
- ASTM E 112 Determining Average Grain Size
- ASTM E 228 Linear Thermal Expansion of Solid Materials with a Vitreous Silica Dilatometer
- ASTM E 292 Conducting Time-for-Rupture Notch Tension Tests of Materials
- ASTM E 354 Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys
- ASTM E 930 Estimating the Largest Grain Observed in a Metallographic Section (ALA Grain Size)
- ASTM E 1181 Characterizing Duplex Grain Sizes

2.3 U.S. Government Publications:

Available from Standardization Documents Order Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.

MIL-STD-163 Steel Mill Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:**3.1 Composition:**

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 354, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

AMS 5893

SAE

AMS 5893

TABLE 1 - Composition

Element	min	max
Carbon	--	0.06
Manganese	--	1.0
Silicon	0.25	0.50
Phosphorus	--	0.015
Sulfur	--	0.015
Nickel	35.0	40.0
Cobalt	12.0	16.0
Columbium + Tantalum	4.3	5.2
Titanium	1.3	1.8
Chromium	--	1.0
Aluminum	--	0.15
Boron	--	0.012
Copper	--	0.5
Iron	remainder	

3.1.1 Check Analysis: Composition variations shall meet the requirements of AMS 2269.

3.2 Melting Practice:

Alloy shall be multiple melted using consumable electrode practice in the remelt cycle. If consumable electrode remelting is not performed in vacuum, electrodes which have been produced by vacuum induction melting shall be used for remelting.

3.3 Condition:

The product shall be supplied in the following condition:

3.3.1 Bars, Forgings, and Flash Welded Rings: Solution heat treated and descaled.

3.3.1.1 Bars shall be hot finished; round bars shall be ground or turned.

3.3.1.2 Flash welded rings shall not be supplied unless specified or permitted on purchaser's part drawing. When supplied, rings shall be manufactured in accordance with AMS 7490.

3.3.2 Stock for Forging, Flash Welded Rings, of Heading: As ordered by the forging, flash welded ring, or heading manufacturer.

AMS 5893

SAE

AMS 5893

3.4 Solution Heat Treatment:

Bars, forgings, and flash welded rings shall be solution heat treated by heating to a temperature within the range of 1775 to 1850 °F (968 to 1010 °C), holding at a selected temperature within ± 25 °F (± 14 °C) for a time commensurate with section thickness, and cooling at a rate equivalent to a still air cool (See 8.1).

3.4.1 Pyrometry shall be in accordance with AMS 2750.

3.4.2 If forgings are not to be machined all over, heat treatment shall be performed in a suitable protective atmosphere or, when permitted by purchaser, a suitable protective coating may be applied to the forgings in lieu of using a protective atmosphere.

3.5 Properties:

The product shall conform to the following requirements:

3.5.1 Bars, Forgings, and Flash Welded Rings:

3.5.1.1 As Solution Heat Treated:

3.5.1.1.1 Hardness: Shall be not higher than 277 HB, or equivalent, determined in accordance with ASTM E 10 or ASTM E 103.

3.5.1.1.2 Grain Size:

3.5.1.1.2.1 Bars, forgings, and flash welded rings 9 square inches (58 cm²) and under in cross-sectional area shall exhibit an average grain size, determined in accordance with ASTM E 112, of ASTM No. 5 or finer with no more than 20% of the specimen area as large as ASTM No. 3. No single grain shall be larger than 0.010 inch (0.25 mm), determined in accordance with ASTM E 930.

3.5.1.1.2.2 Bars, forgings, and flash welded rings over 9 square inches (58 cm²) in cross-sectional area shall exhibit an average grain size, determined in accordance with ASTM E 112, of ASTM No. 4 or finer with no more than 20% of the specimen area as large as ASTM No. 2. No single grain shall be larger than 0.014 inch (0.36 mm), determined in accordance with ASTM E 930.

3.5.1.1.2.3 When agreed upon by purchaser and vendor, the grain size of 20% of the specimen area may be as large as ASTM No. 0. No single grain shall be larger than 0.020 inch (0.51 mm), determined in accordance with ASTM E 930.

3.5.1.1.2.4 Limitations on duplex grain structures as defined by ASTM E 1181 shall be as agreed upon by purchaser and vendor.

AMS 5893

SAE

AMS 5893

3.5.1.2 After Re-Solution and Precipitation Heat Treatment: The product shall have the following properties after being re-solution heat treated by heating to $1800^{\circ}\text{F} \pm 25$ ($982^{\circ}\text{C} \pm 14$), holding at heat for 60 minutes ± 15 , and cooling at a rate equivalent to an air cool and precipitation heat treated by heating to $1375^{\circ}\text{F} \pm 15$ ($746^{\circ}\text{C} \pm 8$), holding at heat for four hours ± 0.5 , cooling at a maximum rate of 100 F (56 C) degrees per hour to $1150^{\circ}\text{F} \pm 15$ ($621^{\circ}\text{C} \pm 8$), holding at heat for four hours ± 0.5 , and cooling at a rate equivalent to an air cool (See 8.1 and 8.2).

3.5.1.2.1 Tensile Properties:

3.5.1.2.1.1 At Room Temperature: Shall be as shown in Table 2, determined in accordance with ASTM E 8 or ASTM E 8M.

TABLE 2 - Minimum Tensile Properties

Property	Value
Tensile Strength	170 ksi (1172 MPa)
Yield Strength at 0.2% Offset	125 ksi (862 MPa)
Elongation in 4D %	10%
Reduction of Area %	15%

3.5.1.2.1.2 At 1200°F (649°C): Shall be as shown in Table 3, determined in accordance with ASTM E 21 on specimens heated to $1200^{\circ}\text{F} \pm 5$ ($649^{\circ}\text{C} \pm 3$), held at heat for 20 to 30 minutes before testing, and tested at $1200^{\circ}\text{F} \pm 5$ ($649^{\circ}\text{C} \pm 3$).

TABLE 3 - Minimum Tensile Properties

Property	Value
Tensile Strength	130 ksi (896 MPa)
Yield Strength at 0.2% Offset	95.0 ksi (655 MPa)
Elongation in 4D %	10%
Reduction of Area %	20%

3.5.1.2.1.3 Specific location of specimens from forgings and flash welded rings shall be as agreed upon by purchaser and vendor.

AMS 5893

SAE

AMS 5893

- 3.5.1.2.2 Hardness: Should be not lower than 331 HB, or equivalent, determined in accordance with ASTM E 10 or ASTM E 103, but the product shall not be rejected on the basis of hardness if the tensile property requirements of 3.5.1.2.1.1 are met.
- 3.5.1.2.3 Stress-Rupture Properties at 1000 °F (538 °C): Shall be as follows: testing of notched specimens shall be performed in accordance with ASTM E 292.
- 3.5.1.2.3.1 A notched specimen conforming to Figure 1 of this specification maintained at 1000 °F $\pm$ 3 (538 °C $\pm$ 2) while a load sufficient to produce an initial axial stress of 120 ksi (827 MPa) is applied continuously, shall not rupture in less than 60 hours. Tests may be discontinued after 120 hours.
- 3.5.1.2.3.2 The test may be conducted using a load higher than required to produce an initial stress of 120 ksi (827 MPa) but the load shall not be changed while the test is in progress. The minimum time to rupture shall be as specified in 3.5.1.2.3.1.
- 3.5.1.2.4 Thermal Expansion: Shall be determined in accordance with ASTM E 228 on each heat of alloy.
- 3.5.1.2.4.1 Coefficient of Expansion: Shall be $4.00 - 4.50 \times 10^{-6}$ inch/inch/°F ($7.2 - 8.1 \times 10^{-6}$ mm/mm/°C) at 780 °F (416 °C) using 77 °F (25 °C) as a reference temperature.
- 3.5.1.2.4.2 Inflection Temperature: Shall be 750 to 850 °F (399 to 454 °C), determined by establishing the intersection of the tangents of the upper and lower portions of the dilatometric expansion curve.
- 3.5.2 Forging Stock: When a sample of stock is forged to a test coupon and heat treated as in 3.4 and 3.5.1.2, specimens taken from the heat treated coupon shall conform to the requirements of 3.5.1.2.1, 3.5.1.2.2, 3.5.1.2.3, and 3.5.1.2.4. If specimens taken from the stock after heat treatment as in 3.4 and 3.5.1.2 conform to the requirements of 3.5.1.2.1, 3.5.1.2.2, 3.5.1.2.3, and 3.5.1.2.4, the tests shall be accepted as equivalent to tests of a forged coupon.
- 3.5.3 Stock for Flash Welded Rings or Heading: Specimens taken from the stock after heat treatment as in 3.4 and 3.5.1.2 shall conform to the requirements of 3.5.1.2.1, 3.5.1.2.2, 3.5.1.2.3, and 3.5.1.2.4.
- 3.6 Quality:
- The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.
- 3.6.1 Grain flow of die forgings, except in areas which contain flash-line end grain, shall follow the general contour of the forgings showing no evidence of re-entrant grain flow.

AMS 5893

SAE

AMS 5893

3.7 Tolerances:

Bars shall conform to all applicable requirements of AMS 2261 or MAM 2261.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

4.2 Classification of Tests:

Tests for all technical requirements are acceptance tests and shall be performed on each heat or lot as applicable.

4.3 Sampling and Testing:

Shall be in accordance with the following:

4.3.1 Bars, Flash Welded Rings, and Stock for Forging, Flash Welded Rings, or Heading: AMS 2371.

4.3.2 Forgings: AMS 2374.

4.4 Reports:

4.4.1 The vendor of bars, forgings, and flash welded rings shall furnish with each shipment a report showing the results of tests for chemical composition of each heat and the results of tests on each lot to determine conformance to the other acceptance test requirements. This report shall include the purchase order number, lot number, AMS 5893, solution heat treatment temperature used, size, and quantity. If forgings are supplied, the part number and the size and melt source of stock used to make the forgings shall also be included.

4.4.2 The vendor of stock for forgings, flash welded rings, or heading shall furnish with each shipment a report showing the results of tests for chemical composition of each heat. This report shall include the purchase order number, heat number, AMS 5893, size, and quantity.

4.5 Resampling and Retesting:

Shall be in accordance with the following:

4.5.1 Bars, Flash Welded Rings, and Stock for Forging, Flash Welded Rings, or Heading: AMS 2371.

4.5.2 Forgings: AMS 2374.

AMS 5893

SAE

AMS 5893

5. PREPARATION FOR DELIVERY:

5.1 Sizes:

Except when exact lengths or multiples of exact lengths are ordered, straight bars will be acceptable in mill lengths of 6 to 24 feet (1.8 to 7.3 m) but not more than 25% of any shipment shall be supplied in lengths of 6 to 9 feet (1.8 to 2.7 m) except that for bars weighing over 25 pounds per foot (37 kg/m), short lengths down to 2 feet (610 m) may be supplied.

5.2 Identification:

Shall be as follows:

5.2.1 Bars: In accordance with AMS 2806.

5.2.2 Forgings: In accordance with AMS 2808.

5.2.3 Flash Welded Rings and Stock for Forging, Flash Welded Rings, or Heading: As agreed upon by purchaser and vendor.

5.3 Packaging:

5.3.1 The product shall be prepared for shipment in accordance with commercial practice and in compliance with applicable rules and regulations pertaining to the handling, packaging, and transportation of the product to ensure carrier acceptance and safe delivery.

5.3.2 For direct U.S. Military procurement, packaging shall be in accordance with MIL-STD-163, Commercial Level, unless Level A is specified in the request for procurement.

6. ACKNOWLEDGMENT:

A vendor shall mention this specification number in all quotations and when acknowledging purchase orders.

7. REJECTIONS:

Product not conforming to this specification, or to modifications authorized by purchaser, will be subject to rejection.

8. NOTES:

8.1 Heating and cooling should be done in a vacuum or a suitable protective atmosphere so as to avoid oxidation of the surface. If heat treating is done in air, the product must be properly processed to completely recover the oxide formed before further fabrication or testing.