

AEROSPACE MATERIAL SPECIFICATION

SAE AMS5925

REV. A

Issued 1999-05
Revised 2006-08
Reaffirmed 2012-04

Superseding AMS5925

Steel, Corrosion-Resistant, Bars, Wire, and Forgings

15.5Cr - 1.8Mo - 0.20N (0.37 - 0.45C)

Electroslag Remelted

(Composition similar to UNS S42025)

RATIONALE

AMS5925A has been reaffirmed to comply with the SAE five-year review policy.

1. SCOPE

1.1 Form

This specification covers a premium aircraft-quality, corrosion-resistant steel in the form of bars, wire, forgings, and forging stock.

1.2 Application

These products have been used typically for anti-friction bearing components requiring resistance to both corrosion and wear with hardness not lower than 58 HRC after hardening and tempering, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or 724-776-4970 (outside USA), or www.sae.org.

AMS 2241	Tolerances, Corrosion and Heat-Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Bars and Wire
AMS 2248	Chemical Check Analysis Limits, Corrosion and Heat-Resistant Steels and Alloys, Maraging and Other Highly-Alloyed Steels, and Iron Alloys
AMS 2300	Steel Cleanliness, Premium Aircraft-Quality Magnetic Particle Inspection Procedure
AMS 2371	Quality Assurance Sampling and Testing, Corrosion and Heat-Resistant Steels and Alloys, Wrought Products and Forging Stock
AMS 2374	Quality Assurance Sampling and Testing, Corrosion and Heat-Resistant Steel and Alloy Forgings
AMS 2806	Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Corrosion and Heat-Resistant Steels and Alloys

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2012 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

**SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS5925A>**

AMS 2808 Identification, Forgings

AS1182 Standard Machining Allowance, Aircraft-Quality and Premium Aircraft-Quality Steel Bars and Mechanical Tubing

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, or www.astm.org.

ASTM A 370 Mechanical Testing of Steel Products

ASTM A 604 Macroetch Testing of Consumable Electrode Remelted Steel Bars and Billets

ASTM E 45 Determining the Inclusion Content of Steel

ASTM E 112 Determining Average Grain Size

ASTM E 353 Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys

ASTM E 384 Microindentation Hardness of Materials

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 353, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - COMPOSITION

Element	min	max
Carbon	0.37	0.45
Manganese	--	0.60
Silicon	--	0.60
Phosphorus	--	0.020
Sulfur	--	0.005
Chromium	15.00	16.50
Molybdenum	1.50	1.90
Vanadium	0.20	0.40
Nitrogen	0.16	0.25
Nickel	--	0.30

3.1.1 Check Analysis

Composition variations shall meet the applicable requirements of AMS 2248.

3.2 Melting Practice

Steel shall be multiple melted using the electroslog remelt practice in the final melting cycle.

3.3 Condition

The product shall be supplied in the following condition; hardness and tensile strength shall be determined in accordance with ASTM A 370:

3.3.1 Bars

Annealed having hardness not higher than 255 HB, or equivalent (See 8.2).

3.3.1.1 Bars 2.750 Inches (69.85 mm) and Under in Nominal Diameter or Least Distance Between Parallel Sides and All Hexagons

Cold finished.

3.3.1.2 Bars, Other than Hexagons, Over 2.750 Inches (69.85 mm) in Nominal Diameter or Least Distance Between Parallel Sides

Hot finished.

3.3.2 Wire

Annealed and cold finished having tensile strength not higher than 130 ksi (896 MPa).

3.3.3 Forgings

As ordered.

3.3.4 Forging Stock

As ordered by the forging manufacturer.

3.4 Properties

The product shall conform to the following requirements; hardness testing shall be performed in accordance with ASTM A 370:

3.4.1 Bars, Wire and Forgings

3.4.1.1 Macrostructure

Visual examination of transverse sections from bars, wire, billets, and forging stock etched in hot hydrochloric acid in accordance with ASTM A 604, shall show no pipe or cracks. Porosity, segregation, inclusions, and other imperfections for product 36 square inches (232 cm²) and under in nominal cross-sectional area shall be no worse than the macrographs of ASTM A 604 shown in Table 2.

TABLE 2 - MACROSTRUCTURE LIMITS

Class	Condition	Severity
1	Freckles	A
2	White Spots	A
3	Radial Segregation	B
4	Ring Pattern	B

3.4.1.2 Micro-Inclusion Rating

No specimens shall exceed the limits of Table 3, determined in accordance with ASTM E 45, Method D.

TABLE 3 - MICRO-INCLUSION RATING LIMITS

	A Thin	A Heavy	B Thin	B Heavy	C Thin	C Heavy	D Thin	D Heavy
Worst Field Severity	1.5	1.0	1.5	1.0	1.0	1.0	1.5	1.0
Worst Field								
Frequency, maximum	a	1	a	1	a	1	3	1
Total Rateable Fields,								
Frequency, maximum (c)	b	1	b	1	b	1	b	1
a Combined A+B+C; not more 3 fields b Combined A+B+C; not more 8 fields c A+B+C+D; not more 16 fields								

3.4.1.2.1 A rateable field is defined as one which has a type A, B, C, or D inclusion rating of at least No. 1.0 thin or heavy in accordance with the Jernkontoret chart, Plate I-r, ASTM E 45 (See 8.4).

3.4.1.3 Microstructure

The product shall be free of carbide network. For the products of sections between 0.15 and 12.4 square inches (1 and 80 cm²), the maximum carbide size allowed is: 0.0014 inch (35 μm) for isolated carbides, 0.0010 inch (25 μm) for grouped carbides [distance between carbides < 0.0020 inch (50 μm)]. The examination shall be carried out at mid-radius (or equivalent) on a surface that is parallel to the grain flow.

3.4.1.4 Average Grain Size

Shall be ASTM No. 6 or finer, determined in accordance with ASTM E 112.

3.4.2 Decarburization and Denitridation

3.4.2.1 Bars and wire ordered ground, turned, or polished shall be free from decarburization and/or denitridation on the ground, turned, or polished surfaces.

3.4.2.2 Allowable decarburization and/or denitridation of bars, wire, and billets ordered for redrawing or forging or to specified microstructural requirements shall be as agreed upon by purchaser and vendor.

3.4.2.3 Decarburization and/or denitridation of bars and wire, to which 3.4.2.1 or 3.4.2.2 is not applicable, shall be not greater than shown in Table 4.

TABLE 4A - MAXIMUM DECARBURIZATION/DENITRIDATION, INCH/POUND UNITS

Nominal Diameter or Distance Between Parallel Sides, Inches	Total Depth of Decarburization/Denitridation Inch
Up to 0.500, incl	0.015
Over 0.500 to 1.000, incl	0.020
Over 1.000 to 1.500, incl	0.025
Over 1.500 to 2.000, incl	0.030
Over 2.000 to 2.500, incl	0.035
Over 2.500 to 3.000, incl	0.040
Over 3.000 to 4.000, incl	0.045

TABLE 4B - MAXIMUM DECARBURIZATION/DENITRIDATION, SI UNITS

Nominal Diameter or Distance Between Parallel Sides, Millimeters	Total Depth of Decarburization/Denitridation Millimeters
Up to 12.70, incl	0.38
Over 12.70 to 25.40, incl	0.51
Over 25.40 to 38.10, incl	0.64
Over 38.10 to 50.80, incl	0.76
Over 50.80 to 63.50, incl	0.89
Over 63.50 to 76.20, incl	1.02
Over 76.20 to 101.60, incl	1.14

3.4.2.4 Decarburization and denitridation shall be measured by the microscopic method, by HR30N scale hardness testing method, or by the microhardness traverse method using microhardness testing in accordance with ASTM E 384. The hardness method(s) shall be conducted on a hardened but untempered specimen protected during heat treatment to prevent changes in surface carbon and nitrogen content. Depth of decarburization or denitridation, when measured by a hardness method, is defined as the perpendicular distance from the surface to the depth under that surface below which there is no further increase in hardness. Such measurements shall be far enough away from any adjacent surface to be uninfluenced by decarburization/denitridation on the adjacent surface. In case of dispute, the microhardness traverse method shall govern.

3.4.2.4.1 When determining the depth of decarburization/denitridation it is permissible to disregard local areas provided the decarburization/denitridation of such areas does not exceed the above limits by more than 0.005 inch (0.13 mm) and the width is 0.065 inch (1.65 mm) or less.

3.4.3 Response to Heat Treatment

Specimens as in 4.3.3, protected by suitable means or treated in neutral atmosphere to minimize scaling and prevent either carburization or decarburization, shall have hardness not lower than 58 HRC, or equivalent (See 8.2), after being heated to $1920^{\circ}\text{F} \pm 25$ ($1049^{\circ}\text{C} \pm 14$), held at heat for 30 minutes ± 3 , quenched in oil, sub-zero cooled to $-100^{\circ}\text{F} \pm 20$ ($-73^{\circ}\text{C} \pm 11$), held for 2 hours ± 0.25 , warmed in air to room temperature and tempered at $350^{\circ}\text{F} \pm 10$ ($177^{\circ}\text{C} \pm 6$) for 60 minutes ± 5 .

3.5 Quality

The product, as received by the purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.5.1 Steel shall be premium aircraft-quality conforming to AMS 2300.

3.5.2 Bars and wire ordered hot rolled or cold drawn or ground, turned, or polished shall, after removal of the standard machining allowance in accordance with AS1182, be free from seams, laps, tears, and cracks open to the ground, turned, or polished surface.

3.5.3 Grain flow of die forgings, except in areas that contain flash-line end grain, shall follow the general contour of the forgings showing no evidence of reentrant grain flow.

3.6 Tolerances

Bars and wire shall conform to all applicable requirements of AMS 2241.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.

4.2 Classification of Tests

4.2.1 Acceptance Tests

Composition (3.1), condition (3.3), macrostructure (3.4.1.1), microinclusion rating (3.4.1.2), microstructure (3.4.1.3), average grain size (3.4.1.4), decarburization and denitridation (3.4.2), response to heat treatment (3.4.3), frequency-severity cleanliness rating (3.5.1 & 8.3), and tolerances (3.6) are acceptance tests and shall be performed on each heat or lot as applicable.

4.2.2 Periodic Tests

Grain flow of die forgings (3.5.3) is a periodic test and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.3 Sampling and Testing

Shall be as follows:

4.3.1 Bars, Wire and Forging Stock

In accordance with AMS 2371.

4.3.2 Forgings

In accordance with AMS 2374.

4.3.3 Specimens for response to heat treatment (3.4.3) from bars, wire, and billets shall be not less than 0.375 inch (9.52 mm) in thickness. Minimum dimensions in other directions shall be either those of the product cross-section or 1.125×1.125 inches (28.58×28.58 mm).

4.4 Reports

The vendor of the product shall furnish with each shipment a report showing the results of tests for composition, macrostructure, micro-inclusion rating, and frequency-severity cleanliness rating of each heat (See 8.3) and for microstructure, decarburization denitridation, and response to heat treatment of each lot, and stating that the product conforms to the other technical requirements. This report shall include the purchase order number, heat and lot numbers, AMS 5925A, size, and quantity. If forgings are supplied, the size and melt source of stock used to make the forgings shall also be included.

4.5 Resampling and Retesting

Shall be as follows:

4.5.1 Bars, Wire, and Forging Stock

In accordance with AMS 2371.

4.5.2 Forgings

In accordance with AMS 2374.

5. PREPARATION FOR DELIVERY

5.1 Sizes

Except when exact lengths or multiples of exact lengths are ordered, straight bars and wire will be acceptable in mill lengths of 6 to 20 feet (1.8 to 6.1 m) but not more than 10% of any shipment shall be supplied in lengths shorter than 10 feet (3 m).