



# AEROSPACE MATERIAL SPECIFICATION

**AMS6281™****REV. L**

Issued 1945-10  
Reaffirmed 2015-05  
Revised 2025-04

Superseding AMS6281K

Steel, Mechanical Tubing  
0.50Cr - 0.55Ni - 0.20Mo (0.25 - 0.33C) (SAE 8630)  
Aircraft Quality  
(Composition similar to UNS G86300)

## RATIONALE

AMS6281L is the result of a Five-Year Review and update of the specification. The revision updates composition reporting (see 3.1.2), revises decarburization test methods (see 3.3.4.4), addresses periodic testing in AMS2301 (see 4.2.1, 4.4.1, and 4.4.3), adds country of origin to reporting requirements (see 4.4.1), and provides guidance on stock removal and naming convention (see 8.7 and 8.8).

### 1. SCOPE

#### 1.1 Form

This specification covers an aircraft-quality, low-alloy steel in the form of mechanical tubing.

#### 1.2 Application

This product has been used typically for parts, with section thickness of 0.50 inch (12.7 mm) and under at time of heat treatment, requiring a through-hardening steel capable of developing hardness as high as 35 HRC and for parts of greater thickness requiring proportionately lower hardness, but usage is not limited to such applications.

### 2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

#### 2.1 SAE Publications-

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or +1 724-776-4970 (outside USA), [www.sae.org](http://www.sae.org).

AMS2253 Tolerances, Carbon and Alloy Steel Tubing

AMS2259 Chemical Check Analysis Limits, Wrought Low-Alloy and Carbon Steels

SAE Executive Standards Committee Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2025 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system, transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, or used for text and data mining, AI training, or similar technologies, without the prior written permission of SAE.

**TO PLACE A DOCUMENT ORDER:** Tel: 877-606-7323 (inside USA and Canada)  
Tel: +1 724-776-4970 (outside USA)  
Fax: 724-776-0790  
Email: [CustomerService@sae.org](mailto:CustomerService@sae.org)  
**SAE WEB ADDRESS:** <http://www.sae.org>

**For more information on this standard, visit**  
<https://www.sae.org/standards/content/AMS6281L/>

|          |                                                                                                                                            |
|----------|--------------------------------------------------------------------------------------------------------------------------------------------|
| AMS2301  | Steel Cleanliness, Aircraft Quality, Magnetic Particle Inspection Procedure                                                                |
| AMS2370  | Quality Assurance Sampling and Testing, Carbon and Low-Alloy Steel Wrought Products and Forging Stock                                      |
| AMS2806  | Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels, and Corrosion and Heat-Resistant Steels and Alloys |
| AS1182   | Standard Stock Removal Allowance, Aircraft-Quality and Premium Aircraft-Quality Steel Bars and Mechanical Tubing                           |
| AS7766   | Terms Used in Aerospace Metals Specifications                                                                                              |
| SAE J404 | Chemical Compositions of SAE Alloy Steels                                                                                                  |

## 2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, [www.astm.org](http://www.astm.org).

|            |                                                                                                                                                                                               |
|------------|-----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| ASTM A255  | End-Quench Test for Hardenability of Steel                                                                                                                                                    |
| ASTM A370  | Mechanical Testing of Steel Products                                                                                                                                                          |
| ASTM A751  | Chemical Analysis of Steel Products                                                                                                                                                           |
| ASTM E112  | Determining Average Grain Size                                                                                                                                                                |
| ASTM E140  | Hardness Conversion Tables for Metals Relationship Among Brinell Hardness, Vickers Hardness, Rockwell Hardness, Superficial Hardness, Knoop Hardness, Scleroscope Hardness, and Leeb Hardness |
| ASTM E381  | Macroetch Testing, Steel Bars, Billets, Blooms, and Forgings                                                                                                                                  |
| ASTM E1077 | Estimating the Depth of Decarburization of Steel Samples                                                                                                                                      |

## 2.3 Definitions

Terms used in AMS are defined in AS7766.

## 3. TECHNICAL REQUIREMENTS

### 3.1 Composition

Composition shall conform to the percentages by weight shown in Table 1, determined in accordance with ASTM A751 or by other analytical methods acceptable to the purchaser.

**Table 1 - Composition**

| Element    | Min  | Max   |
|------------|------|-------|
| Carbon     | 0.28 | 0.33  |
| Manganese  | 0.70 | 0.90  |
| Silicon    | 0.15 | 0.35  |
| Phosphorus | --   | 0.025 |
| Sulfur     | --   | 0.025 |
| Chromium   | 0.40 | 0.60  |
| Nickel     | 0.40 | 0.70  |
| Molybdenum | 0.15 | 0.25  |
| Copper     | --   | 0.35  |

3.1.1 Aluminum, vanadium, and columbium (niobium) are optional grain refining elements and need not be determined or reported unless used to satisfy the average grain size requirements of 3.3.2.2.

3.1.2 The producer may test for any element not listed in Table 1 and include this analysis in the report of 4.4. Reporting of any element not listed in the composition table is not a basis for rejection unless limits of acceptability are specified by the purchaser.

3.1.3 Check Analysis

Composition variations shall meet the applicable requirements of AMS2259.

3.2 Condition

Tubing shall be cold finished, unless otherwise ordered, having hardness not higher than 25 HRC, or equivalent (see 8.2). Tubing ordered hot finished and annealed or tempered shall have hardness not higher than 99 HRB, or equivalent (see 8.2). Hardness shall be determined in accordance with ASTM A370.

3.3 Properties

Tubing shall conform to the following requirements:

3.3.1 Macrostructure

Visual examination of full cross sections from billets or tube rounds, etched in hot hydrochloric acid in accordance with ASTM E381, shall show no pipe or cracks. Porosity, segregation, inclusions, and other imperfections shall be no worse than the macrographs of ASTM E381 shown in Table 2.

**Table 2 - Macrostructure limits**

| Section Size<br>Square Inches | Section Size<br>Square Centimeters | Macrographs  |
|-------------------------------|------------------------------------|--------------|
| Up to 36, incl                | Up to 232, incl                    | S2 - R1 - C2 |
| Over 36 to 133, incl          | Over 232 to 858, incl              | S2 - R2 - C3 |
| Over 133                      | Over 858                           | (1)          |

(1) Limits for larger sizes shall be agreed upon by the purchaser and producer.

3.3.1.1 Macrostructure examination is not required for tubing that is produced directly from ingots or blooms unless specified by the purchaser, in which case the purchaser shall specify standards to be used.

3.3.2 Average Grain Size of Tubing

Average grain size shall be determined by either 3.3.2.1 or 3.3.2.2.

3.3.2.1 The average grain size shall be ASTM No. 5 or finer, determined in accordance with ASTM E112.

3.3.2.2 The product of a heat shall be considered to have an ASTM No. 5 or finer austenitic grain size if one or more of the following are determined by heat analysis (see 8.6):

- A total aluminum content of 0.020 to 0.050%.
- An acid soluble aluminum content of 0.015 to 0.050%.
- A vanadium content of 0.02 to 0.08%.
- A columbium (niobium) content of 0.02 to 0.05%.

### 3.3.3 Hardenability

Hardenability shall be J 5/16 inch (7.9 mm) = 35 HRC minimum and J 8/16 inch (12.7 mm) = 28 HRC minimum, determined on the standard end-quench test specimen in accordance with ASTM A255, except that the steel shall be normalized at 1650 °F ± 10 °F (899 °C ± 6 °C) and the test specimen austenitized at 1600 °F ± 10 °F (871 °C ± 6 °C). Cast specimens do not need to be normalized.

### 3.3.4 Decarburization

3.3.4.1 Tubing ordered ground, turned, or polished shall be free from decarburization on the ground, turned, or polished surfaces. Decarburization on tubing ID shall not exceed the maximum depth specified in Table 3.

3.3.4.2 Allowable decarburization of pierced billets, of tube rounds or tubing for redrawing or forging, or of tubing ordered to specified microstructural requirements shall be as agreed upon by the purchaser and producer.

3.3.4.3 Where 3.3.4.1 or 3.3.4.2 are not applicable, decarburization of tubing shall not be greater than shown in Table 3.

**Table 3A - Maximum decarburization, inch/pound units**

| Nominal Wall Thickness<br>Inch | Total Depth of<br>Decarburization, Inch<br>ID | Total Depth of<br>Decarburization, Inch<br>OD |
|--------------------------------|-----------------------------------------------|-----------------------------------------------|
| Up to 0.109, incl              | 0.008                                         | 0.015                                         |
| Over 0.109 to 0.203, incl      | 0.010                                         | 0.020                                         |
| Over 0.203 to 0.400, incl      | 0.012                                         | 0.025                                         |
| Over 0.400 to 0.600, incl      | 0.015                                         | 0.030                                         |
| Over 0.600 to 1.000, incl      | 0.017                                         | 0.035                                         |
| Over 1.000                     | 0.020                                         | 0.040                                         |

**Table 3B - Maximum decarburization, SI units**

| Nominal Wall Thickness<br>Millimeters | Total Depth of<br>Decarburization, Millimeters<br>ID | Total Depth of<br>Decarburization, Millimeters<br>OD |
|---------------------------------------|------------------------------------------------------|------------------------------------------------------|
| Up to 2.77, incl                      | 0.20                                                 | 0.38                                                 |
| Over 2.77 to 5.16, incl               | 0.25                                                 | 0.51                                                 |
| Over 5.16 to 10.16, incl              | 0.30                                                 | 0.64                                                 |
| Over 10.16 to 15.24, incl             | 0.38                                                 | 0.76                                                 |
| Over 15.24 to 25.40, incl             | 0.43                                                 | 0.89                                                 |
| Over 25.40                            | 0.51                                                 | 1.02                                                 |

3.3.4.4 Decarburization shall be evaluated by one of the two methods of 3.3.4.4.1 or 3.3.4.4.2.

#### 3.3.4.4.1 Metallographic (Microscopic) Method

A cross section taken perpendicular to the surface shall be prepared, etched, and visually examined metallographically at a magnification not to exceed 200X. The sample shall not show a layer of complete (ferrite) or partial decarburization exceeding the limits of Table 3.

#### 3.3.4.4.2 Hardness Traverse (Microindentation) Method

The total depth of decarburization shall be determined by a traverse method using microindentation hardness testing in accordance with ASTM E1077. Samples shall be hardened and protected during heat treatment to prevent changes in surface carbon content. Samples may be tempered at the option of the producer. Measurements shall be far enough away from any adjacent surface to be uninfluenced by any decarburization on the adjacent surface. Acceptance shall be as listed in Table 3.

3.3.4.5 When determining the depth of decarburization, it is permissible to disregard local areas provided the decarburization of such areas does not exceed the above limits by more than 0.005 inch (0.13 mm) and the width is 0.065 inch (1.65 mm) or less.

3.3.4.6 In case of dispute, the total depth of decarburization determined using the microindentation hardness traverse method shall govern.

### 3.4 Quality

Tubing, as received by the purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the tubing.

3.4.1 Steel shall be aircraft-quality conforming to AMS2301.

3.4.2 Mechanical tubing shall be free from seams, laps, tears, and cracks after removal of the standard stock removal allowance in accordance with AS1182.

### 3.5 Tolerances

Tolerances shall conform to all applicable requirements of AMS2253.

### 3.6 Exceptions

Any exceptions shall be authorized by the purchaser and reported as in 4.4.2.

## 4. QUALITY ASSURANCE PROVISIONS

### 4.1 Responsibility for Inspection

The producer of tubing shall supply all samples for the producer's tests and shall be responsible for the performance of all required tests. The purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the tubing conforms to specified requirements.

### 4.2 Classification of Tests

#### 4.2.1 Acceptance Tests

All technical requirements are acceptance tests and shall be performed on each heat or lot as applicable. If grain refining elements (see 3.3.2.2) are not present, the ASTM E112 grain size test (see 3.3.2.1) shall be conducted on each lot. If process qualification in accordance with AMS2301 has been met, the frequency-severity cleanliness rating shall be conducted on a periodic basis as defined in AMS2301.

#### 4.2.2 Periodic Tests

If grain refining elements (see 3.3.2.2) are present, the ASTM E112 grain size test (see 3.3.2.1) shall be conducted on a periodic basis and shall be performed at a frequency selected by the producer (not to exceed 1 year) unless frequency of testing is specified by the purchaser.

### 4.3 Sampling and Testing

Sampling and testing shall be in accordance with AMS2370.