



AEROSPACE MATERIAL SPECIFICATION

AMS6282**REV. J**

Issued 1944-11
Revised 2006-05
Reaffirmed 2015-05

Superseding AMS6282H

Steel Tubing, Mechanical
0.50Cr - 0.55Ni - 0.25Mo (0.33 - 0.38C) (SAE 8735)
(Composition similar to UNS G87350)

RATIONALE

AMS6282J has been reaffirmed to comply with the SAE five-year review policy.

1. SCOPE

1.1 Form

This specification covers an aircraft-quality, low-alloy steel in the form of mechanical tubing.

1.2 Application

This product has been used typically for parts, 0.75 inch (19.0 mm) and under in section thickness at time of heat treatment, requiring a through-hardening steel capable of developing hardness as high as 40 HRC when properly hardened and tempered, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or 724-776-4970 (outside USA), or www.sae.org.

AMS 2253	Tolerances, Carbon and Alloy Steel Tubing
AMS 2259	Chemical Check Analysis Limits, Wrought Low-Alloy and Carbon Steels
AMS 2301	Steel Cleanliness, Aircraft-Quality, Magnetic Particle Inspection Procedure
AMS 2370	Quality Assurance Sampling and Testing, Carbon and Low-Alloy Steel, Wrought Products and Forging Stock
AMS 2806	Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Corrosion and Heat-Resistant Steels and Alloys
AS1182	Standard Machining Allowance, Aircraft-Quality and Premium Aircraft-Quality Steel Bars and Mechanical Tubing

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2015 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
<http://www.sae.org>

SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS6282J>

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P. O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, or www.astm.org.

ASTM A 255	Determining Hardenability of Steel
ASTM A 370	Mechanical Testing of Steel Products
ASTM E 112	Determining Average Grain Size
ASTM E 350	Chemical Analysis of Carbon Steel, Low-Alloy Steel, Silicon Electrical Steel, Ingot Iron, and Wrought Iron
ASTM E 381	Macroetch Testing Steel Bars, Billets, Blooms, and Forgings
ASTM E 384	Microindentation Hardness of Materials

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the percentages by weight, shown in Table 1, determined by wet chemical methods in accordance with ASTM E 350, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - COMPOSITION

Element	min	max
Carbon	0.33	0.38
Manganese	0.75	1.00
Silicon	0.15	0.35
Phosphorus	--	0.025
Sulfur	--	0.025
Chromium	0.40	0.60
Nickel	0.40	0.70
Molybdenum	0.20	0.30
Copper	--	0.35

3.1.1 Check Analysis

Composition variations shall meet the applicable requirements of AMS 2259.

3.2 Condition

Cold finished, unless otherwise ordered, having hardness not higher than 25 HRC, or equivalent (See 8.2). Tubing ordered hot finished and annealed or tempered shall have hardness not higher than 99 HRB, or equivalent (See 8.2). Hardness shall be determined in accordance with ASTM A 370.

3.3 Properties

Tubing shall conform to the following requirements; hardness testing shall be performed in accordance with ASTM A 370:

3.3.1 Macrostructure

Visual examination of transverse full cross sections from billets or tube rounds, etched in hot hydrochloric acid in accordance with ASTM E 381, shall show no pipe or cracks. Porosity, segregation, inclusions, and other imperfections shall be no worse than the macrographs of ASTM E 381 shown in Table 2.

TABLE 2 - MACROSTRUCTURE LIMITS

Section Size Square Inches	Section Size Square Centimeters	Macrographs
Up to 36, incl	Up to 232, incl	S2 - R1 - C2
Over 36 to 100, incl	Over 232 to 645, incl	S2 - R2 - C3

3.3.2 Average Grain Size

Shall be ASTM No. 5 or finer, determined in accordance with ASTM E 112.

3.3.3 Hardenability

Shall be J 5/16 inch (7.9 mm) = 45 HRC minimum and J 6/16 inch (9.5 mm) = 41 HRC minimum, determined on the standard end-quench test specimen in accordance with ASTM A 255 except that the steel shall be normalized at 1700 °F ± 10 (927 °C ± 6) and the test specimen austenitized at 1500 °F ± 10 (816 °C ± 6).

3.3.4 Decarburization

3.3.4.1 Tubing ordered ground, turned, or polished shall be free from decarburization on the ground, turned, or polished surfaces. Decarburization on the ID of such tubing shall not exceed the maximum depth specified in Table 3.

3.3.4.2 Allowable decarburization of pierced billets, of tube rounds, or tubing for redrawing or forging, or of tubing ordered to specified microstructural requirements, shall be as agreed upon by purchaser and vendor.

3.3.4.3 Decarburization of tubing to which 3.3.4.1 or 3.3.4.2 is not applicable shall not be greater than shown in Table 3.

TABLE 3A - MAXIMUM DECARBURIZATION, INCH/POUND UNITS

Nominal Wall Thickness Inches	Total Depth of Decarburization, Inch	Total Depth of Decarburization, Inch
	ID	OD
Up to 0.109, incl	0.008	0.015
Over 0.109 to 0.203, incl	0.010	0.020
Over 0.203 to 0.400, incl	0.012	0.025
Over 0.400 to 0.600, incl	0.015	0.030
Over 0.600 to 1.000, incl	0.017	0.035
Over 1.000	0.020	0.040

TABLE 3B - MAXIMUM DECARBURIZATION, SI UNITS

Nominal Wall Thickness Millimeters	Total Depth of Decarburization, Millimeter	Total Depth of Decarburization, Millimeters
	ID	OD
Up to 2.77, incl	0.20	0.38
Over 2.77 to 5.16, incl	0.25	0.51
Over 5.16 to 10.16, incl	0.30	0.64
Over 10.16 to 15.24, incl	0.38	0.76
Over 15.24 to 25.40, incl	0.43	0.89
Over 25.40	0.51	1.02

3.3.4.4 Decarburization shall be measured by the metallographic method, by the HR30N scale hardness testing method, or by a traverse method using microhardness testing in accordance with ASTM E 384. The hardness method(s) shall be conducted on a hardened but untempered specimen protected during heat treatment to prevent changes in surface carbon content. Depth of decarburization, when measured by a hardness method, is defined as the perpendicular distance from the surface to the depth under that surface below which there is no further increase in hardness. Such measurements shall be far enough away from any adjacent surface to be influenced by any decarburization on the adjacent surface. In case of dispute, the depth of decarburization determined using the microhardness traverse method shall govern.

3.3.4.4.1 When determining the depth of decarburization, it is permissible to disregard local areas provided the decarburization of such areas does not exceed the above limits by more than 0.005 inch (0.13 mm) and the width is 0.065 inch (1.65 mm) or less.

3.4 Quality

3.4.1 Steel shall be aircraft-quality conforming to AMS 2301.

3.4.2 Tubing, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the tubing.

3.4.3 Mechanical tubing ordered hot rolled or cold drawn, or ground, turned, or polished shall, after removal of the standard machining allowance in accordance with AS1182, be free from seams, laps, tears, and cracks open to the ground, turned, or polished surface.

3.5 Tolerances

Shall conform to all applicable requirements of AMS 2253.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The vendor of tubing shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the tubing conforms to specified requirements.

4.2 Classification of Tests

All technical requirements of this specification are acceptance tests and shall be performed on each heat or lot as applicable.

4.3 Sampling and Testing

Shall be in accordance with AMS 2370.

4.4 Reports

The vendor shall furnish with each shipment a report showing the results of tests for composition, macrostructure, hardenability, and frequency-severity cleanliness rating of each heat, and for hardness and average grain size of each lot, and stating that the product conforms to the other technical requirements. This report shall include the purchase order number, heat and lot numbers, AMS 6282J, size, and quantity.

4.5 Resampling and Retesting

Shall be in accordance with AMS 2370.

5. PREPARATION FOR DELIVERY

Sizes

Except when exact lengths or multiples of exact lengths are ordered, straight tubing will be acceptable in mill lengths of 6 to 20 feet (1.8 to 6.1 m) but not more than 10% of any shipment shall be supplied in lengths shorter than 10 feet (3 m).

5.1 Identification

Shall be in accordance with AMS 2806.

5.2 Protective Treatment

Tubing ordered cold drawn, cold rolled, ground, turned, or polished shall be protected from corrosion prior to shipment.