

AEROSPACE MATERIAL SPECIFICATION

AMS 6327J

Issued SEP 1942
Reaffirmed OCT 2000
Revised OCT 2007

Superseding AMS 6327H

Steel Bars and Forgings
0.50Cr - 0.55Ni - 0.25Mo (0.38 - 0.43C) (SAE 8740)
Heat Treated, 125 ksi (862 MPa) Tensile Strength

(Composition similar to UNS G87400)

RATIONALE

AMS 6327J results from a Five Year Review and update of this specification.

1. SCOPE

1.1 Form

This specification covers an aircraft-quality, low-alloy steel in the form of bars and forgings.

1.2 Application

These products have been used typically for parts, such as nuts, bolts, and screws, 1.50 inch (38.1 mm) and under in section thickness, requiring a minimum tensile strength of 125 ksi (862 MPa), but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or 724-776-4970 (outside USA), www.sae.org.

AMS 2251	Tolerances, Low-Alloy Steel Bars
AMS 2259	Chemical Check Analysis Limits, Wrought Low-Alloy and Carbon Steels
AMS 2301	Steel Cleanliness, Aircraft Quality, Magnetic Particle Inspection Procedure
AMS 2370	Quality Assurance Sampling and Testing, Carbon and Low-Alloy Steel, Wrought Products and Forging Stock
AMS 2372	Quality Assurance Sampling and Testing, Carbon and Low-Alloy Steel, Forgings
AMS 2750	Pyrometry
AMS 2806	Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Corrosion and Heat-Resistant Steels and Alloys

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2007 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
SAE WEB ADDRESS: <http://www.sae.org>

AMS 2808 Identification, Forgings
AMS-H-6875 Heat Treatment of Steel

AS1182 Standard Stock Removal Allowance, Aircraft-Quality and Premium Aircraft-Quality Steel Bars and Mechanical Tubing

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM A 370 Mechanical Testing of Steel Products
ASTM E 112 Determining Average Grain Size
ASTM E 350 Chemical Analysis of Carbon Steel, Low-Alloy Steel, Silicon Electrical Steel, Ingot Iron, and Wrought Iron
ASTM E 381 Macroetch Testing, Inspection, and Rating Steel Products Comprising Bars, Billets, Blooms, and Forgings
ASTM E 384 Microindentation Hardness of Materials

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 350, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - COMPOSITION

Element	min	max
Carbon	0.38	0.43
Manganese	0.75	1.00
Silicon	0.15	0.35
Phosphorus	--	0.025
Sulfur	--	0.025
Chromium	0.40	0.60
Nickel	0.40	0.70
Molybdenum	0.20	0.30
Copper	--	0.35

3.1.1 Check Analysis

Composition variations shall meet the applicable requirements of AMS 2259.

3.2 Condition

The product shall be supplied in the following condition:

3.2.1 Bars

3.2.1.1 Bars 0.500 Inch (12.70 mm) and Under in Nominal Diameter or Least Distance Between Parallel Sides

Cold finished, hardened, and tempered.

3.2.1.2 Bars Over 0.500 Inch (12.70 mm) in Nominal Diameter or Least Distance Between Parallel Sides

Hot finished, or cold finished when so ordered, and hardened and tempered.

3.2.2 Forgings

Hardened and tempered in accordance with AMS-H-6875.

3.3 Heat Treatment

Bars shall be hardened by quenching from 1550 °F ± 25 (843 °C ± 14) and tempered as required; Pyrometry shall be in accordance with AMS 2750.

3.4 Properties

The product shall conform to the following requirements; hardness and tensile testing shall be performed in accordance with ASTM A 370:

3.4.1 Average Grain Size

Shall be ASTM No. 5 or finer, determined in accordance with ASTM E 112.

3.4.2 Macrostructure

Visual examination of transverse full cross sections from bars, billets, and forging stock, etched in hot hydrochloric acid in accordance with ASTM E 381, shall show no pipe or cracks. Porosity, segregation, inclusions, and other imperfections shall be no worse than the macrographs of ASTM E 381 shown in Table 2:

TABLE 2 - MACROSTRUCTURE LIMITS

Section Size Square Inches	Section Size Square Centimeters	Macrographs
Up to 36, incl	Up to 232, incl	S2 - R1 - C2
Over 36 to 100, incl	Over 232 to 645, incl	S2 - R2 - C3

3.4.3 Decarburization

3.4.3.1 Bars ordered ground, turned, or polished shall be free from decarburization on the ground, turned, or polished surfaces.

3.4.3.2 Decarburization of bars to which 3.4.3.1 is not applicable shall be not greater than shown in Table 3.

TABLE 3A - MAXIMUM DECARBURIZATION LIMITS, INCH/POUND UNITS

Nominal Diameter or Distance Between Parallel Sides Inches	Total Depth of Decarburization Inch
Up to 0.375, incl	0.010
Over 0.375 to 0.500, incl	0.012
Over 0.500 to 0.625, incl	0.014
Over 0.625 to 1.000, incl	0.017
Over 1.000 to 1.500, incl	0.020

TABLE 3B - MAXIMUM DECARBURIZATION LIMITS, SI UNITS

Nominal Diameter or Distance Between Parallel Sides Millimeters	Total Depth of Decarburization Millimeter
Up to 9.52, incl	0.25
Over 9.52 to 12.70, incl	0.30
Over 12.70 to 15.88, incl	0.36
Over 15.88 to 25.40, incl	0.43
Over 25.40 to 38.10, incl	0.51

3.4.3.3 Decarburization shall be measured by the metallographic method, by the HR30N scale hardness testing method, or by a traverse method using microhardness testing in accordance with ASTM E 384. The hardness method(s) shall be conducted on a hardened but untempered specimen protected during heat treatment to prevent changes in surface carbon content. Depth of decarburization, when measured by a hardness method, is defined as the perpendicular distance from the surface to the depth under that surface below which there is no further increase in hardness. Such measurements shall be far enough away from any adjacent surface to be uninfluenced by any decarburization on the adjacent surface. In case of dispute, the depth of decarburization determined using the microhardness traverse method shall govern.

3.4.3.3.1 When determining the depth of decarburization, it is permissible to disregard local areas provided the decarburization of such areas does not exceed the above limits by more than 0.005 inch (0.13 mm) and the width is 0.065 inch (1.65 mm) or less.

3.4.4 Tensile Properties

Specimens cut from bars 1.500 inches (38.10 mm) and under in nominal diameter or distance between parallel sides and from forgings 1.500 inches (38.10 mm) and under in nominal cross-section shall conform to the requirements of Table 4.

TABLE 4 - MINIMUM MECHANICAL PROPERTIES

Property	Value
Tensile Strength	125 ksi (862 MPa)
Yield Strength at 0.2% Offset	100 ksi (689 MPa)
Elongation in 4D	16%
Reduction of Area	50%

3.4.5 Hardness

Shall be 252 to 311 HB, or equivalent (See 8.2), but the product shall not be rejected on the basis of hardness if the tensile property requirements of 3.4.4 are acceptable, determined on specimens taken from the same sample as the one with nonconforming hardness or from another sample with similar nonconforming hardness.

3.5 Quality

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.5.1 Steel shall be aircraft-quality conforming to AMS 2301.

3.5.2 Bars ordered hot rolled or cold drawn, or ground, turned, or polished, shall, after removal of the standard stock removal allowance in accordance with AS1182, be free from seams, laps, tears, and cracks open to the ground, turned, or polished surface.

3.5.3 Forgings shall have substantially uniform macrostructure. Standards for acceptance shall be as agreed upon by purchaser and vendor (See 8.5).

3.5.4 Grain flow of die forgings, except in areas that contain flash-line end grain, shall follow the general contour of the forgings showing no evidence of reentrant grain flow.

3.6 Tolerances

Bars shall conform to all applicable requirements of AMS 2251.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.

4.2 Classification of Tests

4.2.1 Acceptance Tests

Composition (3.1), average grain size (3.4.1), macrostructure (3.4.2), decarburization (3.4.3), tensile properties (3.4.4), hardness (3.4.5), frequency-severity cleanliness (3.5.1), and tolerances (3.6) are acceptance tests and shall be performed on each heat or lot as applicable.

4.2.2 Periodic Tests

Grain flow of die forgings (3.5.4) is a periodic test and shall be performed at a frequency selected by the vendor unless a frequency of testing is specified by purchaser.

4.3 Sampling

Shall be as follows:

4.3.1 Bars and Forging Stock

In accordance with AMS 2370.

4.3.2 Forgings

In accordance with AMS 2372.

4.4 Reports

The vendor of the product shall furnish with each shipment a report showing the results of composition, macrostructure, and frequency-severity cleanliness rating for each heat and for average grain size, tensile properties and hardness of each lot, and stating that the product conforms to other technical requirements. This report shall include the purchase order number, heat and lot numbers, AMS 6327J, product form, size, and quantity. If forgings are supplied, the size and melt source of stock used to make the forgings shall also be included.

4.5 Resampling and Retesting

Shall be as follows:

4.5.1 Bars and Forging Stock

In accordance with AMS 2370.

4.5.2 Forgings

In accordance with AMS 2372.