

NOTICE OF
ADOPTION

ADOPTION NOTICE
20 December 1991
AMS 6350H
1 October 1990
SUPERSEDING
AMS 6350G
3 August 1987

AMS 6350H was adopted on 20 December 1991 and is approved for use by the Department of Defense (DOD). Copies of this document are stocked at the Standardization Documents Order Desk, Bldg 4D, 700 Robbins Avenue, Philadelphia, Pennsylvania 19111-5094 for issue to DOD activities only. Other Government Agencies, contractors, private concerns, or other requestors must obtain the document from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

Title of Document: Steel Sheet, Strip, and Plate
0.95Cr - 0.20Mo (0.28 - 0.33C) (SAE 4130)

Date of Specific Issue Adopted: 1 October 1990

Releasing Non-Government Standards Body: SAE

Custodians:

Air Force - 11
Army - MR
Navy - AS

Military Coordinating Activity

Air Force - 11

(Project No: 9515-0908)

FSC 9515

DISTRIBUTION STATEMENT A: Approved for public release; distribution is unlimited.

SAE The Engineering Society
For Advancing Mobility
Land Sea Air and Space®
INTERNATIONAL

400 Commonwealth Drive, Warrendale, PA 15096-0001

AEROSPACE MATERIAL SPECIFICATION

SAE AMS-6350

REV
H

Issued 1942-12-01
Revised 1990-10-01

Superseding AMS-6350G

Submitted for recognition as an American National Standard

STEEL SHEET, STRIP, AND PLATE
0.95Cr - 0.20Mo (0.28 - 0.33C) (SAE 4130)

UNS G41300

1. SCOPE:

1.1 Form: This specification covers an aircraft-quality, low-alloy steel in the form of sheet, strip, and plate.

1.2 Application: Primarily for use where welding and moderate tensile properties are required. Sheet and strip are extensively used where minimum tensile strength of 180,000 psi (1241 MPa) is required in sections up to 0.125 inch (3.18 mm) in nominal thickness and proportionately lower strength is required in heavier thicknesses.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

2.1.1 Aerospace Material Specifications:

AMS-2252 - Tolerances, Low-Alloy Steel Sheet, Strip, and Plate
MAM-2252 - Tolerances, Metric, Low-Alloy Steel Sheet, Strip, and Plate
AMS-2259 - Chemical Check Analysis Limits, Wrought Low-Alloy and Carbon Steels
AMS-2301 - Aircraft Quality Steel Cleanliness, Magnetic Particle Inspection Procedure
AMS-2370 - Quality Assurance Sampling of Carbon and Low-Alloy Steels, Wrought Products Except Forgings and Forging Stock

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

AMS-6350 Revision H

- 2.2 ASTM Publications: Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

ASTM A 370 - Mechanical Testing of Steel Products

ASTM E 112 - Determining Average Grain Size

ASTM E 350 - Chemical Analysis of Carbon Steel, Low-Alloy Steel, Silicon Electrical Steel, Ingot Iron, and Wrought Iron

- 2.3 U.S. Government Publications: Available from Standardization Documents Order Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.

- 2.3.1 Military Standards:

MIL-STD-163 - Steel Mill Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

- 3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E 350, by spectrochemical methods, or by other analytical methods acceptable to purchaser:

	min	max
Carbon	0.28	0.33
Manganese	0.40	0.60
Silicon	0.15	0.35
Phosphorus	--	0.025
Sulfur	--	0.025
Chromium	0.80	1.10
Molybdenum	0.15	0.25
Nickel	--	0.25
Copper	--	0.35

- 3.1.1 Check Analysis: Composition variations shall meet the applicable requirements of AMS-2259.

- 3.2 Condition: The product shall be supplied in the following condition; hardness shall be determined in accordance with ASTM A 370:

- 3.2.1 Sheet and Strip: Cold finished, bright or atmosphere annealed, and descaled if necessary, having hardness not higher than 98 HRB, or equivalent.

- 3.2.2 Plate: Hot rolled, annealed if necessary, and descaled, having hardness not higher than 25 HRC, or equivalent.

- 3.3 Properties: The product shall conform to the following requirements; hardness, tensile, and bend testing shall be performed in accordance with ASTM A 370:

AMS-6350 Revision H

- 3.3.1 Response to Heat Treatment: Product 0.249 inch (6.32 mm) and under in nominal thickness and thicker product reduced to 0.249 inch $\pm$ 0.010 (6.32 mm $\pm$ 0.25) in thickness shall have tensile strength not lower than 125,000 psi (862 MPa) or hardness not lower than 26 HRC, or equivalent, after being hardened by quenching in oil from 1600°F $\pm$ 10 (871°C $\pm$ 6) and tempered for not less than 30 minutes at not lower than 900°F (482°C).
- 3.3.2 Grain Size: Predominantly 5 or finer with occasional grains as large as 2 permissible, determined in accordance with ASTM E 112.
- 3.3.3 Decarburization:
- 3.3.3.1 Product Under 0.045 Inch (1.14 mm) in Nominal Thickness: The method of test and the allowance shall be as agreed upon by purchaser and vendor.
- 3.3.3.2 Product 0.045 to 0.375 Inch (1.14 to 9.52 mm), Excl, in Nominal Thickness:
- 3.3.3.2.1 Specimens: Shall be the full thickness of the product except that specimens from plate 0.250 inch (6.35 mm) and over in nominal thickness shall be slices approximately 0.250 inch (6.35 mm) thick cut parallel to and preserving one original surface of the plate. Recommended specimen size is 1 x 4 inches (25 x 102 mm).
- 3.3.3.2.2 Procedure: Specimens shall be hardened by austenitizing and quenching; preferably, they shall not be tempered but, if tempered, the tempering temperature shall be not higher than 300°F (149°C). During heat treatment, specimens shall be protected by suitable atmosphere or medium or by suitable plating to prevent carburization or further decarburization. Protective plating, if used, shall then be removed from specimens of product 0.045 to 0.250 inch (1.14 - 6.35 mm), excl, in nominal thickness and a portion of the specimen shall be ground to a depth of 0.050 inch (1.27 mm) or one-half thickness, whichever is less. Specimens from product 0.250 to 0.375 inch (6.35 to 9.52 mm), excl, in nominal thickness shall be ground to remove 0.020 inch (0.51 mm) of metal from the original surface of the plate and a portion of the specimen shall be further ground to a depth of at least one-third the original thickness of the specimen. At least three Rockwell hardness readings shall be taken on each prepared step and each group of readings averaged.
- 3.3.3.2.3 Allowance:
- 3.3.3.2.3.1 Product 0.045 to 0.250 Inch (1.14 to 6.35 mm), Excl, in Nominal Thickness: The product shall show no layer of complete decarburization, determined microscopically at a magnification not exceeding 100X. It shall also be free from partial decarburization to the extent that the difference in hardness between the original surface and the portion ground as in 3.3.3.2.2 shall be not greater than two units on the Rockwell "A" scale.

AMS-6350 Revision H

3.3.3.2.3.2 Product 0.250 to 0.375 Inch (6.35 to 9.52 mm), Excl. in Nominal Thickness: Shall be free from decarburization to the extent that the difference in hardness between the two prepared steps shall be not greater than three units on the Rockwell "A" scale.

3.3.3.3 Product 0.375 Inch (9.52 mm) and Over in Nominal Thickness: The total decarburization, determined microscopically at a magnification not exceeding 100X on the as-supplied plate, shall be not greater than shown in Table I.

TABLE I

Nominal Wall Thickness Inches	Depth of Decarburization Inch
0.375 to 0.500, incl	0.015
Over 0.500 to 1.000, incl	0.025
Over 1.000 to 2.000, incl	0.035
Over 2.000	As agreed upon

TABLE I (SI)

Nominal Thickness Millimetres	Depth of Decarburization Millimetre
9.52 to 12.70, incl	0.38
Over 12.70 to 25.40, incl	0.64
Over 25.40 to 50.80, incl	0.89
Over 50.80	As agreed upon

3.3.4 Bending: The product shall withstand, without cracking, free bending through the angle shown below around a diameter equal to the nominal thickness of the product with axis of bend parallel to the direction of rolling:

Nominal Thickness		Angle
Inch	Millimetres	Deg, min
Up to 0.249, incl	Up to 6.32, incl	180
Over 0.249 to 0.749, incl	Over 6.32 to 19.02, incl	90

3.3.4.1 Bending requirements for plate over 0.749 inch (19.02 mm) in nominal thickness shall be as agreed upon by purchaser and vendor.

3.4 Quality:

3.4.1 Steel shall be aircraft quality conforming to AMS-2301.

AMS-6350 Revision H

3.4.2 The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.5 Tolerances: Shall conform to all applicable requirements of AMS-2252 or MAM-2252.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

4.2 Classification of Tests: Tests for all technical requirements are acceptance tests and shall be performed on each heat or lot as applicable.

4.3 Sampling and Testing: Shall be in accordance with AMS-2370.

4.4 Reports: The vendor of the product shall furnish with each shipment a report showing the results of tests on each heat for chemical composition, grain size, and frequency-severity cleanliness rating and the results of tests on each lot to determine conformance to the other technical requirements. This report shall include the purchase order number, lot number, AMS-6350H, size, and quantity.

4.5 Resampling and Retesting: Shall be in accordance with AMS-2370.

5. PREPARATION FOR DELIVERY:

5.1 Identification: The product shall be identified as in 5.1.1 unless purchaser permits a method from 5.1.2.

5.1.1 Each sheet, strip, and plate shall be legibly marked on one face, in the respective location indicated below, with AMS-6350H, lot number, manufacturer's identification, and nominal thickness. The characters shall be applied using a suitable marking fluid and shall be removable in hot alkaline cleaning solution without rubbing. The markings shall have no deleterious effect on the product or its performance and shall be sufficiently stable to withstand normal handling. The specification number, manufacturer's identification, and nominal thickness shall be continuously line marked; the lot number may be included in the line marking or may be marked at one location on each piece.

5.1.1.1 Flat Strip 6 Inches (152 mm) and Under in Width: Shall be marked in one or more lengthwise rows of characters recurring at intervals not greater than 3 feet (914 mm).