



AEROSPACE MATERIAL

Society of Automotive Engineers, Inc.

TWO PENNSYLVANIA PLAZA, NEW YORK, N.Y. 10001

SPECIFICATION

AMS 6358D

Superseding AMS 6358C

Issued 10-1-43

Revised 12-1-73

STEEL SHEET, STRIP, AND PLATE

0.50Cr - 0.55Ni - 0.25Mo (0.38 - 0.43C) (SAE 8740)

1. SCOPE:

1.1 Form: This specification covers an aircraft-quality, low-alloy steel in the form of sheet, strip, and plate.

1.2 Application: Primarily for heat treated parts requiring through-hardening to minimum tensile strength of 200,000 psi (1,379 MPa) in section thickness up to 0.375 in. (9.52 mm) and proportionately lower strength in heavier thicknesses.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from Society of Automotive Engineers, Inc., Two Pennsylvania Plaza, New York, New York 10001.

2.1.1 Aerospace Material Specifications:

AMS 2252 - Tolerances, Alloy Steel Sheet, Strip, and Plate

AMS 2259 - Chemical Check Analysis Limits, Wrought Low-Alloy and Carbon Steel

AMS 2301 - Aircraft Quality Steel Cleanliness, Magnetic Particle Inspection Procedure

AMS 2350 - Standards and Test Methods

AMS 2370 - Quality Assurance Sampling of Carbon and Low Alloy Steel, Wrought Products Except Forgings and Forging Stock

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, Pennsylvania 19103.

ASTM A370 - Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials

ASTM E112 - Estimating Average Grain Size of Metals

ASTM E350 - Chemical Analysis of Carbon Steel, Low-Alloy Steel, Silicon Electrical Steel, Ingot Iron, and Wrought Iron

2.3 Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, Pennsylvania 19120.

2.3.1 Federal Standards:

Federal Test Method Standards No. 151 - Metals; Test Methods

3. TECHNICAL REQUIREMENTS:

3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E350, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other approved analytical methods:

SAE Technical Board rules provide that: "All technical reports, including standards applications and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

	min	max
Carbon	0.38	0.43
Manganese	0.75	1.00
Silicon	0.20	0.35
Phosphorus	--	0.025
Sulfur	--	0.025
Chromium	0.40	0.60
Nickel	0.40	0.70
Molybdenum	0.20	0.30
Copper	--	0.35

- 3.1.1 Check Analysis: Composition variations shall meet the requirements of AMS 2259, paragraph titled "Low Alloy Steels".
- 3.2 Condition: The product shall be supplied in the following condition; hardness shall be determined in accordance with ASTM A370:
- 3.2.1 Sheet and Strip: Cold finished, bright or atmosphere annealed, and descaled if necessary, or hot rolled, annealed if necessary, and descaled. The product shall have hardness not higher than 98 HRB or equivalent.
- 3.2.2 Plate: Hot rolled, annealed if necessary, and descaled, having hardness not higher than 24 HRC or equivalent.
- 3.3 Properties: The product shall conform to the following requirements; hardness and bend testing shall be performed in accordance with ASTM A370:
- 3.3.1 Grain Size: Predominantly 5 or finer with occasional grains as large as 3 permissible, ASTM E112, McQuaid-Ehn test.
- 3.3.2 Decarburization:
- 3.3.2.1 Product Under 0.045 In. (1.14 mm) in Thickness: The method of test and the allowance shall be as agreed upon by purchaser and vendor.
- 3.3.2.2 Product 0.045 to 0.375 In. (1.14 to 9.52 mm), Excl, Thick:
- 3.3.2.2.1 Specimens: Shall be the full thickness of the product except that specimens from plate over 0.249 in. (6.32 mm) thick shall be slices approximately 0.250 in. (6.35 mm) thick cut parallel to and preserving one original surface of the plate. Recommended specimen size is 1 x 4 in. (25 x 102 mm).
- 3.3.2.2.2 Procedure: Specimens shall be hardened by austenitizing and quenching; preferably, they shall not be tempered but, if tempered, the tempering temperature shall be not higher than 300° F (149° C). During heat treatment, specimens shall be protected by suitable atmosphere or medium or by suitable plating to prevent carburization or further decarburization. Protective plating, if used, shall then be removed from specimens of product 0.045 to 0.250 in. (1.14 to 6.35 mm), excl, in thickness and a portion of the specimen shall be ground to a depth of 0.050 in. (1.27 mm) or one-half thickness, whichever is less. Specimens from product 0.250 to 0.375 in. (6.35 to 9.52 mm), excl, in thickness shall be ground to remove 0.020 in. (0.51 mm) of metal from the original surface of the plate and a portion of the specimen shall be further ground to a depth of at least one-third the original thickness of the specimen. At least three Rockwell hardness readings shall be taken on each prepared step and each group of readings averaged.

3.3.2.2.3 Allowance:

3.3.2.2.3.1 Product 0.045 to 0.250 In. (1.14 to 6.35 mm), Excl, Thick: The product shall show no layer of complete decarburization as determined microscopically at a magnification not exceeding 100X. It shall also be free from partial decarburization to the extent that the difference in hardness between the original surface and the portion ground as in 3.3.2.2.2 shall be not greater than 2 units on the Rockwell "A" scale.

3.3.2.2.3.2 Product 0.250 to 0.375 In. (6.35 to 9.52 mm), Excl, Thick: Shall be free from decarburization to the extent that the difference in hardness between the two prepared steps shall be not greater than 3 units on the Rockwell "A" scale.

3.3.2.3 Product 0.375 In. (9.52 mm) and Over in Thickness: The total decarburization as determined microscopically at a magnification not exceeding 100X on the plate, as supplied, shall be not greater than shown in Table I.

TABLE I

Nominal Thickness Inches	Depth of Decarburization Inch
0.375 to 0.500, incl	0.015
Over 0.500 to 1.000, incl	0.025
Over 1.000 to 2.000, incl	0.035
Over 2.000	As agreed upon

TABLE I (SI)

Nominal Thickness Millimeters	Depth of Decarburization Millimeters
9.52 to 12.70, incl	0.38
Over 12.70 to 25.40, incl	0.64
Over 25.40 to 50.80, incl	0.89
Over 50.80	As agreed upon

3.3.3 Bending: The product shall withstand, without cracking, free bending through the angle indicated in Table II around a diameter equal to the nominal thickness of the product with axis of bend parallel to the direction of rolling.

TABLE II

Nominal Thickness Inch	Bend Angle Deg
Up to 0.249	180
Over 0.249 to 0.749, incl	90

TABLE II (SI)

Nominal Thickness Millimeters	Bend Angle Rad
Up to 6.32, incl	3.14
Over 6.32 to 19.02, incl	1.57

3.4 Quality:

3.4.1 Steel shall be aircraft quality conforming to AMS 2301.

3.4.2 The product shall be uniform in quality and condition, clean, sound, and free from foreign materials and from internal and external imperfections detrimental to fabrication or to performance of parts.

3.5 Tolerances: Unless otherwise specified, tolerances shall conform to all applicable requirements of AMS 2252.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of the product shall supply all samples and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to perform such confirmatory testing as he deems necessary to assure that the product conforms to the requirements of this specification.

4.2 Classification of Tests: Tests to determine conformance to all technical requirements of this specification are classified as acceptance or routine control tests.

4.3 Sampling: Shall be in accordance with AMS 2370.

4.4 Reports:

4.4.1 The vendor of the product shall furnish with each shipment three copies of a report of the results of tests for chemical composition, grain size, and AMS 2301 frequency-severity rating for each heat in the shipment and the results of tests on each size from each heat to determine conformance to the hardness, bending, and decarburization requirements. This report shall include the purchase order number, heat number, material specification number and its revision letter, thickness, size, and quantity from each heat.

4.4.2 The vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, material specification number and its revision letter, contractor or other direct supplier of material, part number, and quantity. When material for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of material to determine conformance to the requirements of this specification, and shall include in the report a statement that the material conforms, or shall include copies of laboratory reports showing the results of tests to determine conformance.

4.5 Resampling and Retesting: If any specimen used in the above tests fails to meet the specified requirements, disposition of the product may be based on the results of testing three additional specimens for each original nonconforming specimen. Failure of any retest specimen to meet the specified requirements shall be cause for rejection of the product represented and no additional testing shall be permitted. Results of all tests shall be reported.

5. PREPARATION FOR DELIVERY:

5.1 Identification: Each sheet, strip, and plate shall be marked as in 5.1.1 unless purchaser permits a method from 5.1.2.

5.1.1 Each sheet, strip, and plate shall be marked on one face, in the respective location indicated below, with AMS 6358D, heat number, manufacturer's identification, and nominal thickness. The characters shall be of such size as to be clearly legible, shall be applied using a suitable marking fluid, and shall be capable of being removed in hot alkaline cleaning solution without rubbing. The markings shall have no deleterious effect on the material or its performance and shall be sufficiently stable to withstand normal handling. The specification number, manufacturer's identification, and nominal thickness shall be continuously line marked; the heat number may be included in the line marking or may be marked at one location on each piece.