



# AEROSPACE MATERIAL SPECIFICATIONS

SOCIETY OF AUTOMOTIVE ENGINEERS, Inc.

485 Lexington Ave., New York, N.Y. 10017

## AMS 6360E

Supersedes AMS 6360D

Issued 12-4-39

Revised 9-30-66

### STEEL TUBING, SEAMLESS 0.95Cr - 0.20Mo (0.28 - 0.33C) (SAE 4130)

1. **ACKNOWLEDGMENT:** A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. **APPLICATION:** Primarily for general use where welding and moderate tensile properties are required. Extensively used when minimum tensile strength of 160,000 psi is required.
3. **COMPOSITION:**

|            | min  | max   |
|------------|------|-------|
| Carbon     | 0.28 | 0.33  |
| Manganese  | 0.40 | 0.60  |
| Silicon    | 0.20 | 0.35  |
| Phosphorus | --   | 0.025 |
| Sulfur     | --   | 0.025 |
| Chromium   | 0.80 | 1.10  |
| Molybdenum | 0.15 | 0.25  |
| Nickel     | --   | 0.25  |
| Copper     | --   | 0.35  |

- 3.1 **Check Analysis:** Composition variations shall meet the requirements of the latest issue of AMS 2259, paragraph titled "Low Alloy Steels".

4. **CONDITION:** Normalized and tempered, stress relieved, or otherwise heat treated after the last cold drawing operation.

5. **TECHNICAL REQUIREMENTS:** When ASTM methods are specified for determining conformance to the following requirements, tests shall be conducted in accordance with the issue of the ASTM method listed in the latest issue of AMS 2350.

- 5.1 **Tensile Properties:**

| Nominal OD<br>Inch | Nominal Wall<br>Thickness<br>Inch | Tensile<br>Strength<br>psi, min | Yield Strength at 0.2% Offset<br>or at Extension Indicated<br>(E = 29,000,000) |                                         | Elongation<br>% in 2 In. |                    |
|--------------------|-----------------------------------|---------------------------------|--------------------------------------------------------------------------------|-----------------------------------------|--------------------------|--------------------|
|                    |                                   |                                 | psi, min                                                                       | Extension<br>Under Load<br>in. in 2 in. | min                      | Full<br>Tube Strip |
| Up to 0.500, excl  | Up to 0.188, incl                 | 95,000                          | 75,000                                                                         | 0.0092                                  | 10                       | -                  |
| Up to 0.500, excl  | Over 0.188                        | 90,000                          | 70,000                                                                         | 0.0088                                  | 10                       | -                  |
| 0.500 and over     | Up to 0.188, incl                 | 95,000                          | 75,000                                                                         | 0.0092                                  | 12                       | 7                  |
| 0.500 and over     | Over 0.188                        | 90,000                          | 70,000                                                                         | 0.0088                                  | 15                       | 10                 |

- 5.2 **Grain Size:** Predominantly 5 or finer with occasional grains as large as 3 permissible, ASTM E112, McQuaid-Ehn Test.

5.3 Decarburization:

- 5.3.1 Tubing ordered ground, turned, or polished shall be free from decarburization on the ground, turned, or polished surfaces. On other surfaces, decarburization shall not exceed the maximum depth specified in 5.3.3.
- 5.3.2 Allowable decarburization of pierced billets, or of tubing for redrawing, or of tubing ordered to specific microstructural requirements shall be as agreed upon by purchaser and vendor.
- 5.3.3 Decarburization of tubing to which 5.3.1 or 5.3.2 is not applicable shall be not greater than the following:

| Nominal Wall Thickness<br>Inch | Maximum Depth of Decarburization, Inch |         |                  |
|--------------------------------|----------------------------------------|---------|------------------|
|                                | Inside                                 | Outside | Inside + Outside |
| Up to 0.040, incl              | 0.008                                  | 0.008   | 0.010            |
| Over 0.040 to 0.050, incl      | 0.009                                  | 0.009   | 0.012            |
| Over 0.050 to 0.070, incl      | 0.010                                  | 0.010   | 0.014            |
| Over 0.070 to 0.080, incl      | 0.012                                  | 0.012   | 0.016            |
| Over 0.080 to 0.090, incl      | 0.014                                  | 0.014   | 0.018            |
| Over 0.090 to 0.100, incl      | 0.015                                  | 0.015   | 0.020            |
| Over 0.100 to 0.150, incl      | 0.017                                  | 0.017   | 0.022            |
| Over 0.150 to 0.200, incl      | 0.020                                  | 0.020   | 0.026            |

- 5.3.4 Unless otherwise agreed upon by purchaser and vendor, decarburization shall be measured by the microscopic method or by Rockwell Superficial 30-N scale hardness method, or equivalent hardness testing method, on hardened but untempered specimens protected during heat treatment to prevent changes in surface carbon content. Depth of decarburization, when measured by a hardness method, is defined as the perpendicular distance from the surface to the nondecarburized depth under that surface below which there is no further increase in hardness. Such measurements shall be far enough away from any adjacent surface to be uninfluenced by any decarburization or lack of decarburization thereon.
- 5.3.4.1 When determining the depth of decarburization, it is permissible to disregard local areas provided the decarburization of such areas does not exceed the limits above by more than 0.005 in. and the width is 0.065 in. or less.
6. QUALITY: Steel shall be aircraft quality and shall conform to the latest issue of AMS 2301. Tubing shall be uniform in quality and condition, shall have a good workmanlike finish conforming to the best practice for high quality material, and shall be suitable for use in parts required to pass magnetic particle inspection either with or without machining of the surface. It shall be smooth, clean, and free from heavy scale or oxide, burrs, seams, tears, grooves, laminations, slivers, pits, and other injurious conditions. Surface imperfections such as handling marks, straightening marks, light mandrel and die marks, shallow pits and scale pattern will not be considered injurious if the imperfections are removable within the tolerances specified for diameter and wall thickness. The removal of surface imperfections is not required.
7. TOLERANCES: Unless otherwise specified, tolerances shall conform to all applicable requirements of the latest issue of AMS 2253.
8. REPORTS:
- 8.1 Unless otherwise specified, the vendor of the product shall furnish with each shipment three copies of a report of the results of tests for chemical composition, hardenability, grain size, and AMS 2301 frequency-severity rating of each heat in the shipment. This report shall include the purchase order number, heat number, material specification number, size, and quantity from each heat.