

AEROSPACE MATERIAL SPECIFICATION


AMS 6418G

Submitted for recognition as an American National Standard

Issued 15 JUN 1950
Revised 1 OCT 1992
Superseding AMS 6418F

STEEL BARS, FORGINGS, TUBING, AND RINGS
1.3Mn - 1.5Si - 0.30 Cr - 1.8Ni - 0.40Mo (0.23 - 0.28C)

This specification has been declared "NONCURRENT" by the Aerospace Materials Division, SAE, as of April, 1992. It is recommended, therefore, that this specification not be specified for new designs.

This cover sheet should be attached to the "F" revision of the subject specification.

"NONCURRENT" refers to those materials which have previously been widely used and which may be required on some existing designs in the future. The Aerospace Materials Division, however, does not recommend these as standard materials for future use in new designs. Each of these "NONCURRENT" specifications is available from SAE upon request.

PREPARED UNDER THE JURISDICTION OF AMS COMMITTEE "E".

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

AN AMERICAN NATIONAL STANDARD

SAE The Engineering Society
For Advancing Mobility
Land Sea Air and Space®
INTERNATIONAL
400 Commonwealth Drive, Warrendale, PA 15096-0001

**AEROSPACE
MATERIAL
SPECIFICATION**

AMS 6418F
Superseding AMS 6418E

Issued 6-15-50
Revised 10-1-84

STEEL BARS, FORGINGS, TUBING, AND RINGS
1.3Mn - 1.5Si - 0.30Cr - 1.8Ni - 0.40Mo (0.23 - 0.28C)

UNS K32550

1. SCOPE:

1.1 Form: This specification covers an aircraft-quality, low-alloy steel in the form of bars, forgings, mechanical tubing, flash welded rings, and stock for forging and flash welded rings.

1.2 Application: Primarily for parts requiring high tensile strength and good ductility with relatively high impact strength and hardness.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications and Aerospace Standards shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

AMS 6418F

2.1.1 Aerospace Material Specifications:

- AMS 2251 - Tolerances, Low-Alloy Steel Bars
- MAM 2251 - Tolerances, Metric, Low-Alloy Steel Bars
- AMS 2253 - Tolerances, Carbon and Alloy Steel Tubing
- MAM 2253 - Tolerances, Metric, Carbon and Alloy Steel Tubing
- AMS 2259 - Chemical Check Analysis Limits, Wrought Low-Alloy and Carbon Steels
- AMS 2301 - Aircraft Quality Steel Cleanliness, Magnetic Particle Inspection Procedure
- AMS 2310 - Qualification Sampling of Steels, Transverse Tensile Properties
- AMS 2350 - Standards and Test Methods
- AMS 2370 - Quality Assurance Sampling of Carbon and Low-Alloy Steels, Wrought Products Except Forgings and Forging Stock
- AMS 2372 - Quality Assurance Sampling of Carbon and Low-Alloy Steels, Forgings and Forging Stock
- AMS 2375 - Control of Forgings Requiring First Article Approval
- AMS 2806 - Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Heat and Corrosion Resistant Steels and Alloys
- AMS 2808 - Identification, Forgings
- AMS 7496 - Rings, Flash Welded, Carbon and Low-Alloy Steels

2.1.2 Aerospace Standards:

- AS 1182 - Standard Machining Allowance, Aircraft Quality and Premium Quality Steel Products

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

- ASTM A255 - End-Quench Test for Hardenability of Steel
- ASTM A370 - Mechanical Testing of Steel Products
- ASTM E23 - Notched Bar Impact Testing of Metallic Materials
- ASTM E112 - Determining Average Grain Size
- ASTM E350 - Chemical Analysis of Carbon Steel, Low-Alloy Steel, Silicon Electrical Steel, Ingot Iron, and Wrought Iron
- ASTM E381 - Macroetch Testing, Inspection, and Rating Steel Products, Comprising Bars, Billets, Blooms, and Forgings

2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Federal Standards:

- Federal Test Method Standard No. 151 - Metals; Test Methods

2.3.2 Military Standards:

- MIL-STD-163 - Steel Mill Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

- 3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E350, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other analytical methods approved by purchaser:

	min	max
Carbon	0.23	0.28
Manganese	1.20	1.50
Silicon	1.30	1.70
Phosphorus	- -	0.025
Sulfur	- -	0.025
Chromium	0.20	0.40
Nickel	1.65	2.00
Molybdenum	0.35	0.45
Copper	-	0.35

- 3.1.1 Check Analysis: Composition variations shall meet the applicable requirements of AMS 2259.

- 3.2 Condition: Unless otherwise specified, the product shall be supplied in the following condition; hardness and tensile strength shall be determined in accordance with ASTM A370:

3.2.1 Bars:

- 3.2.1.1 Bars 0.500 in. (12.50 mm) and Under in Nominal Diameter or Distance Between Parallel Sides: Cold finished having tensile strength not higher than 145,000 psi (1000 PMA) or equivalent hardness.

- 3.2.1.2 Bars Over 0.500 In. (12.50 mm) in Nominal Diameter or Distance Between Parallel Sides: Hot finished having hardness not higher than 293 HB or equivalent except that bars ordered cold finished may have hardness as high as 302 HB or equivalent.

3.2.2 Forgings and Flash Welded Rings: As ordered.

- 3.2.2.1 Flash welded rings shall not be supplied unless specified or permitted on purchaser's part drawing. When supplied, they shall be manufactured in accordance with AMS 7496.

- 3.2.3 Mechanical Tubing: Cold finished having hardness not higher than 32 HRC or equivalent except that tubing ordered hot finished shall have hardness not higher than 31 HRC or equivalent.

- 3.2.4 Stock for Forging or Flash Welded Rings: As ordered by the forging or flash welded ring manufacturer.

3.3 Properties: The product shall conform to the following requirements; hardness testing shall be performed in accordance with ASTM A370:

3.3.1 Macrostructure: Visual examination of transverse sections as in 4.3.4
 Ø from bars, billets, tube rounds or tubes, and stock for forging or flash welded rings, etched in accordance with ASTM E381 in hot hydrochloric acid (1:1) at 160° - 180°F (70° - 80°C) for sufficient time to develop a well-defined macrostructure, shall show no pipe or cracks. Except as specified in 3.3.1.1 porosity, segregation, inclusions, and other imperfections shall be no worse than the following macrographs of ASTM E381:

Section Size		Macrographs
Square Inches	(Square Centimetres)	
Up to 36, incl	(Up to 230, incl)	S2 - R1 - C2
Over 36 to 100, incl	(Over 230 to 645, incl)	S2 - R2 - C3
Over 100	(Over 645)	As agreed upon

3.3.1.1 If tubes are produced directly from ingots or large blooms, transverse
 Ø sections may be taken from tubes rather than tube rounds.
 Macrostructure standards for such tubes shall be as agreed upon by purchaser and vendor.

3.3.2 Grain Size: Predominantly 5 or finer with occasional grains as large as 3 permissible, determined in accordance with ASTM E112 on specimens cooled from the carburizing temperature to 1300°F ± 25 (705°C ± 15) and held for 60 min. ± 5 before cooling to room temperature.

3.3.3 Hardenability: Shall be J45=24 min, determined on the standard end-quench
 Ø test specimen in accordance with ASTM A255 except that the steel shall be normalized at 1725°F ± 25 (940°C ± 15) and the test specimen austenitized at 1600°F ± 25 (870°C ± 15). The hardenability test is not required on a product which will not yield a suitable specimen but the steel from which the product is made shall conform to the hardenability specified.

3.3.4 Decarburization:

3.3.4.1 Bars, tubing, and flash welded rings ordered ground, turned, or polished shall be free from decarburization on the ground, turned, or polished surfaces. Decarburization on tubing ID shall not exceed the maximum depth specified in Table II.

3.3.4.2 Allowable decarburization of bars, billets, and tube rounds ordered for redrawing, forging, or flash welding or to specified microstructural requirements shall be as agreed upon by purchaser and vendor.

- 3.3.4.3 Decarburization of bars and flash welded rings to which 3.3.4.1 or 3.3.4.2 is not applicable shall be not greater than shown in Table I.

TABLE I

Nominal Diameter or Distance Between Parallel Sides Inches	Depth of Decarburization Inch
Up to 0.375, incl	0.010
Over 0.375 to 0.500, incl	0.012
Over 0.500 to 0.625, incl	0.014
Over 0.625 to 1.000, incl	0.017
Over 1.000 to 1.500, incl	0.020
Over 1.500 to 2.000, incl	0.025
Over 2.000 to 2.500, incl	0.030
Over 2.500 to 3.000, incl	0.035
Over 3.000 to 4.000, incl	0.045

TABLE I (SI)

Nominal Diameter or Distance Between Parallel Sides Millimetres	Depth of Decarburization Millimetres
Up to 9.50, incl	0.25
Over 9.50 to 12.50, incl	0.30
Over 12.50 to 15.75, incl	0.35
Over 15.75 to 25.00, incl	0.42
Over 25.00 to 37.50, incl	0.50
Over 37.50 to 50.00, incl	0.62
Over 50.00 to 62.50, incl	0.75
Over 62.50 to 75.00, incl	0.88
Over 75.00 to 100.00, incl	1.12

- 3.3.4.3.1 Limits for depth of decarburization of bars and ring cross-sections over 4.000 in (100.00 mm) in nominal diameter or distance between parallel sides shall be as agreed upon by purchaser and vendor.

- 3.3.4.4 Decarburization of tubing to which 3.3.4.1 or 3.3.4.2 is not applicable shall be not greater than shown in Table II.

TABLE II

Nominal Wall Thickness Inches	<u>Depth of Decarburization, Inch</u>	
	ID	OD
Up to 0.109, incl	0.008	0.015
Over 0.109 to 0.203, incl	0.010	0.020
Over 0.203 to 0.400, incl	0.012	0.025
Over 0.400 to 0.600, incl	0.015	0.030
Over 0.600 to 1.000, incl	0.017	0.035
Over 1.000	0.020	0.040

TABLE II (SI)

Nominal Wall Thickness Millimetres	<u>Depth of Decarburization, Millimetres</u>	
	ID	OD
Up to 2.75, incl	0.20	0.38
Over 2.75 to 5.00, incl	0.25	0.50
Over 5.00 to 10.00, incl	0.30	0.62
Over 10.00 to 15.00, incl	0.38	0.75
Over 15.00 to 25.00, incl	0.42	0.88
Over 25.00	0.50	1.00

- 3.3.4.5 Decarburization shall be measured by the microscopic method or by Rockwell Superficial 30-N scale or equivalent hardness testing method on hardened but untempered specimens protected during heat treatment to prevent changes in surface carbon content. Depth of decarburization, when measured by a hardness method, is defined as the perpendicular distance from the surface to the depth under that surface below which there is no further increase in hardness. Such measurements shall be far enough away from any adjacent surface to be uninfluenced by any decarburization or lack of decarburization thereon.

- 3.3.4.5.1 When determining the depth of decarburization, it is permissible to disregard local areas provided the decarburization of such areas does not exceed the above limits by more than 0.005 in. (0.12 mm) and the width is 0.065 in. (1.65 mm) or less.

- 3.3.5 Properties After Heat Treatment: Product 2.50 in. (62.5 mm) and over in nominal diameter or distance between parallel sides shall have transverse tensile properties as specified in 3.3.5.1 after being heat treated as follows:

Normalize by heating to 1725°F ± 25 (940°C ± 15), holding at heat for 60 min. ± 10, and cooling in air.

Harden by heating to 1600°F ± 25 (870°C ± 15), holding at heat for 60 min. ± 10, and quenching in oil at 120° - 140°F (50° - 60°C).

Temper by heating to 550°F ± 25 (290°C ± 15), holding at heat for 2 - 3 hr, and cooling in air.

- 3.3.5.1 Tensile Properties: Shall meet the following requirements, determined on test specimens prepared in accordance with AMS 2310 and heat treated as in 3.3.5:

Tensile Strength	220,000 - 245,000 psi (1515 - 1690 MPa)
Yield Strength at 0.2% Offset, min	185,000 psi (1275 MPa)
Elongation in 4D, min	5%
Reduction of Area, min	
Average	20%
Individual	15%

3.4 Quality:

- 3.4.1 Steel shall be aircraft quality conforming to AMS 2301.

- 3.4.2 The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and free from imperfections detrimental to usage of the product.

- 3.4.2.1 Bars, tubing, and flash welded rings ordered ground, turned, or polished shall be free from seams, laps, tears, and cracks open to the ground, turned or polished surfaces.

- 3.4.2.2 Product ordered to surface conditions other than ground, turned, or polished shall, after removal of the standard machining allowance, be free from seams, laps, tears, cracks, and other defects exposed to the machined surfaces. Standard machining allowance shall be in accordance with AS 1182.

- 3.5 Sizes: Except when exact lengths or multiples of exact lengths are ordered, straight bars and tubing will be acceptable in mill lengths of 6 - 20 ft (2 - 6 m) but not more than 10% of any shipment shall be supplied in lengths shorter than 10 ft (3 m).

- 3.6 Tolerances: Unless otherwise specified, tolerances shall conform to all applicable requirements of the following: