



AEROSPACE MATERIAL

Society of Automotive Engineers, Inc. SPECIFICATION

400 COMMONWEALTH DRIVE, WARRENDALE, PA. 15096

AMS 6468

Issued 4-15-78

Revised

STEEL WIRE, WELDING

1.0Cr - 10Ni - 3.8Co - 0.45Mo - 0.08V (0.14 - 0.17C)

Vacuum Melted, Environment Controlled

1. SCOPE:

1.1 Form: This specification covers a premium-quality, low-alloy steel in the form of welding wire.

1.2 Application: Primarily for use as filler metal for gas-tungsten-arc and gas-metal-arc welding of low-alloy steels having composition similar to that of this wire and requiring a combination of high strength and high notch toughness without the need for post-weld heat treatment.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2259 - Chemical Check Analysis Limits, Wrought Low-Alloy and Carbon Steels

AMS 2350 - Standards and Test Methods

AMS 2370 - Quality Assurance Sampling of Carbon and Low-Alloy Steels, Wrought Products
Except Forgings and Forging Stock

AMS 2635 - Radiographic Inspection

AMS 2814 - Packaging, Welding Wire, Premium Quality

AMS 2815 - Identification, Welding Wire, Line Code System

AMS 6523 - Steel Sheet, Strip, and Plate, 0.75Cr - 9.0Ni - 4.5Co - 1.0Mo - 0.09V
(0.17 - 0.23C), Premium Quality, Consumable Electrode Melted, Annealed

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM E350 - Chemical Analysis of Carbon Steel, Low-Alloy Steel, Silicon Electrical Steel,
Ingot Iron, and Wrought Iron

ASTM E399 - Plane-Strain Fracture Toughness of Metallic Materials

2.3 Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Federal Standards:

Federal Test Method Standard No. 151 - Metals; Test Methods

2.3.2 Military Specifications:

MIL-W-10430 - Welding Rods and Electrodes, Preparation for Delivery of

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against infringement of patents."

3. TECHNICAL REQUIREMENTS:

- 3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E350, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other analytical methods approved by purchaser:

	min	max	Target Maxima
Carbon	0.14 -	0.17	--
Manganese	0.40 -	0.55	--
Silicon	0.15 -	0.25	--
Phosphorus	--	0.008	0.006
Sulfur	--	0.008	0.005
Chromium	0.90 -	1.05	--
Nickel	9.75 -	10.25	--
Cobalt	3.50 -	4.00	--
Molybdenum	0.40 -	0.50	--
Vanadium	0.06 -	0.10	--
Copper	--	0.10	--
Oxygen	--	0.0050 (50 ppm)	25 ppm
Nitrogen	--	0.0080 (80 ppm)	50 ppm
Hydrogen	--	0.0010 (10 ppm)	5 ppm

- 3.1.1 Check Analysis: Composition variations shall meet the applicable requirements of AMS 2259. No variation is permitted for oxygen, nitrogen, and hydrogen.
- 3.2 Condition: Cold drawn, bright finish, as-drawn temper. Wire shall be furnished on disposable spools for machine welding and in cut lengths for manual welding, as ordered. Surface roughness of spooled wire shall be as agreed upon by purchaser and vendor.
- 3.2.1 Drawing compounds, oxides, and dirt shall be removed by cleaning processes which will neither result in pitting nor cause gas absorption by the wire or deposition of substances harmful to welding operations.
- 3.2.2 Residual elements and dissolved gasses deposited on, or absorbed by, the welding wire as a result of cleaning or drawing operations shall be removed by vacuum degassing. Annealing, if required, shall be performed in vacuum or inert gas atmosphere.
- 3.2.3 Environment shall be controlled during manufacture, shipping, and storage so as to prevent contamination or corrosion of the wire and to help maintain target maxima limits as in 3.1.
- 3.3 Properties: Wire shall conform to the following requirements:
- 3.3.1 Weldability: Melted wire shall flow smoothly and evenly during welding and shall produce acceptable welds, determined by a procedure agreed upon by purchaser and vendor.
- 3.3.2 Spooled Wire: Shall conform to the following, unless otherwise agreed upon by purchaser and vendor:
- 3.3.2.1 Cast: Wire shall have imparted to it a curvature such that a specimen sufficient in length to form one loop, when cut from the spool and laid on a flat surface, shall form a circle not less than 15 in. (380 mm) and not greater than 30 in. (760 mm) in diameter.
- 3.3.2.2 Helix: The specimen on which cast was determined, when laid on a flat surface and measured between adjacent turns, shall show a vertical separation not greater than 1 in. (25 mm).

3.3.3 **Fracture-Toughness:** When specified by purchaser, or when composition (3.1) is in excess of target maximum for any element, test specimens prepared as in 4.3.2.1 shall be subjected to fracture-toughness testing. The method of testing and standards for acceptance shall be as agreed upon by purchaser and vendor. ASTM E399, using the Compact Tension Specimen, is a suggested method of testing.

3.4 **Quality:**

3.4.1 Steel shall be vacuum induction melted; it may be remelted using vacuum consumable electrode process, but remelting is not required.

3.4.2 Wire shall be uniform in quality and condition, sound, and free from foreign materials and from internal and external imperfections detrimental to welding operations, operation of welding equipment, or properties of the deposited weld metal.

3.5 **Sizes and Tolerances:** Unless otherwise specified, wire shall be supplied in the sizes and to the tolerances shown in 3.5.1 and 3.5.2.

3.5.1 **Diameter:**

TABLE I

Form	Nominal Diameter Inch	Tolerance Inch	
		plus	minus
Cut Lengths	0.030, 0.045, 0.062, 0.078, 0.093, 0.125	0.003	0.003
Spools	0.062, 0.078, 0.093	0.002	0.002
Spools	0.030, 0.035, 0.045	0.001	0.002
Spools	0.020	0.0005	0.0005

TABLE I (SI)

Form	Nominal Diameter Millimetres	Tolerance Millimetre	
		plus	minus
Cut Lengths	0.76, 1.14, 1.57, 1.98, 2.36, 3.18	0.08	0.08
Spools	1.57, 1.98, 2.36	0.05	0.05
Spools	0.76, 0.89, 1.14	0.03	0.05
Spools	0.51	0.013	0.013

3.5.2 **Length:** Cut lengths shall be furnished in 18, 27, or 36 in. (455, 685, or 915 mm) lengths, as ordered, and shall not vary more than +0, -0.5 in. (-13 mm) from the length ordered.

4. **QUALITY ASSURANCE PROVISIONS:**

4.1 **Responsibility for Inspection:** The vendor of wire shall supply all samples and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.5. Purchaser reserves the right to perform such confirmatory testing as he deems necessary to ensure that the wire conforms to the requirements of this specification.

4.2 **Classification of Tests:**

4.2.1 **Acceptance Tests:** Tests to determine conformance to composition (3.1) and tolerance (3.5) requirements are classified as acceptance tests and shall be performed on each heat of wire.

- 4.2.2 Periodic Tests: Tests to determine conformance to weldability (3.3.1), cast (3.3.2.1), helix (3.3.2.2), and, when specified by purchaser, fracture-toughness (3.3.3) requirements are classified as periodic tests shall be performed on the wire at a frequency agreed upon by purchaser and vendor.
- 4.2.3 Preproduction Tests: Tests to determine conformance to all technical requirements of this specification are classified as preproduction tests and shall be performed on the initial shipment of wire supplied and after each change for which reapproval as in 4.4.2 is required.
- 4.2.3.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, the contracting officer, or the request for procurement.
- 4.3 Sampling: Shall be in accordance with the following:
- 4.3.1 Acceptance Tests: AMS 2370.
- 4.3.2 Periodic Tests and Preproduction Tests: As agreed upon by purchaser and vendor and as follows:
- 4.3.2.1 Specimens for Fracture Toughness Testing: A double-vee-groove, butt-joint weld shall be made between two pieces of AMS 6523 steel plate, 1.00 - 1.25 in. (25 - 32 mm) in thickness, which have been chamfered full depth to a 60 deg included angle; the weld shall be perpendicular to the longitudinal grain direction of the test pieces. The weld metal shall be finished flush with the parent metal on both faces. The weld area in the location from which the test specimens are machined shall be free from defects detrimental to properties of the weld, determined by radiographic inspection in accordance with AMS 2635. The number and configuration of test specimens for fracture toughness testing shall be as agreed upon by purchaser and vendor.
- 4.4 Approval:
- 4.4.1 Sample wire shall be approved by purchaser before wire for production use is supplied, unless such approval be waived. Results of tests on production wire shall be essentially equivalent to those on the approved sample.
- 4.4.2 Vendor shall use materials, manufacturing procedures and processes, and methods of inspection on production wire which are essentially the same as those used on the approved sample wire. If any change is necessary in materials or in manufacturing procedures and processes, vendor shall submit for reapproval a statement of the proposed changes in material and processing and, when requested by purchaser, sample wire. Production wire made by the revised procedure shall not be shipped prior to receipt of reapproval.
- 4.5 Reports:
- 4.5.1 The vendor of wire shall furnish with each shipment three copies of a report showing the results of tests for chemical composition of each heat and stating that the wire conforms to the other technical requirements of this specification. This report shall include the purchase order number, heat number, material specification number, nominal size, and quantity from each heat.
- 4.5.2 When parts made of this wire or assemblies requiring use of this welding wire are supplied, the part or assembly manufacturer shall inspect each lot of wire to determine conformance to the requirements of this specification and shall furnish with each shipment three copies of a report stating that the wire conforms. This report shall include the purchase order number, material specification number, part or assembly number, and quantity.
- 4.6 Resampling and Retesting: Shall be in accordance with AMS 2370.
5. PREPARATION FOR DELIVERY: