



AEROSPACE MATERIAL SPECIFICATION

AMS6493**REV. A**Issued 2009-09
Revised 2013-11

Superseding AMS6493

Steel Bars, Forgings, and Tubing
1.0Cr - 3.25Ni - 0.40Mo (0.17 - 0.22C)
Electroslag Remelted or Consumable Electrode Vacuum Remelted
Premium Aircraft-Quality
(Composition similar to UNS K41910)

RATIONALE

AMS6493A results from a Five Year Review and update of this specification.

1. SCOPE

1.1 Form

This specification covers a premium aircraft-quality, low-alloy steel in the form of bars, forgings, mechanical tubing, and forging stock.

1.2 Application

These products have been used typically for carburized parts requiring high minimum core hardness with a narrow range, reduced distortion and subject to stringent magnetic particle inspection standards, but usage is not limited to such applications.

1.3 Classification

Steel covered by this specification is classified by melting practice as follows:

Type 1 Electroslag remelted (ESR)

Type 2 Consumable electrode vacuum remelted (VAR)

1.3.1 Unless a specific type is ordered, either type may be supplied.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2013 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

**SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS6493A>**

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or 724-776-4970 (outside USA), www.sae.org.

AMS2251	Tolerances, Low-Alloy Steel Bars
AMS2253	Tolerances, Carbon and Alloy Steel Tubing
AMS2259	Chemical Check Analysis Limits, Wrought Low-Alloy and Carbon Steels
AMS2300	Steel Cleanliness, Premium Aircraft-Quality, Magnetic Particle Inspection Procedure
AMS2370	Quality Assurance Sampling and Testing, Carbon and Low-Alloy Steel Wrought Products and Forging Stock
AMS2372	Quality Assurance Sampling and Testing, Carbon and Low-Alloy Steel, Forgings
AMS2806	Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Corrosion and Heat-Resistant Steels and Alloys
AMS2808	Identification, Forgings
AS1182	Standard Stock Removal Allowance, Aircraft-Quality and Premium Aircraft-Quality Steel Bars and Mechanical Tubing

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P. O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM A 255	Determining Hardenability of Steel
ASTM A 370	Mechanical Testing of Steel Products
ASTM A 604	Macroetch Testing of Consumable Electrode Remelted Steel Bars and Billets
ASTM E 112	Determining Average Grain Size
ASTM E 350	Chemical Analysis of Carbon Steel, Low-Alloy Steel, Silicon Electrical Steel, Ingot Iron, and Wrought Iron
ASTM E 384	Knoop and Vickers Hardness of Materials

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the following percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 350, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 – COMPOSITION

Element	min	max
Carbon	0.17	0.22
Manganese	0.30	0.60
Silicon	--	0.40
Phosphorus	--	0.020
Sulfur	--	0.015
Chromium	0.80	1.20
Nickel	3.00	3.50
Molybdenum	0.30	0.60

3.1.1 Check Analysis

Composition variations shall meet the applicable requirements of AMS2259.

3.2 Melting Practice

Steel shall be multiple melted using either electroslog remelt practice (ESR) or vacuum arc consumable electrode practice (VAR) in the remelt cycle (See 1.3).

3.3 Condition

The product shall be supplied in the following condition; hardness and tensile strength shall be determined in accordance with ASTM A 370:

3.3.1 Bars

3.3.1.1 Bars 0.500 inch (12.70 mm) and Under in Nominal Diameter or Least Distance Between Parallel Sides

Cold finished having tensile strength not higher than 138 ksi (950 MPa) or hardness not higher than 285 HB or equivalent (See 8.2).

3.3.1.2 Bars over 0.500 inch (12.70 mm) in Nominal Diameter or Least Distance Between Parallel Sides

Hot finished and annealed, unless otherwise ordered, having hardness not higher than 285 HB or equivalent (See 8.2). Bars ordered cold finished may have hardness as high as 310 HB or equivalent (See 8.2).

3.3.1.3 Bars shall not be cut from plate.

3.3.2 Forgings

As ordered.

3.3.3 Mechanical Tubing

Cold finished, unless otherwise ordered, having hardness not higher than 285 HB, or equivalent (See 8.2). Tubing ordered hot finished and annealed or tempered shall have hardness not higher than 285 HB or equivalent (See 8.2).

3.3.4 Forging Stock

As ordered by the forging manufacturer.

3.4 Properties

The product shall conform to the following requirements; hardness, tensile, and impact testing shall be performed in accordance with ASTM A 370:

3.4.1 Macrostructure

Visual examination of transverse full cross-sections from bars, billets, tube rounds, and forging stock, etched in hot hydrochloric acid in accordance with ASTM A 604, shall show no pipe or cracks. Porosity, segregation, inclusions, and other imperfections shall be no worse than the macrographs of ASTM A 604 shown in Table 2.

TABLE 2 – MACROSTRUCTURE LIMITS

Class	Condition	Severity
1	Freckles	A
2	White Spots	A
3	Radial Segregation	B
4	Ring Pattern	B

3.4.2 Average Grain Size

Shall be ASTM No. 5 or finer determined in accordance with ASTM E 112.

3.4.3 Response to Heat Treatment

3.4.3.1 Bars, Forgings and Mechanical Tubing

Specimens from product shall have the properties shown in Table 3 after being austenitized by heating to $1515^{\circ}\text{F} \pm 25$ ($824^{\circ}\text{C} \pm 14$), holding at heat for a time commensurate with section thickness, heating equipment, and procedure used, oil quenched to below 90°F (32°C) followed by tempering for 2 hours minimum at $285^{\circ}\text{F} \pm 10$ ($141^{\circ}\text{C} \pm 6$).

TABLE 3 – MINIMUM LONGITUDINAL MECHANICAL PROPERTIES

PROPERTY	VALUE
Tensile Strength	196 ksi (1350 MPa)
Yield Strength 0.2%	152 ksi (1050 MPa)
Elongation in 4D	11%
Charpy V-notch	44 ft-lb (60 J)

3.4.3.2 Forging Stock

When a sample of stock is forged to a test coupon and heat treated as in 3.4.3.1, specimens taken from the heat treated coupon shall conform to the requirements of 3.4.3.1. If specimens taken from the stock after heat treatment as in 3.4.3.1 conform to the requirements of 3.4.3.1, tests shall be accepted as equivalent to tests of a forged coupon.

3.5 Quality

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.5.1 Steel shall be premium aircraft-quality conforming to AMS2300.

3.5.2 Product ordered hot finished or cold finished or ground, turned, or polished shall, after removal of the standard stock removal allowance in accordance with AS1182, be free from seams, laps, tears, and cracks open to the machined, ground, turned, or polished surface.

3.5.3 Grain flow of die forgings, except in areas that contain flash-line end grain, shall follow the general contour of the forgings showing no evidence of reentrant grain flow.

3.6 Tolerances

3.6.1 Bars

In accordance with AMS2251.

3.6.2 Mechanical Tubing

In accordance with AMS2253.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.

4.2 Classification of Tests

4.2.1 Acceptance Tests

Composition (3.1), condition (3.3), macrostructure (3.4.1), average grain size (3.4.2), response to heat treatment (3.4.3.1), and tolerances (3.6) are acceptance tests and shall be performed on each heat or lot as applicable.

4.2.2 Periodic Tests

Frequency-severity cleanliness rating (3.5.1), grain flow of die forgings (3.5.3) and response to heat treatment of forging stock (3.4.3.2) are periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.3 Sampling and Testing

4.3.1 Bars, Mechanical Tubing, and Forging Stock

In accordance with AMS2370.

4.3.2 Forgings

In accordance with AMS2372.

4.4 Reports

4.4.1 The producer of bars, forgings, and tubing shall furnish with each shipment a report showing the producer identity and country where the metal was melted (i.e., final melt in the case of metal processed by multiple melting operations) and the results of tests for composition, macrostructure of each heat, and for condition, average grain size, and response to heat treatment of each lot, and stating that the product conforms to the other technical requirements. This report shall include the purchase order number, heat and lot numbers, AMS6493A, melt practice, product form and size or part number, and quantity. If forgings are supplied, the size and melt source of stock used to make the forgings shall also be included.

4.4.2 Report the nominal metallurgically worked cross sectional size and the cut size, if different (See 3.3.1.3).

4.4.3 The producer of forging stock shall furnish with each shipment a report showing the producer identity and country where the metal was melted (e. g., final melt in the case of metal processed by multiple melting operations) and the composition and macrostructure of each heat. This report shall include the purchase order number, heat number, AMS6493A, size and quantity.

4.5 Resampling and Retesting

4.5.1 Bars, Mechanical Tubing, and Forging Stock

In accordance with AMS2370.