

**AEROSPACE
MATERIAL
SPECIFICATION**

AMS 6512B

Superseding AMS 6512A

Issued 5-1-70

Revised 7-1-85

STEEL BARS, FORGINGS, TUBING, AND RINGS
18Ni - 7.8Co - 4.9Mo - 0.40Ti - 0.10Al
Vacuum Consumable Electrode Melted, Annealed

UNS K92890

1. SCOPE:

1.1 Form: This specification covers a premium aircraft quality, maraging alloy steel in the form of bars, forgings, mechanical tubing, flash welded rings, and stock for forging or flash welded rings.

1.2 Application: Primarily for parts, such as pressure vessels, requiring through hardening, without quenching, to a minimum yield strength of 240,000 psi (1655 MPa) and where such parts may require welding during fabrication.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications and Aerospace Standards shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

AMS 6512B

2.1.1 Aerospace Material Specifications:

AMS 2248 - Chemical Check Analysis Limits, Wrought Corrosion and Heat Resistant Steels and Alloys, Maraging and Other Highly-Alloyed Steels, and Iron Alloys
AMS 2251 - Tolerances, Low-Alloy Steel Bars
MAM 2251 - Tolerances, Metric, Low-Alloy Steel Bars
AMS 2253 - Tolerances, Carbon and Alloy Steel Tubing
MAM 2253 - Tolerances, Metric, Carbon and Alloy Steel Tubing
AMS 2300 - Premium Aircraft-Quality Steel Cleanliness, Magnetic Particle Inspection Procedure
MAM 2300 - Premium Aircraft-Quality Steel Cleanliness, Magnetic Particle Inspection Procedure, Metric (SI) Measurement
AMS 2350 - Standards and Test Methods
AMS 2370 - Quality Assurance Sampling of Carbon and Low-Alloy Steels, Wrought Products Except Forgings and Forging Stock
AMS 2372 - Quality Assurance Sampling of Carbon and Low-Alloy Steels, Forgings and Forging Stock
AMS 2375 - Control of Forgings Requiring First-Article Approval
AMS 2806 - Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Heat and Corrosion Resistant Steels and Alloys
AMS 2808 - Identification, Forgings
AMS 7496 - Rings, Flash Welded, Carbon and Low-Alloy Steels

2.1.2 Aerospace Standards:

AS 1182 - Standard Machining Allowance, Aircraft Quality and Premium Quality Steel Products

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM A370 - Mechanical Testing of Steel Products
ASTM A604 - Macroetch Testing of Consumable Electrode Remelted Steel Bars and Billets
ASTM E45 - Determining the Inclusion Content of Steel
ASTM E112 - Determining Average Grain Size
ASTM E353 - Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys
ASTM E399 - Plane-Strain Fracture Toughness of Metallic Materials

2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Military Standards:

MIL-STD-163 - Steel Mill Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

- 3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E353 or by spectrographic or other analytical methods approved by purchaser:

Ø

	min	max
Carbon	--	0.03
Manganese	--	0.10
Silicon	--	0.10
Phosphorus	--	0.010
Sulfur	--	0.010
Nickel	17.00 - 19.00	
Cobalt	7.00 - 8.50	
Molybdenum	4.60 - 5.20	
Titanium	0.30 - 0.50	
Aluminum	0.05 - 0.15	
Chromium	--	0.50
Copper	--	0.50

- 3.1.1 Additives: Prior to pouring, up to 0.05% calcium, 0.02% zirconium, and 0.003% boron shall be added to the air melted heat; analysis for these elements need not be made.

- 3.1.2 Check Analysis: Composition variations shall meet the requirement of AMS 2248.

- 3.2 Condition: The product shall be supplied in the following condition:

- 3.2.1 Bars, Forgings, Mechanical Tubing, and Flash Welded Rings: Annealed and descaled.

- 3.2.1.1 Flash welded rings shall not be supplied unless specified or permitted on purchaser's part drawing. When supplied, they shall be manufactured in accordance with AMS 7496.

- 3.2.2 Stock for Forging or Flash Welded Rings: As ordered by the forging or flash welded ring manufacturer.

- 3.3 Heat Treatment: Bars, forgings, mechanical tubing, and flash-welded rings shall be annealed by heating to a temperature within the range 1500° - 1700°F (815° - 925°C), holding at the selected temperature within ±25°F (±15°C) for 1 - 2 hr, and cooling in air to room temperature.

- 3.4 Properties: The product shall conform to the following requirements; hardness and tensile testing shall be performed in accordance with ASTM A370:

- 3.4.1 Heat of Steel:

- 3.4.1.1.1 Micro-Inclusion Rating: No specimen from 4.3.3 shall exceed the following limits, determined in accordance with ASTM E45, Method D:

Type	Inclusion Rating				
	A	B	C	D	E
Thin	1.5	1.5	1.5	2.0	3.0
Heavy	1.0	1.0	1.0	1.5	1.5

- 3.4.1.1.1 Type E (titanium nitrides) shall be rated in the same manner as Type B.

- 3.4.1.2 Macrostructure: Visual examination of transverse sections as in 4.3.4 from bars, billets, tube rounds or tubes, and stock for forgings or flash welded rings, etched in accordance with ASTM A604 in a suitable etchant for sufficient time to develop a well-defined macrostructure, shall show no pipe or cracks. Except as specified in 3.4.1.2.1, porosity, segregation, inclusions and other imperfections for product 36 sq in. (230 cm²) and under in nominal cross-sectional area shall be no worse than the following macrographs of ASTM A604; macrostructure standards for product over 36 sq in. (230 cm²) in nominal cross-sectional area shall be as agreed upon by purchaser and vendor:

Class	Condition	Severity
1	Freckles	A
2	White Spots	A
3	Radial Segregation	B
4	Ring Pattern	B

- 3.4.1.2.1 If tubes are produced directly from ingots or large blooms, transverse sections may be taken from tubes rather than tube rounds. Macrostructure standards for such tubes shall be as agreed upon by purchaser and vendor.

3.4.2 Bars, Forgings, Tubing, and Flash Welded Rings:

3.4.2.1 As Annealed:

- 3.4.2.1.1 Hardness: Bars over 0.500 in. (12.50 mm) in nominal diameter or distance between parallel sides, forgings, tubing, and flash welded rings shall have hardness not higher than 321 HB or equivalent.
- 3.4.2.1.2 Tensile Strength: Bars 0.500 in. (12.50 mm) and under in nominal diameter or distance between parallel sides shall have tensile strength not higher than 160,000 psi (1105 MPa) or equivalent hardness.
- 3.4.2.1.3 Grain Size: Shall be as follows, determined in accordance with ASTM E112; the procedure used shall be as agreed upon by purchaser and vendor:

- 3.4.2.1.3.1 Product Under 2.50 In. (62.5 mm) in Nominal Section Thickness: Predominantly 6 or finer with occasional grains as large as 4 permissible.
- 3.4.2.1.3.2 Product 2.50 to 10.00 In. (62.5 to 250.0 mm), Incl, in Nominal Section Thickness: Predominantly 4 or finer with occasional grains as large as 2 permissible.
- 3.4.2.1.3.3 Product Over 10.00 In. (250.0 mm) in Section Thickness: As agreed upon by purchaser and vendor.
- 3.4.2.2 Maraging Heat Treatment: Specimens shall have the following properties
Ø after being maraged by heating to $900^{\circ}\text{F} \pm 10$ ($480^{\circ}\text{C} \pm 5$), holding at heat for 6 hr ± 0.5 , and cooling in air to room temperature:
- 3.4.2.2.1 Tensile Properties: Shall be as specified in Table I and 3.4.2.2.1.1.

SAENORM.COM : Click to view the full PDF of AMS 6512B

TABLE I

Nominal Section Thickness Inches	Specimen Orientation	Tensile Strength psi, min	Yield Strength at 0.2% Offset psi, min	Elongation in 4D , min	Reduction of Area , min
Up to 4.000, excl	Longitudinal	255,000	250,000	6	45
	Transverse	255,000	250,000	4	35
4.000 to 10.000, incl	Longitudinal	245,000	240,000	5	30
	Transverse	245,000	240,000	3	20

TABLE I (SI)

Nominal Section Thickness Millimetres	Specimen Orientation	Tensile Strength MPa, min	Yield Strength at 0.2% Offset MPa, min	Elongation in 4D , min	Reduction of Area , min
Up to 100.00, excl	Longitudinal	1760	1725	6	45
	Transverse	1760	1725	4	35
100.00 to 250.00, incl	Longitudinal	1690	1655	5	30
	Transverse	1690	1655	3	20

- 3.4.2.2.1.1 Tensile property requirements for product over 10.000 in. (250.00 mm) in nominal section thickness shall be as agreed upon by purchaser and vendor.
- 3.4.2.2.1.2 Longitudinal requirements apply to specimens taken with axis of specimens approximately parallel to the grain flow and to specimens taken in the radial direction and in the tangential direction at the rim of disc forgings. All other specimens shall be considered to be in the transverse direction.
- 3.4.2.2.1.3 Transverse test requirements apply only to product from which tensile specimens not less than 2.50 in. (62.5 mm) in length can be taken.
- 3.4.2.2.1.4 Tensile properties in the longitudinal direction need not be determined on product tested in the transverse direction.
- 3.4.2.2.2 Hardness: Should be not lower than 48 HRC, or equivalent, but the product shall not be rejected on the basis of hardness if the tensile property requirements are met.
- 3.4.2.2.3 Fracture Toughness: When specified, product shall be subjected to fracture toughness testing in accordance with ASTM E399. Acceptance standards shall be as agreed upon between purchaser and vendor.
- 3.4.3 Forging Stock: When a sample of stock is forged to a test coupon and heat treated as in 3.3 and 3.4.2.2, specimens taken from the heat treated coupon shall conform to the requirements of 3.4.2.2.1, 3.4.2.2.2, and, when specified, 3.4.2.2.3. If specimens taken from the stock after heat treatment as in 3.3 and 3.4.2.2 conform to the requirements of 3.4.2.2.1, 3.4.2.2.2, and, when specified, 3.4.2.2.3, the tests shall be accepted as equivalent to tests of a forged coupon.
- 3.4.4 Stock for Flash Welded Rings: Specimens taken from the stock after heat treatment as in 3.3 and 3.4.2.2 shall conform to the requirements of 3.4.2.2.1, 3.4.2.2.2, and, when specified, 3.4.2.2.3.
- 3.5 Quality:
- 3.5.1 Steel shall be premium aircraft quality conforming to AMS 2300 or MAM 2300. It shall be produced by multiple melting using vacuum consumable electrode practice in the remelt cycle.
- 3.5.2 The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.
- 3.5.2.1 Bars, tubing, and flash welded rings ordered ground, turned, or polished shall be free from seams, laps, tears, and cracks open to the ground, turned, or polished surfaces.

AMS 6512B

3.5.2.2 Product ordered to surface conditions other than ground, turned, or polished shall, after removal of the standard machining allowance, be free from seams, laps, tears, cracks, and other defects exposed to the machined surfaces. Standard machining allowance shall be in accordance with AS 1182.

3.5.3 Grain flow of die forgings, except in areas which contain end grain, shall follow the general contour of the forging and shall show no evidence of re-entrant flow. Standards for acceptance shall be as agreed upon by purchaser and vendor.

3.6 Sizes: Except when exact lengths or multiples of exact lengths are ordered, straight bars and tubing will be acceptable in mill lengths of 6 - 20 ft (2 - 6 m) but not more than 10% of any shipment shall be supplied in lengths shorter than 10 ft (3 m).

3.7 Tolerances: Shall conform to all applicable requirements of the following:

3.7.1 Bars: AMS 2251 or MAM 2251.

3.7.2 Mechanical Tubing: AMS 2253 or MAM 2253.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.5. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests to determine conformance to the following requirements are classified as acceptance tests and shall be performed on each heat or lot as applicable.

4.2.1.1 Composition (3.1), micro-inclusion rating (3.4.1.1), macrostructure (3.4.1.2), and frequency-severity cleanliness rating (3.5.1) of each heat.

4.2.1.2 Hardness (3.4.2.1.1) of each lot of bars, forgings, tubing, and flash welded rings as annealed and tensile strength (3.4.2.1.2) of each lot of bars as annealed.

4.2.1.3 Grain size (3.4.2.1.3) of each lot of bars, forgings, tubing, and flash welded rings as annealed.

4.2.1.4 Tensile properties (3.4.2.2.1), hardness (3.4.2.2.2), and, when specified, fracture toughness (3.4.2.2.3) of each lot of bars, forgings, tubing, and flash welded rings after maraging heat treatment.