

# AEROSPACE MATERIAL SPECIFICATION



**AMS 6524E**

|                       |          |
|-----------------------|----------|
| Issued                | NOV 1970 |
| Revised               | OCT 1991 |
| Noncurrent            | SEP 1996 |
| Cancelled             | APR 2003 |
| Superseding AMS 6524D |          |

Steel, Sheet, Strip, and Plate  
1.0Cr - 7.5Ni - 4.5Co - 1.0Mo - 0.09V (0.29 - 0.34C)  
Consumable Electrode Vacuum Melted, Annealed  
(Composition similar to UNS K91313)

## CANCELLATION NOTICE

This specification has been "CANCELLED" by the Aerospace Materials Division, SAE, as of April, 2003. By this action, this document will remain listed in the Numerical Section of the Index of Aerospace Material Specifications.

Cancelled specifications are available from SAE.

SAENORM.COM : Click to view the full PDF of AMS 6524E

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2003 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

**TO PLACE A DOCUMENT ORDER:**    **Tel:**        **877-606-7323 (inside USA and Canada)**  
                                                 **Tel:**        **724-776-4970 (outside USA)**  
                                                 **Fax:**        **724-776-0790**  
                                                 **Email:**      **custsvc@sae.org**  
**SAE WEB ADDRESS:**                **http://www.sae.org**

## 1. SCOPE:

### 1.1 Form:

This specification covers a premium aircraft-quality, low-alloy steel in the form of sheet, strip, and plate.

### 1.2 Application:

These products have been used typically for parts, such as pressure vessels, requiring through-hardening to high strength levels and where such parts may require welding during fabrication, but usage is not limited to such applications.

## 2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

### 2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

|          |                                                                                                                                       |
|----------|---------------------------------------------------------------------------------------------------------------------------------------|
| AMS 2252 | Tolerances, Low-Alloy Steel Sheet, Strip, and Plate                                                                                   |
| MAM 2252 | Tolerances, Metric, Low-Alloy Steel Sheet, Strip, and Plate                                                                           |
| AMS 2259 | Chemical Check Analysis Limits, Wrought Low-Alloy and Carbon Steels                                                                   |
| AMS 2300 | Premium Aircraft-Quality Steel Cleanliness, Magnetic Particle Inspection Procedure                                                    |
| MAM 2300 | Premium Aircraft-Quality Steel Cleanliness, Magnetic Particle Inspection Procedure, Metric (SI) Measurement                           |
| AMS 2370 | Quality Assurance Sampling and Testing of Carbon and Low-Alloy Steels, Wrought Products and Forging Stock                             |
| AMS 2807 | Identification, Carbon and Low-Alloy Steels, Corrosion and Heat Resistant Steels and Alloys, Sheet, Strip, Plate, and Aircraft Tubing |

### 2.2 ASTM Publications:

Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

|            |                                                                                                            |
|------------|------------------------------------------------------------------------------------------------------------|
| ASTM A 370 | Mechanical Testing of Steel Products                                                                       |
| ASTM A 604 | Macroetch Testing of Consumable Electrode Remelted Steel Bars and Billets                                  |
| ASTM E 45  | Determining the Inclusion Content of Steel                                                                 |
| ASTM E 112 | Determining Average Grain Size                                                                             |
| ASTM E 338 | Sharp-Notch Tension Testing of High-Strength Sheet Materials                                               |
| ASTM E 350 | Chemical Analysis of Carbon Steel, Low-Alloy Steel, Silicon Electrical Steel, Ingot Iron, and Wrought Iron |
| ASTM E 399 | Plane-Strain Fracture Toughness of Metallic Materials                                                      |

## 2.3 U.S. Government Publications:

Available from Standardization Documents Order Desk, Building 4D, 700 Robbins Avenue,  
Philadelphia, PA 19111-5094.

MIL-STD-163 Steel Mill Products, Preparation for Shipment and Storage

## 3. TECHNICAL REQUIREMENTS:

## 3.1 Composition:

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 350, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

| Element    | min  | max  |
|------------|------|------|
| Carbon     | 0.29 | 0.34 |
| Manganese  | 0.10 | 0.35 |
| Silicon    | --   | 0.20 |
| Phosphorus | --   | 0.01 |
| Sulfur     | --   | 0.01 |
| Chromium   | 0.90 | 1.10 |
| Nickel     | 7.00 | 8.00 |
| Cobalt     | 4.25 | 4.75 |
| Molybdenum | 0.90 | 1.10 |
| Vanadium   | 0.06 | 0.12 |
| Copper     | --   | 0.35 |

3.1.1 Check Analysis: Composition variations shall meet the applicable requirements of AMS 2259.

## 3.2 Condition:

The product shall be supplied in the following condition; hardness shall be determined in accordance with ASTM A 370:

3.2.1 Sheet and Strip: Cold finished, bright or atmosphere annealed, and descaled if necessary; or hot rolled, annealed, and descaled; having hardness not higher than 36 HRC, or equivalent.

3.2.2 Plate: Hot rolled, annealed, and descaled having hardness not higher than 36 HRC, or equivalent.

3.2.3 When normalized and tempered product is ordered, hardness shall be not higher than 40 HRC, or equivalent.

## 3.3 Properties:

The product shall conform to the following requirements; tensile testing shall be performed in accordance with ASTM A 370:

- 3.3.1 Macrostructure: Visual examination of specimens, etched in hot hydrochloric acid in accordance with ASTM A 604, shall show no pipe or cracks. Porosity, segregation, inclusions, and other imperfections shall be no worse than standards agreed upon by purchaser and vendor.
- 3.3.2 Micro-Inclusion Rating: No specimen shall exceed the limits of Table 2, determined in accordance with ASTM E 45, Method D:

TABLE 2 - Micro-Inclusion Rating Limits

| Type                                          | A<br>Thin | A<br>Heavy | B<br>Thin | B<br>Heavy | C<br>Thin | C<br>Heavy | D<br>Thin | D<br>Heavy |
|-----------------------------------------------|-----------|------------|-----------|------------|-----------|------------|-----------|------------|
| Worst Field Severity                          | 1.5       | 1.0        | 1.0       | 1.0        | 1.0       | 1.0        | 1.5       | 1.0        |
| Worst Field Frequency                         | *         | 1          | *         | 1          | *         | 1          | 3         | 1          |
| Total Rateable Fields<br>Frequency, maximum   | **        | 1          | **        | 1          | **        | 1          | 8         | 1          |
| * Combined A + B + C, not more than 3 fields  |           |            |           |            |           |            |           |            |
| ** Combined A + B + C, not more than 8 fields |           |            |           |            |           |            |           |            |

- 3.3.2.1 A rateable field is defined as one which has a type A, B, C, or D inclusion rating of at least No. 1.0 thin or heavy in accordance with the Jernkontoret Chart, Plate III, ASTM E 45.
- 3.3.3 Grain Size: Predominantly 5 or finer with occasional grains as large as 3 permissible, determined in accordance with ASTM E 112.
- 3.3.4 Decarburization:
- 3.3.4.1 Product Under 0.045 Inch (1.14 mm) in Nominal Thickness: The method of test and the allowance shall be as agreed upon by purchaser and vendor.
- 3.3.4.2 Product 0.045 to 0.375 Inch (1.14 to 9.52 mm), Exclusive, in Nominal Thickness:
- 3.3.4.2.1 Specimens: Shall be the full thickness of the product except that specimens from plate 0.250 inch (6.35 mm) and over in nominal thickness may be slices approximately 0.250 inch (6.35 mm) thick cut parallel to and preserving one original surface of the plate. Recommended specimen size is 1 x 4 inches (25 x 102 mm).

3.3.4.2.2 Procedure: Specimens shall be hardened by austenitizing and quenching; preferably, they shall not be tempered but, if tempered, the tempering temperature shall be not higher than 300°F (149°C). During heat treatment, specimens shall be protected by suitable atmosphere or medium or by suitable plating to prevent carburization or further decarburization. Protective plating, if used, shall then be removed from specimens of product 0.045 to 0.250 inch (1.14 to 6.35 mm), exclusive, in nominal thickness and a portion of the specimen shall be ground to a depth of 0.050 inch (1.27 mm) or one-half thickness, whichever is less. Specimens from product 0.250 to 0.375 inch (6.35 to 9.52 mm), exclusive, in nominal thickness shall be ground to remove 0.020 inch (0.51 mm) of metal from the original surface of the plate and a portion of the specimen shall be further ground to a depth of at least one-third the original thickness of the specimen. At least three Rockwell hardness readings shall be taken on each prepared step and each group of readings averaged.

3.3.4.2.3 Allowance:

3.3.4.2.3.1 Product 0.045 to 0.250 inch (1.14 to 6.35 mm) Exclusive in Nominal Thickness: The product shall show no layer of complete decarburization, determined microscopically at a magnification not exceeding 100X. It shall also be free from any partial decarburization to the extent that the difference in hardness between the original surface and the portion ground as in 3.3.4.2.2 shall be not greater than 2 units on the Rockwell "A" Scale.

3.3.4.2.3.2 Product 0.250 to 0.375 inch (6.35 to 9.52 mm), Exclusive, in Nominal Thickness: Shall be free from decarburization to the extent that the difference in hardness between the two prepared steps shall be not greater than 3 units on the Rockwell "A" Scale.

3.3.4.3 Product 0.375 inch (9.52 mm) and Over in Nominal Thickness: The total decarburization, determined microscopically at a magnification not exceeding 100X on the as-supplied plate, shall be not greater than shown in Table 3.

TABLE 3A - Decarburization, Maximum, Inches

| Nominal Thickness         | Depth of Decarburization |
|---------------------------|--------------------------|
| 0.375 to 0.500, incl      | 0.015                    |
| Over 0.500 to 1.000, incl | 0.025                    |
| Over 1.000 to 2.000, incl | 0.035                    |
| Over 2.000                | As agreed upon           |

TABLE 3B - Decarburization, Maximum, Millimeters

| Nominal Thickness         | Depth of Decarburization |
|---------------------------|--------------------------|
| 9.52 to 12.70, incl       | 0.38                     |
| Over 12.70 to 25.40, incl | 0.64                     |
| Over 25.40 to 50.80, incl | 0.89                     |
| Over 50.80                | As agreed upon           |

3.3.5 Properties After Heat Treatment: Product shall meet the following requirements after being normalized by heating to  $1650^{\circ}\text{F} \pm 25$  ( $899^{\circ}\text{C} \pm 14$ ), holding at heat for 1 hour per inch (25 mm) of maximum cross-section, and cooling in air to room temperature; hardened by heating to  $1550^{\circ}\text{F} \pm 25$  ( $843^{\circ}\text{C} \pm 14$ ), holding at heat for 1 hour per inch (25 mm) of maximum cross-section but not less than 1 hour, and quenching in oil or water; cooling to  $-100^{\circ}\text{F} \pm 10$  ( $-73^{\circ}\text{C} \pm 6$ ), holding at  $-100^{\circ}\text{F} \pm 10$  ( $-73^{\circ}\text{C} \pm 6$ ) for not less than 2 hours, warming to room temperature; and double tempered by heating to  $975^{\circ}\text{F} \pm 15$  ( $524^{\circ}\text{C} \pm 8$ ), holding at heat for 2 hours per inch (25 mm) of maximum cross-section but not less than 2 hours, cooling to approximately  $125^{\circ}\text{F}$  ( $52^{\circ}\text{C}$ ), reheating to  $975^{\circ}\text{F} \pm 15$  ( $524^{\circ}\text{C} \pm 8$ ), holding at heat for 2 hours per inch (25 mm) of maximum cross-section but not less than 2 hours, and cooling in air to room temperature.

3.3.5.1 Tensile Properties: Shall be as specified in Table 4.

TABLE 4A - Tensile Properties

| Nominal Thickness<br>Inches | Tensile<br>Strength<br>ksi, min | Yield Strength<br>at 0.2% Offset<br>ksi, min | Elongation in<br>2 Inches or 4D<br>%, min | Reduction<br>of Area<br>%, min |
|-----------------------------|---------------------------------|----------------------------------------------|-------------------------------------------|--------------------------------|
| Up to 0.250, excl           | 220                             | 185                                          | 6                                         | --                             |
| 0.250 and over              | 220                             | 190                                          | 10                                        | 35                             |

TABLE 4B - Tensile Properties (SI)

| Nominal Thickness<br>Millimeters | Tensile<br>Strength<br>MPa, min | Yield Strength<br>at 0.2% Offset<br>MPa, min | Elongation in<br>50.8 mm or 4D<br>%, min | Reduction<br>of Area<br>%, min |
|----------------------------------|---------------------------------|----------------------------------------------|------------------------------------------|--------------------------------|
| Up to 6.35, excl                 | 1517                            | 1276                                         | 6                                        | --                             |
| 6.35 and over                    | 1517                            | 1310                                         | 10                                       | 35                             |

3.3.5.2 Hardness: Should be not lower than 46 HRC, or equivalent, but the product shall not be rejected on the basis of hardness if the tensile property requirements of 3.3.5.1 are met.

3.3.5.3 Fracture Toughness: When specified, the product shall be subjected to fracture toughness testing and the results reported. Sheet and strip shall be tested in accordance with ASTM E 338 and plate shall be tested in accordance with ASTM E 399. Acceptance standards shall be as agreed upon by purchaser and vendor.

3.4 Quality:

3.4.1 Steel shall be premium aircraft-quality conforming to AMS 2300 or MAM 2300. It shall be multiple melted using consumable electrode vacuum practice in the remelt cycle.

3.4.2 The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

### 3.5 Tolerances:

Shall conform to all applicable requirements of AMS 2252 or MAM 2252.

## 4. QUALITY ASSURANCE PROVISIONS:

### 4.1 Responsibility for Inspection:

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

### 4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests for composition (3.1), condition (3.2), macrostructure (3.3.1), micro-inclusion rating (3.3.2), grain size (3.3.3), decarburization (3.3.4), frequency-severity cleanliness rating (3.4.1), and tolerances (3.5) are acceptance tests and shall be performed on each heat or lot as applicable.

4.2.2 Periodic Tests: Tests for response to heat treatment (3.3.5) are periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

### 4.3 Sampling and Testing:

Shall be in accordance with AMS 2370; a heat shall be the consumable electrode remelted ingots produced from steel originally melted as a single furnace charge:

### 4.4 Reports:

The vendor of the product shall furnish with each shipment a report showing the results of tests for chemical composition, macrostructure, micro-inclusion rating, grain size, and frequency-severity cleanliness rating of each heat and, when performed, to the periodic test requirements. This report shall include the purchase order number, lot number, AMS 6524E, size, and quantity.

### 4.5 Resampling and Retesting:

Shall be in accordance with AMS 2370.

## 5. PREPARATION FOR DELIVERY:

### 5.1 Identification:

Shall be in accordance with AMS 2807.