



# AEROSPACE MATERIAL SPECIFICATION

**AMS6910™****REV. D**Issued 2004-01  
Revised 2022-08

Superseding AMS6910C

Titanium Alloy Bars, Forgings and Forging Stock  
8Al - 1Mo - 1V  
Duplex Annealed  
(Composition similar to UNS R54810)

## RATIONALE

AMS6910D results from a Five-Year Review and update of this specification with changes to update wording to prohibit unauthorized exceptions (3.5.1.1.5, 8.5), relocate definitions (2.3) and information regarding data and statistical analysis (3.5.1.1.6), update applicable documents (Section 2), and ordering information (8.6).

## 1. SCOPE

### 1.1 Form

This specification covers a titanium alloy in the form of bars up through 4.000 inches (101.60 mm), inclusive, in nominal diameter or least distance between parallel sides, forgings of thickness up through 4.000 inches (101.60 mm), inclusive, and stock for forging of any size (see 8.6).

### 1.2 Application

This alloy has been used typically for parts requiring strength up to 800 °F (427 °C), but usage is not limited to such applications.

1.2.1 Certain processing procedures and service conditions may cause these products to become subject to stress-corrosion cracking; ARP982 recommends practices to minimize such conditions.

## 2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

### 2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or +1 724-776-4970 (outside USA), [www.sae.org](http://www.sae.org).

AMS2241 Tolerances, Corrosion- and Heat-Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Bars and Wire

AMS2249 Chemical Check Analysis Limits, Titanium and Titanium Alloys

SAE Executive Standards Committee Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2022 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

**TO PLACE A DOCUMENT ORDER:** Tel: 877-606-7323 (inside USA and Canada)  
Tel: +1 724-776-4970 (outside USA)  
Fax: 724-776-0790  
Email: [CustomerService@sae.org](mailto:CustomerService@sae.org)  
http://www.sae.org

SAE WEB ADDRESS:

**For more information on this standard, visit**  
<https://www.sae.org/standards/content/AMS6910D/>

|         |                                                                                          |
|---------|------------------------------------------------------------------------------------------|
| AMS2368 | Sampling and Testing of Wrought Titanium Raw Material, Except Forgings and Forging Stock |
| AMS2631 | Ultrasonic Inspection, Titanium and Titanium Alloy Bar, Billet and Plate                 |
| AMS2643 | Structural Examination of Titanium Alloys, Chemical Etch Inspection Procedure            |
| AMS2750 | Pyrometry                                                                                |
| AMS2808 | Identification, Forgings                                                                 |
| AMS2809 | Identification, Titanium and Titanium Alloy Wrought Products                             |
| ARP982  | Minimizing Stress-Corrosion Cracking in Wrought Titanium Alloy Products                  |
| AS1814  | Terminology for Titanium Microstructures                                                 |
| AS6279  | Standard Practice for Production, Distribution, and Procurement of Metal Stock           |
| AS7766  | Terms Used in Aerospace Metals Specifications                                            |

## 2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, [www.astm.org](http://www.astm.org).

### ASTM E8/E8M Tension Testing of Metallic Materials

|            |                                                                                                                                                                    |
|------------|--------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| ASTM E539  | Analysis of Titanium Alloys by Wavelength Dispersive X-Ray Fluorescence Spectrometry                                                                               |
| ASTM E1409 | Determination of Oxygen and Nitrogen in Titanium and Titanium Alloys by Inert Gas Fusion                                                                           |
| ASTM E1447 | Determination of Hydrogen in Titanium and Titanium Alloys by Inert Gas Fusion Thermal Conductivity/Infrared Detection Method                                       |
| ASTM E1941 | Determination of Carbon in Refractory and Reactive Metals and Their Alloys by Combustion Analysis                                                                  |
| ASTM E2371 | Analysis of Titanium and Titanium Alloys by Direct Current Plasma and Inductively Coupled Plasma Atomic Emission Spectrometry (Performance-Based Test Methodology) |
| ASTM E2994 | Analysis of Titanium and Titanium Alloys by Spark Atomic Emission Spectrometry and Glow Discharge Atomic Emission Spectrometry (Performance-Based Method)          |

## 2.3 Definitions

Terms used in AMS are defined in AS7766.

### 2.3.1 Terminology relating to titanium microstructures is presented in AS1814.

## 3. TECHNICAL REQUIREMENTS

### 3.1 Composition

Shall conform to the percentages by weight shown in Table 1; carbon shall be determined in accordance with ASTM E1941, hydrogen in accordance with ASTM E1447, oxygen and nitrogen in accordance with ASTM E1409, and other elements in accordance with ASTM E539, ASTM E2371, or ASTM E2994. Other analytical methods may be used if acceptable to the purchaser.

**Table 1 - Composition**

| Element                       | Min       | Max             |
|-------------------------------|-----------|-----------------|
| Aluminum                      | 7.35      | 8.35            |
| Molybdenum                    | 0.75      | 1.25            |
| Vanadium                      | 0.75      | 1.25            |
| Iron                          | --        | 0.30            |
| Oxygen                        | --        | 0.15            |
| Carbon                        | --        | 0.08            |
| Nitrogen                      | --        | 0.05 (500 ppm)  |
| Hydrogen                      | --        | 0.015 (150 ppm) |
| Yttrium (3.1.1)               | --        | 0.005 ( 50 ppm) |
| Other Elements, each (3.1.1)  | --        | 0.10            |
| Other Elements, total (3.1.1) | --        | 0.40            |
| Titanium                      | remainder |                 |

3.1.1 Determination not required for routine acceptance.

3.1.2 Check Analysis

Composition variations shall meet the applicable requirements of AMS2249.

3.2 Melting Practice

Alloy shall be multiple melted. The first melt shall be made by vacuum consumable electrode, nonconsumable electrode, electron beam cold hearth, or plasma arc cold hearth melting practice. The subsequent melt or melts shall be made using vacuum arc remelting (VAR) practice. Alloy additions are not permitted in the final melt cycle.

3.2.1 The atmosphere for nonconsumable electrode melting shall be vacuum or shall be argon or helium at an absolute pressure not higher than 1000 mm of mercury.

3.2.2 The electrode tip for nonconsumable electrode melting shall be water-cooled copper.

3.3 Condition

The product shall be supplied in the following condition:

3.3.1 Bars

Hot finished with or without subsequent cold reduction, duplex annealed, and descaled. A machined or ground surface is permitted unless prohibited by the purchaser. The product shall be processed to the final thickness/diameter by metallurgical working operations prior to any straightening, dimensional sizing, or surface finishing operations. Bar shall not be cut from plate.

3.3.2 Forgings

Duplex annealed and descaled.

3.3.3 Stock for Forging

As ordered by the forging manufacturer.

3.4 Heat Treatment

Bars and forgings shall be duplex annealed as follows: Pyrometry shall be in accordance with AMS2750.

### 3.4.1 Solution Heat Treatment

Heat to a temperature within the range 1650 to 1850 °F (899 to 1010 °C), hold at the selected temperature within  $\pm 25$  °F ( $\pm 14$  °C) for time commensurate with section thickness and the heating equipment and procedure used, and cool at a rate equivalent to an air cool or faster.

### 3.4.2 Stabilization Heat Treatment

Heat to 1100 °F  $\pm$  25 °F (595 °C  $\pm$  14 °C), hold for not less than 8 hours, and cool at a rate equivalent to air cooling.

## 3.5 Properties

The product shall conform to the following requirements:

### 3.5.1 Bars and Forgings

#### 3.5.1.1 Tensile Properties

Shall be as specified in Table 2, determined in accordance with ASTM E8/E8M with the rate of strain set at 0.005 in/in/min (0.005 mm/mm/min) and maintained within a tolerance of  $\pm 0.002$  in/in/min (0.002 mm/mm/min) through the 0.2% offset yield strain.

3.5.1.1.1 Tensile property requirements apply in both the longitudinal and transverse directions. Transverse tensile properties of Table 2 apply only to product that a test specimen not less than 2.50 inches (63.5 mm) in length can be obtained.

3.5.1.1.2 Specimens for the longitudinal requirements in Table 2 shall be taken with the axis of the specimen within 15 degrees of parallel to the grain flow.

3.5.1.1.3 Yield strength and reduction of area requirements do not apply to product under 0.125 inch (3.18 mm) in nominal diameter.

3.5.1.1.4 Values in brackets [ ] apply to the short transverse direction for short transverse dimensions of 3.00 inches or greater. When short transverse properties are determined, long transverse properties do not need to be determined.

**Table 2 - Minimum tensile properties (see 8.2)**

| Nominal Diameter or<br>Least Distance Between<br>Parallel Sides<br>Inches (mm) | Tensile<br>Strength<br>ksi (MPa) | Yield Strength<br>at 0.2% Offset<br>ksi (MPa) | Elongation in<br>2 Inches (50.8 mm)<br>or 4D, %<br>(3.5.1.1.4) | Reduction of<br>Area<br>%<br>(3.5.1.1.4) |
|--------------------------------------------------------------------------------|----------------------------------|-----------------------------------------------|----------------------------------------------------------------|------------------------------------------|
| Up to 2.500 (63.50), incl                                                      | 130 (896)                        | 120 (827)                                     | 10                                                             | 20                                       |
| Over 2.500 to 4.000<br>(63.50 to 101.60), incl                                 | 120 (827)                        | 110 (758)                                     | 10 [8]                                                         | 20 [15]                                  |

3.5.1.1.5 Mechanical property requirements for product outside the size range covered by Table 2 shall be agreed upon between purchaser and producer and reported per 4.4.3 (see 8.6).

3.5.1.1.6 The mechanical properties for product through 4.00 inches (101.60 mm) have been taken from MIL-T-9047 and have not been substantiated by AMS statistical procedures.

#### 3.5.1.2 Microstructure

Shall be that structure resulting from processing within the alpha-beta phase field. Microstructure shall conform to 3.5.1.2.1 or 3.5.1.2.2 (see 2.3.1).

3.5.1.2.1 Equiaxed and/or elongated primary alpha in a transformed beta matrix with no continuous network of alpha at prior beta grain boundaries.

3.5.1.2.2 Essentially complete field of equiaxed and/or elongated alpha with or without intergranular beta and with no continuous network of alpha at prior beta grain boundaries.

### 3.5.1.3 Surface Contamination

Except as specified in 3.5.1.3.1, the product shall be free of any oxygen-rich layer (see 8.2), such as alpha case, or other surface contamination, determined by microscopic examination at not lower than 400X magnification or by other method agreed upon by purchaser and producer.

3.5.1.3.1 When permitted by purchaser, product to be machined all over may have an oxygen-rich layer, provided such layer is removable within the machining allowance on the product.

### 3.5.1.4 Macrostructure

Product shall be uniform in quality and condition, homogenous, sound, and free from foreign materials and from internal imperfections detrimental to fabrication or performance of parts.

3.5.2 When a sample of stock is forged to a test coupon and heat treated as in 3.4, specimens taken from the heat-treated coupon shall conform to the requirements of 3.5.1.1. If specimens taken from the stock after heat treatment as in 3.4 conform to the requirements of 3.5.1.1, the tests shall be accepted as equivalent to tests of a forged coupon.

## 3.6 Quality

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

### 3.6.1 Ultrasonic Inspection

Product 0.500 inch (12.70 mm) to 1.500 inches (38.10 mm) inclusive in nominal thickness, diameter or distance between parallel sides shall meet Class A1 requirements of AMS2631. Product over 1.500 inches (38.10 mm) in nominal thickness, diameter or distance between parallel sides shall meet Class A requirements of AMS2631.

### 3.7 Tolerances

Bars shall conform to all applicable requirements of AMS2241.

3.8 Production, distribution, and procurement of metal stock shall comply with AS6279.

### 3.9 Exceptions

Any exceptions shall be authorized by purchaser and reported as in 4.4.4.

## 4. QUALITY ASSURANCE PROVISIONS

### 4.1 Responsibility for Inspection

The producer of the product shall supply all samples for producer's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the specified requirements.

### 4.2 Classification of Tests

#### 4.2.1 Acceptance Tests

The following requirements are acceptance tests and shall be performed on each heat or lot as applicable.

4.2.1.1 Composition (3.1) of each heat.

4.2.1.2 Hydrogen content (3.1), tensile properties (3.5.1.1), microstructure (3.5.1.2), surface contamination (3.5.1.3), and macrostructure (3.5.1.4), of each lot of bars and forgings.

4.2.1.3 Ultrasonic quality (3.6.1) of each bar, forging, or forging stock as required by 3.6.1.

4.2.1.4 Tolerances (3.7) of bars.

#### 4.2.2 Periodic Tests

Ability of forging stock (3.5.2) to develop specified properties is a periodic test and shall be performed at a frequency selected by the producer unless frequency of testing is specified by purchaser.

#### 4.3 Sampling and Testing

Shall be in accordance with AMS2368 and as follows: A lot shall be all product of the same nominal size from the same heat processed at the same time.

##### 4.3.1 For Acceptance Tests

###### 4.3.1.1 Composition

At least one sample from each heat, except that for hydrogen determinations, one sample from each lot obtained after all thermal and chemical processing is completed.

###### 4.3.1.2 Tensile Properties

At least one sample from bars from each lot. The number, location, and orientation of samples from each lot of forgings shall be as agreed upon by purchaser and producer (see 8.6).

4.3.1.3 A specimen at least 0.50 inch (12.7 mm) long by full cross-section from each end of the bars selected for sampling shall be macrostructurally examined for conformance to the quality requirements. Unless otherwise specified, macrostructural examination shall be performed in accordance with AMS2643. The number of bars selected for examination shall not be less than the amounts shown in Table 3.

**Table 3 - Number of bars selected for macrostructural examination**

| Number of Bars in Lot | Number of Bars Selected         |
|-----------------------|---------------------------------|
| 1 to 15               | 1                               |
| 16 to 50              | 2                               |
| 51 to 150             | 3                               |
| 151 to 500            | 5                               |
| Over 500              | 4 + amount shown above over 500 |

#### 4.4 Reports

4.4.1 The producer shall furnish with each shipment a report showing producer identity, country where the metal was melted (i.e., final melt in the case of metal processed by multiple melting operations), results of tests for chemical composition of each heat and for the hydrogen content, tensile properties, microstructure, and surface contamination of each lot; ultrasonic quality of all product, when required; and state that the product conforms to the other technical requirements. The report shall include the purchase order number, heat and lot numbers, AMS6910D, product form, mill produced size (and/or part number, if applicable), specific annealing treatment used, and quantity. If forgings are supplied, the size and melt source of stock used to make the forgings shall also be included.

4.4.2 Report the nominal metallurgically worked cross sectional size and the cut size, if different (3.3.1).