

RINGS, SEALING, PHOSPHONITRILIC FLUOROELASTOMER
High-Temperature-Fluid Resistant
FZ Type

1. SCOPE:

1.1 Form: This specification and its associated detail specifications cover phosphonitrilic fluoroelastomers in the form of molded rings.

1.2 Application: Sealing rings for use in aircraft fuel and lubricating oil systems operating from -55° to +175°C (-65° to +350°F). The cross section of such rings is usually not over 0.275 in. (7.0 mm) in diameter or thickness. Standard sizes are as shown in AS 568.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS), Aerospace Standards (AS), and Aerospace Information Reports (AIR) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2350 - Standards and Test Methods

AMS 2817 - Packaging and Identification, Preformed Packings

AMS 3021 - Reference Fluid for Testing Di-Ester (Polyol) Resistant
Materials

2.1.2 Aerospace Standards:

AS 568 - Aerospace Size Standard for O-Rings

AS 871 - Manufacturing and Inspection Standards for Preformed Packings
(O-Rings)

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade or their use by governmental agencies is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

2.1.3 Aerospace Information Report:

AIR 851 - O-Ring Tension Testing Calculations

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM D471 - Rubber Property - Effect of Liquids

ASTM D1414 - Testing Rubber O-Rings

ASTM D2240 - Rubber Property - Durometer Hardness

2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Military Standards:

MIL-STD-413 - Visual Inspection Guide for Rubber O-Rings

3. TECHNICAL REQUIREMENTS:

- 3.1 Detail Specifications: The requirements for a specific material shall consist of all the requirements specified herein in addition to the requirements specified in the applicable detail specification. In case of any conflict between the requirements of this basic specification and an applicable detail specification, the requirements of the detail specification shall govern.
- 3.2 Material: Shall be a compound based on a phosphonitrilic fluoroelastomer, suitably cured to produce rings meeting the requirements of this specification and the applicable detail specification.
- 3.3 Properties: Rings shall conform to the requirements of the applicable detail specification; tests shall be performed on the rings supplied and in accordance with ASTM D1414, insofar as practicable. Testing for tensile strength is not required on rings which are too small to permit assembly on rollers and are, after cutting, too short to permit testing as a single strand. Eliminating testing for tensile strength does not eliminate testing for elongation; elongation test can be made by stretching a ring over a mandrel of a size which will stretch the ring sufficiently to produce the required elongation when figured on the ID of the ring. Calculations of tensile strength and elongation may be made in accordance with AIR 851.
- 3.4 Quality: Rings, as received by purchaser, shall be uniform in quality and condition, clean, smooth, as free from foreign material as commercially practicable, and free from internal imperfections detrimental to their performance. Surface imperfections shall, unless otherwise specified, be no greater than permitted by MIL-STD-413.
- 3.5 Sizes and Tolerances: Shall be as specified on the drawing. Inspection for conformance to dimensional requirements shall be made in accordance with AS 871, unless otherwise agreed upon by purchaser and vendor.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of rings shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.5. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the rings conform to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests to determine conformance to requirements for quality (3.4) and to the following requirements of the applicable detail specification are classified as acceptance tests and shall be performed on each lot:

Requirement	Paragraph Reference
Hardness, as received	3.2.1.1
Tensile Strength, as received	3.2.1.2
Elongation, as received	3.2.1.3
Specific Gravity, as received	3.2.1.4
Volume Change in fuel	3.2.2.4
Compression Set	3.2.5.1

4.2.2 Preproduction Tests: Tests to determine conformance to all technical requirements of this specification and the applicable detail specification are classified as preproduction tests and shall be performed prior to or on the initial shipment of rings to a purchaser, when a change in material or processing, or both, requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.

4.2.2.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction rings shall be submitted to the cognizant agency as directed by the procuring activity, the contracting officer, or the request for procurement.

4.3 Sampling:

4.3.1 For Acceptance Tests: Sufficient rings shall be selected at random from each lot to perform all required tests. The number of tests for each requirement shall be as specified in the applicable test procedure or, if not specified therein, not less than three.

4.3.1.1 A lot shall be all rings of the same nominal size produced from the same batch of compound processed in one continuous series of operations and presented for vendor's inspection at one time but shall not exceed 1000 rings or 300 lb (135 kg), whichever is the lesser mass. A lot may be packaged in small quantities under a basic lot approval provided lot identification is maintained.

4.3.1.2 A batch shall be the quantity of compound run through a mill or mixer at one time.

4.3.1.3 When a statistical sampling plan and acceptance quality level (AQL) have been agreed upon by purchaser and vendor, sampling shall be in accordance with such plan in lieu of sampling as in 4.3.1 and the report of 4.5.1 shall state that such plan was used.

4.3.2 For Preproduction Tests: As agreed upon by purchaser and vendor. Tests, except hardness, shall be made on AS 568-214 size rings; hardness tests shall be made on specimens meeting the requirements of ASTM D2240.

4.4 Approval:

4.4.1 Sample rings shall be approved by purchaser before rings for production use are supplied, unless such approval be waived by purchaser. Results of tests on production rings shall be essentially equivalent to those on the approved sample rings.

4.4.2 Vendor shall establish for each size of ring parameters for the process control factors which will produce rings meeting the technical requirements of this specification. These shall constitute the approved procedures and shall be used for manufacturing production rings. If necessary to make any change in parameters for the process control factors, vendor shall submit for reapproval a statement of the proposed changes in material or processing, or both, and, when requested, sample rings. Production rings incorporating the revised procedures shall not be shipped prior to receipt of reapproval.

4.4.2.1 Control factors for producing rings include, but are not limited to, the following:

Compound ingredients and proportions thereof within established limits
Sequence of mixing compound ingredients
Type of mixing equipment
Method and equipment for preparing preforms
Basic molding procedure (compression, transfer, injection)
Curing time and pressure (variations of $\pm 10\%$ are permissible)
Basic and minimum curing temperatures
Finishing methods
Methods of inspection

4.4.2.1.1 Any of the above process control factors for which parameters are considered proprietary by the vendor may be assigned a code designation. Each variation in such parameters shall be assigned a modified code designation.