



AEROSPACE MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
TWO PENNSYLVANIA PLAZA, NEW YORK, N.Y. 1000

AMS 7310E

Superseding AMS 7310D

Issued 11-1-41

Revised 5-1-69

PISTON RINGS, CAST IRON

1. **ACKNOWLEDGMENT:** A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.

2. **COMPOSITION:**

	min	max
Total Carbon	3.50	3.90
Silicon	2.20	3.10
Manganese	0.40	0.80
Phosphorus	0.30	0.80
Sulfur	--	0.13

- 2.1 Alloying elements may be added, with the approval of the purchaser, to produce a high quality iron meeting the requirements of this specification.

3. **CONDITION:** Rings shall be made from individual castings, in the as-cast condition.

4. **TECHNICAL REQUIREMENTS:**

- 4.1 **Chemical Analysis Specimens:** For carbon determinations performed on the melt, a chilled pencil type specimen is preferred but other type samples of proven accuracy are acceptable. For carbon determinations performed on castings, a solid sample cut from the casting shall be used.
- 4.2 **Hardness:** Finished rings shall have hardness of Rockwell B 97 - 104 or equivalent.
- 4.3 **Microstructure:** Shall be free from abnormal segregation. Matrices shall be essentially fine pearlite, with no appreciable amounts of massive cementite. Both phosphide eutectic and graphite shall be evenly distributed, and the latter shall be present for the most part in the form of randomly oriented flakes.
- 4.4 **Finish:** Sides of rings shall be ground or lapped. Periphery shall be turned smooth, unless otherwise specified on drawing.
- 4.5 **Circularity:** The diameter through the gap shall exceed the diameter 90 deg from the gap by not less than 0.0025 in. per inch of nominal ring diameter when finished ring is held around periphery by a flexible steel band 0.0045 - 0.0055 in. thick and of width approximately equal to that of ring, and whose inside circumference is equal to the nominal outside circumference of ring ± 0.003 inch.
- 4.6 **Light-Tightness of Periphery:** When finished ring is placed in a circular gage whose ID is equal to nominal OD of ring $+ 0.0005$ in., the portion of the periphery on each side of the gap equal to 20% of the nominal OD of the ring shall be light-tight. The space between the balance of ring periphery and ID of gage shall be not greater than 0.0005 in. at any point and not less than 85% of the periphery of the ring shall be light-tight. Intermittent or fuzzy light shall be considered the same as light-tight.